# ASSESSMENT OF THE GREENNESS OF MOLECULARLY IMPRINTED POLYMERS USED IN SAMPLE PREPARATION

Mariusz Marć, A. Martín-Esteban

 PII:
 S2772-5820(25)00020-8

 DOI:
 https://doi.org/10.1016/j.sampre.2025.100167

 Reference:
 SAMPRE 100167

To appear in:

Advances in Sample Preparation

Received date:24 January 2025Revised date:28 February 2025Accepted date:2 March 2025

Please cite this article as: Mariusz Marć, A. Martín-Esteban, ASSESSMENT OF THE GREENNESS OF MOLECULARLY IMPRINTED POLYMERS USED IN SAMPLE PREPARATION, *Advances in Sample Preparation* (2025), doi: https://doi.org/10.1016/j.sampre.2025.100167

This is a PDF file of an article that has undergone enhancements after acceptance, such as the addition of a cover page and metadata, and formatting for readability, but it is not yet the definitive version of record. This version will undergo additional copyediting, typesetting and review before it is published in its final form, but we are providing this version to give early visibility of the article. Please note that, during the production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

© 2025 Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (http://creativecommons.org/licenses/by-nc-nd/4.0/)



## Highlights

- AGREEMIP tool is used for assessing the greenness of MIP synthesis procedures
- Scores obtained clearly show that there is an abuse of the use of green-related terms
- Guidelines for greening MIPs used in sample preparation are provided
- Reduction of the amounts of toxic solvents during MIP synthesis is one of the key aspects

Journal Presson

# ASSESSMENT OF THE GREENNESS OF MOLECULARLY IMPRINTED POLYMERS USED IN SAMPLE PREPARATION

Mariusz Marć<sup>1</sup> and A. Martín-Esteban<sup>2,\*</sup>

<sup>1</sup>Department of Analytical Chemistry, Faculty of Chemistry, Gdańsk University of Technology (GUT), ul. G. Narutowicza 11/12, 80-233 Gdańsk, Poland

<sup>2</sup> Departamento de Medio Ambiente y Agronomía. INIA-CSIC. Carretera de A Coruña km. 7.5.
E-28040 Madrid. Spain.

\* Author to whom correspondence should be addressed: Phone: 34 91 347 6821; fax: 34 91 347 4008; Email: amartin@inia.csic.es

#### Abstract

It is now widely accepted that the incorporation of molecularly imprinted polymers (MIPs) into sample preparation techniques has enabled unprecedented selectivity performance of analytical methods for the determination of a wide range of analytes in biological, food and environmental samples. However, according to the Principles of Green Chemistry and the subsequent Principles of Green Sample Freparation, it is clear that MIPs are far from being considered green materials, both due to the common harmful reagents and the experimental conditions used for their synthesis. Accordingly, new greener routes for MIP synthesis have been proposed in recent years. However, although the titles of some of the published papers include terms such as 'green MIP' or 'sustainable MIP', such improved properties have only been assessed intuitively and it is therefore unclear whether such claimed green or sustainable MIPs are actually so. Therefore, in the present review, published papers using apparently green MIPs in sample preparation were evaluated using the recently developed metric tool AGREEMIP. Such a tool is based on the assessment of 12 criteria related to the greenness of the different reagents used, energy requirements and other aspects of MIP synthesis procedures. The final values of performed AGREEMIP assessment ranged from 0.28 to 0.80. The scores obtained after the

AGREEMIP assessment clearly show that, although slight improvements have been achieved in terms of greenness, there is an abuse of the use of green-related terms and further development is needed. In this context, some guidelines for greening MIPs are provided.

Keywords: Molecularly imprinted polymers; sample preparation; green metrics; AGREEMIP.

#### Glossary

µ-SPE: micro solid-phase extraction

AA: acrylic acid

APTES: (3-Aminopropyl)triethoxysilane

CE: capillary electrophoresis

DAD: diode array detector

DES: deep eutectic solvent

DMF: Dimethylformamide

EDGMA: ethylene glycol dimethacrylate

IL: ionic liquid

LPME: liquid-phase microextraction

MAA: methacrylic acid

MIP: molecularly imprinted polymer

SBSE: stir bar sorptive extraction

SPME: solid-phase microextraction

TEOS: tetraethyl orthosilicate

#### 1. Introduction

In spite of the significant development in analytical instrumentation during last decades, sample pretreatment is still unavoidable, especially in trace analysis of different analytes in complex samples, which requires the trace enrichment and clean-up of target analytes from other matrix components in a reproducible manner. In this regard, several microextraction techniques have been developed, such as solid-phase microextraction (SPME), liquid-phase microextraction (LPME), stir-bar sorptive extraction (SBSE) and micro solid-phase extraction ( $\mu$ -SPE), and all of them result appropriated for nowadays sample preparation requirements. In addition, a great variety of new sorbents (i.e. restricted access materials, carbon nanotubes, graphene, metal organic frameworks, coated magnetic nanoparticles, etc.) have been incorporated showing an excellent absorption capacity for target analytes from complex matrices [1,2]. Moreover, their "micro" nature makes them well-suited to cope with the Principles of Green Chemistry [3,4] and the Principles of Green Sample Preparation [5], since all of them allow decreasing the amount of sample and reagents. Thus, it leads to a reduction in the amount of hazardous wastes and, in general, they are suitable for the use of safer chemicals and procedures with lower energy requirements.

However, regardless of the microextraction technique chosen, the extraction process is governed by the partitioning of target analytes between the sample and an acceptor phase (liquid or stationary phase). Unfortunately, such acceptor phases roughly cover the polarity scale and thus target analytes are co-extracted with other matrix compounds, which can negatively affect the determination of analytes by current chromatographic techniques. Accordingly, in most cases, the introduction of several washing steps using harmful solvents is necessary to remove interfering compounds, thus reducing the inherent advantages of microextraction techniques. As an alternative, the use of immunosorbents [6,7], aptamers [8] and molecularly imprinted polymers (MIPs) [9,10] have been proposed as excellent materials capable of successfully

performing selective extractions. However, MIPs have some advantages in terms of stability under different experimental conditions and ease of synthesis.

For MIP synthesis, following the non-covalent approach [11], a template molecule is dissolved in a proper solvent (porogen) able to maximize intermolecular interactions with selected functional monomers in presence of a large amount of a cross-linker. Then, polymerisation takes place thermally or by UV-radiation. Once the polymer is obtained, template molecule is removed by exhaustive washing leaving cavities, complementary in size, shape and functionality, within the polymer matrix and thus able to recognize the template molecule (and related compounds) in rebinding experiments. Originally, MIP particles were used as sorbent for solid-phase extraction (SPE) and later MIP synthesis was readily adapted for the preparation of suitable formats for SPME [12,13], SBSE [14–16] and other micro-extraction techniques [17–19] and thus they are considered ideal materials for selective sample preparation.

However, from a Green Chemistry perspective, most of the reagents used for MIP synthesis are toxic and a large amount of solid or liquid waste is produced, thus posing a threat to both humans and the environment. Accordingly, in order to make MIP synthesis greener, some guidelines were recently proposed in an intuitive manner [20–23] taking into account the different steps of MIP synthesis. Among these, it is important to highlight the 14 principles of green molecular imprinting technology, represented by the acronym GREENIFICATION (Figure 1), proposed by Arabi et al. [20], which include recommendations for the green synthesis of MIPs and have been further exploited by the same authors evaluating different MIPs, so-called greenificated MIPs, whose synthesis follows one or more of the 14 proposed principles [22]. In this regard, the replacement of the typical acrylic-based monomers (i.e., acrylic acid (AA) and methacrylic acid (MAA)) by greener monomers or the use of natural polymers (biopolymers), such as chitosan, cellulose or silk fibroin, to prepare non-toxic,

biodegradable, and biocompatible MIPs have been proposed [24–27]. In addition, the use of greener solvents such as ionic liquids (ILs) [28] or deep eutectic solvents (DESs) [29,30] has been successfully employed as porogen as an alternative to conventional solvents typically used in molecular imprinting (i.e., acetonitrile, toluene). It seems obvious that greener alternatives to the synthesis of MIPs are already available, and several papers have been published in recent years claiming green synthesis of MIPs for sample preparation. However, some questions remain: are such strategies green enough? What would be the greener approach? In this regard, the main aim of this review is to assess the different strategies proposed for the green MIP synthesis using the recently proposed AGREEMIP tool [31], in order to provide to the sample preparation field with an insight into which aspects of MIP synthesis still need to be improved in order to make it truly green.

#### 2. AGREEMIP tool

As mentioned above, it is intuitively possible to design new green MIPs following the GREENIFICATION guidelines given in Figure 1, but such an approach does not allow to have a quantitative measure of the environmental impact of the different changes introduced for their synthesis. In this regard, AGREEMIP tool was recently proposed to assess and compare the greenness of MIP synthesis procedures [31]. AGREEMIP is able to produce an overall score on a scale of 0-1 by calculating the weighted average of individual scores for 12 evaluation criteria covering the different reaction mixture components, energy requirements and details of MIP synthesis procedures. The assessment can be performed using user-friendly open-source software, which can be freely downloaded from *mostwiedzy.pl/agreemip*. The result of the assessment is an easy-to-interpret pictogram showing the performance in each criterion, the weighting of the criteria and the overall performance in terms of greenness. The AGREEMIP tool, its development and detailed scoring are described elsewhere [31]. However, a summary of the 12 criteria considered is provided below for a comprehensive reading of this paper.

2.1. Criterion 1: Removal of Polymerization Inhibitors.

Removal of polymerisation inhibitors from used reagents is recommended in polymer synthesis and such a procedure may generate solid or liquid waste. Accordingly, the best scenario (and thus a score of 1) is when no waste is generated, whereas a score of 0.5 or 0.2 is assigned when solid or liquid waste is generated, respectively, since the former is easier to handle.

2.2. Criteria 2-7: Functional Monomer, Template, Cross-Linking Agent, Porogen/Solvent and Other Reagents/Adjuvants/Carriers, Core/Particle Preparation, and Surface Modification.

The different components of a typical polymerisation mixture (template, functional monomer, cross-linker and porogen) and any other reagent used are treated in the same way, but independently assigned to a single criterion. Each criterion takes into account both the quantity of the compound and its associated risk. Penalty points are assigned as a function of the hazard statements associated with each compound, as proposed by Tobiszewski et al. [32]. In general, increasing the amount of reagent and/or increasing the severity of the hazards will result in a sharp decrease in the final score for each criterion.

#### 2.3. Criterion 8: Polymerization Initiation.

Polymerisation can be initiated in a number of ways, the most common being the addition of an initiator to the polymerisation mixture, which thermally decomposes into free radicals capable of initiating the polymerisation reaction. Depending on the efficiency of the energy supplied to the system (conventional heating, sonication, microwaves, etc.), a score is assigned (the more efficient, the higher the score). Higher scores are also given if the polymerisation is initiated in a more sustainable way (i.e. UV radiation, electropolymerisation or selfpolymerisation). 2.4. Criterion 9: The Size of the Polymer Particles.

Criterion 9 relates to the size of the polymer particles obtained and is therefore linked to how the polymer is disposed of after use and the risk to the operator of being exposed to polymer particles of different sizes. In this respect, the smaller the particle size, the higher the risk of exposure to the operator and therefore the lower the score. On the other hand, a score of 1 is assigned to what is considered to be the greener solution, i.e. carrying out *in-situ* polymerisation (i.e. preparing the imprinted fibres for SPME), as the entire polymerisation mixture is used and therefore no waste is generated.

#### 2.5. Criteria 10 and 11: Template Removal

As mentioned above, in order to obtain selective binding sites within the polymer matrix, the template molecule must be removed after polymerisation. In general, template removal requires the use of large amounts of solvent and is energy consuming. Accordingly, the amount of solvent and the associated hazards are considered in Criterion 10 and scores are assigned in a similar manner as described above for Criteria 2-7. In addition, Criterion 11 relates to the removal technique. In this sense, the use of Soxhlet extraction, which requires long heating times using large amounts of organic solvents, represents the worst-case scenario and is therefore assigned a score of 0. On the other hand, the use of ultrasound or microwaves requires a shorter extraction time and consumes less energy and therefore receives a score of 1.

#### 2.6. Criterion 12: Final Product Reusability.

Finally, Criterion 12 is not related to polymer synthesis but considers MIP reusability. For the single-use sorbent, the score equals 0, the application of MIP between 2- and 10-times scores 0.5, and the most favourable condition, thus scoring 1, is assigned to MIPs used more than 10 times.

Each of the proposed criteria has a different relative importance and therefore weights from 1 to 4 are applied and a higher weight means a greater importance when calculating the weighted average. The weight values for each criterion are listed in Table 1. Detailed information about the description of the pictogram (score, colours, circles and their size) was enclosed elsewhere [31].

# **3.** Application of AGREEMIP for assessing the greenness of the synthesis of MIPs used in sample preparation.

AGREEMIP assessing tool was used to evaluate 30 different MIP preparation procedures defined in the literature as eco-friendly, sustainable, green solution or greener [26,30,33–60]. Table 2 shows the general information on the basic polymerisation mixture components and the final score provided by AGREEMIP assessment. Moreover, in mentioned Table 2, three of the most important criteria, which significantly impact on the green character of defined MIP preparation process, were also listed. Detailed reports with pictograms for each of the evaluated MIP synthesis procedures are included in Supplementary Information.

After evaluating the greenness of the selected procedures for obtaining polymeric sorbents, it was noted that the average total value of AGREEMIP assessment was  $0.49 \pm 0.13$ . Referring only to the average value itself for all 30 evaluated procedures defined in the literature as eco-friendly, sustainable, novel or greener solutions, it can be concluded that, in a general way, all "green" procedures are characterized by a moderate (0.4 to 0.6) degree of greenness. The lowest total value of AGREEMIP assessment (0.28) was obtained for procedure reported in [43], and the corresponding pictogram is shown in Figure 2a, in which the preparation process of magnetic MIPs dedicated for sample preparation and analysis of ractopamine is described. The impact of such low total value of AGREEMIP assessment was mainly caused by the application of organic solvents and reagents such as acetonitrile (as a porogen), acrylic acid (as a functional monomer) and ethylene glycol dimethacrylate (EDGMA) as a cross-linker.

Application of acrylic acid and EDGMA forces a preliminary step to purify them from polymerization inhibitors. Moreover, during the preparation of the mentioned type of magnetic MIPs, it was necessary to previously consume reagents and solvents for the synthesis of the carrier itself (Fe<sub>3</sub>O<sub>4</sub>) as well as the subsequent modification of its surface. A mixture of methanol:acetic acid (9:1) was used several times to elute the template. In addition, the paper lacks information on the possibility of multiple use of the developed polymeric material. Consequently, according to the accepted principle, it should have been assumed that it is used only once. The discussed example illuminates an important problem, which is the whole process of preparing the appropriate polymeric material, and not only its use, as a final product in the analytical procedure. It should be noted, that authors previously used appropriate computer modelling to select the right conditions for the synthesis. Additionally, at the stage of final determinations they used a green analytical technique such as capillary electrophoresis (CE) equipped with diode array detector (DAD).

Also, relatively low AGREEMIP assessment values (below total value of 0.35) were obtained for procedures described in references [42,44,53,56,60]. The low score in these analytical procedures is mainly influenced by the use of toxic and user- and environmentally hazardous solvents as porogenic agents (e.g., chloroform or dimethylformamide), as well as the use of significant amounts of organic solvents such as methanol:acetic acid mixtures to remove the template molecule from the polymer structure. A very interesting example is the procedure described by Chen et al. [53], with a final score of 0.34 (see obtained pictogram in Figure 2b), in which the final product is to be magnetic MIPs with ionic liquid (IL) for the extraction of carbaryl in food. The authors used the IL (1-butyl-3-methylimidazolium hexafluorophosphate (BMIM<sup>+</sup>PF<sub>6</sub><sup>-</sup>)) as an auxiliary solvent which was added to the polymerization mixture together with classical functional monomer (methacrylic acid). Of course, as in any such case, it was necessary to consume an appropriate amount of reagents and solvents in advance to obtain the

magnetic carrier and modify its surface before depositing the polymer sorbent. Moreover, the aforementioned IL was only an additive, and the main porogen in this procedure was still acetonitrile. Unfortunately, also in this case, information on the multiple use of the sorbent was not included in the paper, so it was necessary to assume its single use.

The highest score after AGREEMIP assessment (0.80) was obtained for the synthesis procedure described in [38], and its pictogram is shown in Figure 2c, where a novel green approach in the field of functionalized monomer for molecularly imprinted-enoxaparin polymer is described. New type of MIP was prepared *via* microwave synthesizer workstation. Enoxaparin was introduced as a template, itaconic acid was used as the functional monomer (previously selected using *in silico* studies), N,N'-methylenebisacrylamide was applied as a cross-linking agent and finally water was used as a porogen. Moreover, the high value of the conducted green analysis of the preparation of the MIP-type sorbent is also affected by the use of water to wash out the template molecules and the use of ultrasounds for this purpose. Probably the total value of AGREEMIP assessment will be much higher due to the fact that in the mentioned paper there is a lack of information about the reusability of developed novel green MIP. For this reason for the AGREEMIP assessment it was assumed that described MIP was a single use material.

Taking into account the information listed in Table 2, it might be noticed that several of analysed MIP preparation procedures were characterized by strong/high (between 0.6 and 0.8) degree of greenness. This mainly applies to the evaluated procedures described in [45], [46] and [52] reaching scores of 0.64, 0.70 and 0.69 (pictograms shown in Figure 2d-f), respectively. Arabi et al. [45] describes a green approach and hazardous waste elimination solution in the field of hydrophilic molecularly imprinted nanospheres for the extraction of rhodamine B. As a carrier for the imprinted polymers, the carbon sphere (obtained by the carbonization of glucose in aqueous media) was introduced. The polymerization process was performed under

room temperature and the elution of template molecules from the polymer structure was performed using 5% acetic acid solution. Unfortunately, in the paper there was a lack of information about the reusability of the developed green MIP, which impact on the final score of AGREEMIP assessment. As for the another paper published by the same group [46], in which the preparation process of water-compatible molecularly imprinted nanoparticles for the extraction of hydrochlorothiazide from human urine is described, the most important impact on the final score (0.70) was associated with the amount of reagents and solvent used in core particles preparation and their surface modification. The polymerization process was performed also under room temperature, due to this fact there was no additional power consumption for heating the polymerization mixture. The template molecules were removed from the polymer structure by deionized water/ammonium hydroxide (9:1 v/v) solution by using several times sonication. Finally, in a case of paper published by Elfadil et al. [52], the authors described a new and simple method for the extraction and determination of erythrosine B in food samples. At the sample preparation process, the polydopamine-based MIP coating magnetic nanoparticles was synthesized without the necessity of using a polymerization initiator (selfpolymerization process). The template molecules removing from the polymer structure was performed using 0.1M NaOH. The most sensitive point of this procedure was the consumption of a significant amount of reagents and solvents to obtain the magnetic carrier and modify its surface.

Finally, it is important to point out that the lack of information on the reusability of new MIPs is rather common to all the evaluated papers in this review. Such lack of information makes it necessary to assume that obtained MIPs, after one sorption-desorption cycle, have to be disposed and thus final score is negatively affected. However, such penalty does not likely correspond with the real stability and reusability of MIPs. It is well-known that MIPs are stable and reusable as a consequence of the great chemical stability of the main polymer backbone of

(meth)acrylic MIPs consisting exclusively of carbon atoms. In this sense, MIP stability and reusability are in line with green chemistry principles, since the polymer can be used repeatedly and thus the amount of solid wastes is reduced. However, in parallel, MIPs discharged in the environment should be avoided since their great stability prevents them to be easily degraded. At the best of our knowledge, studies on the (bio)degradability of MIPs are very scarce. For instance, Paruli et al. [61] studied radical-mediated thiol-yne chemistry as a new MIP synthesis route, which allows the incorporation of ester-based polythiols into the polymer network, rendering MIPs hydrolysable under basic and acidic conditions, potentially facilitating their degradability in the environment. Recently, bio-based MIPs were synthesized using a vegetable oil-derived cross-linker, epoxidized soybean acrylate (ESOA) [62]. ESOA-based MIPs showed sensitivity to a fungal lipase, and thus such MIPs could be degraded by the enzyme. These two examples demonstrate that the obtainment of both reusable and degradable MIPs is already possible and further studies in this area are expected in the near future.

#### 4. Conclusions and future remarks

In this work, AGREEMIP tool has been used for assessing the greenness of 30 synthesis procedures of MIPs employed in sample preparation. Selected procedures, mainly published during last 5 years, were those defined in the literature as eco-friendly, sustainable, green solution or greener. After evaluation, it was noted that the average total value of AGREEMIP assessment was 0.49, with most of them reaching scores in the 0.4-0.6 range. In this sense, it seems clear that synthesis procedures are characterized by a moderate degree of greenness and thus, in general, there is an abuse of using sustainability-related terms to define them. Even in some cases, obtained AGREEMIP scores for some synthesis procedures were lower than 0.3, and obviously they cannot be considered as green approaches.

Accordingly, to avoid confusion, it would be desirable to omit terms such as 'green' or 'sustainable' when defining current MIP synthesis processes, as just changing a single step to a more sustainable solution does not mean that the whole synthesis process becomes green. In this sense, AGREEMIP tool appears as a simple way of evaluating the greenness of MIP synthesis procedures and its use is highly recommended. By carrying out a proper greenness assessment, it will be easier to identify weaknesses in the synthesis process and thus which steps need to be improved. In this regard, by carefully observing the 30 papers evaluated in this work, it seems clear that the use of large amounts of toxic solvents as porogens and/or as washing solutions for template removal appears to be one of the key aspects in need of improvement. In addition, the amount of solid waste generated should be reduced by avoiding single-use materials and/or by using the entire polymerization mixture in *in situ* polymerization approaches towards the obtainment of miniaturized MIP formats (i.e. imprinted monoliths as fibers for SPME).

It should also be emphasized the fact that, for the preparation and appropriate modification of the polymer material carrier, significant amounts of solvents and reagents are consumed. These activities should also be taken into account when assessing the green nature of the newly obtained MIP. Unfortunately, this fact is very often overlooked and considered as an element that does not belong to the classical MIP preparation procedure. Therefore, also at this stage of development of a new type of selective molecularly imprinted sorbents, it is necessary to try to find more pro-environmental solutions in the form of less toxic and harmful solvents and reagents. Finally, last but not least, publishing information on the development of a new type of MIPs must include data on whether the material is single-used or reusable. The lack of such information makes it necessary to assume the disposability of the developed material every time.

#### **CRediT** authorship contribution statement

Mariusz Marć: Writing – original draft, review & editing, Investigation, Data curation. Antonio Martín-Esteban: Writing – original draft, review & editing, Supervision, Project administration, Funding acquisition, Conceptualization.

#### **Declaration of Competing Interest**

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

#### Data availability

The data supporting this article have been included as Supplementary Information.

#### Acknowledgements

Grant PID2021-122327OB-I00 funded by MCIN/AEI/10.13039/501100011033 and by "ERDF A way of making Europe" is gratefully acknowledged. Financial support of these studies from Gdansk University of Technology by the DEC-6/1/2024/IDUB/II.1b/Am grant under the Americium International Career Development - 'Excellence Initiative - Research University' program is gratefully acknowledged. This article is based upon work from the Sample Preparation Study Group and Network, supported by the Division of Analytical Chemistry of the European Chemical Society.

#### REFERENCES

- [1] Y. Chen, L. Xia, R. Liang, Z. Lu, L. Li, B. Huo, G. Li, Y. Hu, Advanced materials for sample preparation in recent decade, TrAC Trends Anal. Chem. 120 (2019) 115652. https://doi.org/10.1016/j.trac.2019.115652.
- [2] E.V.S. Maciel, A.L. de Toffoli, E.S. Neto, C.E.D. Nazario, F.M. Lanças, New materials in sample preparation: Recent advances and future trends, TrAC Trends Anal. Chem. 119 (2019) 115633. https://doi.org/10.1016/j.trac.2019.115633.
- [3] J.C. Anastas, P.T. Warner, Green Chemistry: Theory and Practice, Oxford University Press Inc., New York, 1998.
- [4] P.T. Anastas, Green Chemistry and the role of analytical methodology development, Crit. Rev. Anal. Chem. 29 (1999) 167–175. https://doi.org/10.1080/10408349891199356.
- [5] Á.I. López-Lorente, F. Pena-Pereira, S. Pedersen-Bjergaard, V.G. Zuin, S.A. Ozkan, E. Psillakis, The ten principles of green sample preparation, TrAC Trends Anal. Chem. 148 (2022) 116530. https://doi.org/10.1016/j.trac.2022.116530.
- [6] V. Pichon, M. Bouzige, C. Miège, M.C. Hennion, Immunosorbents: Natural molecular recognition materials for sample preparation of complex environmental matrices, TrAC Trends Anal. Chem. 18 (1999) 219–235. https://doi.org/10.1016/s0165-9936(98)00120-4.
- [7] A. Martín-Esteban, P. Fernández, C. Cámara, Immunosorbents: A new tool for pesticide sample handling in environmental analysis, Fresenius J. Anal. Chem. 357 (1997) 927– 933. https://doi.org/10.1007/s002160050276.
- [8] V. Pichon, F. Brothier, A. Combès, Aptamer-based-sorbents for sample treatment A review, Anal. Bioanal. Chem. 407 (2015) 631–698. https://doi.org/10.1007/s00216-014-8129-5.
- [9] V. Pichon, N. Delaunay, A. Combès, Sample Preparation Using Molecularly Imprinted Polymers, Anal. Chem. 92 (2020) 16–33. https://doi.org/10.1021/acs.analchem.9b04816.
- [10] A. Martín-Esteban, Molecularly-imprinted polymers as a versatile, highly selective tool in sample preparation, TrAC Trends Anal. Chem. 45 (2013) 169–181. https://doi.org/10.1016/j.trac.2012.09.023.
- [11] R. Arshady, K. Mosbach, Synthesis of substrate-selective polymers by host-guest polymerization, Makromol. Chem. 182 (1981) 687–692. https://doi.org/10.1002/macp.1981.021820240.
- [12] D. Djozan, T. Baheri, Preparation and evaluation of solid-phase microextraction fibers based on monolithic molecularly imprinted polymers for selective extraction of diacetylmorphine and analogous compounds, J. Chromatogr. A 1166 (2007) 16–23. https://doi.org/10.1016/j.chroma.2007.08.003.
- [13] E. Turiel, J.L. Tadeo, A. Martin-Esteban, Molecularly imprinted polymeric fibers for solid-phase microextraction, Anal. Chem. 79 (2007) 3099–3104. https://doi.org/10.1021/ac062387f.
- [14] M. Díaz-Álvarez, E. Turiel, A. Martín-Esteban, Molecularly imprinted polymer monolith containing magnetic nanoparticles for the stir-bar sorptive extraction of triazines from environmental soil samples, J. Chromatogr. A 1469 (2016) 1–7. https://doi.org/10.1016/j.chroma.2016.09.051.
- [15] M. Díaz-Álvarez, E. Turiel, A. Martín-Esteban, Molecularly imprinted polymer monolith containing magnetic nanoparticles for the stir-bar sorptive extraction of thiabendazole and carbendazim from orange samples, Anal. Chim. Acta 1045 (2019) 117–122. https://doi.org/10.1016/j.aca.2018.09.001.
- [16] M. Díaz-Bao, P. Regal, R. Barreiro, C.A. Fente, A. Cepeda, A facile method for the fabrication of magnetic molecularly imprinted stir-bars: A practical example with

aflatoxins in baby foods, J. Chromatogr. A 1471 (2016) 51–59. https://doi.org/10.1016/j.chroma.2016.10.022.

- [17] F. Du, G. Ruan, S. Liang, F. Xie, H. Liu, Monolithic molecularly imprinted solid-phase extraction for the selective determination of trace cytokinins in plant samples with liquid chromatography-electrospray tandem mass spectrometry, Anal. Bioanal. Chem. 404 (2012) 489–501. https://doi.org/10.1007/s00216-012-6131-3.
- [18] S. Huang, J. Xu, J. Zheng, F. Zhu, L. Xie, G. Ouyang, Synthesis and application of magnetic molecularly imprinted polymers in sample preparation, Anal. Bioanal. Chem. 410 (2018) 3991–4014. https://doi.org/10.1007/s00216-018-1013-y.
- [19] Y. Hua, V. Kumar, K.-H. Kim, Recent progress on hollow porous molecular imprinted polymers as sorbents of environmental samples, Microchem. J. 171 (2021) 106848. https://doi.org/10.1016/j.microc.2021.106848.
- [20] M. Arabi, A. Ostovan, J. Li, X. Wang, Z. Zhang, J. Choo, L. Chen, Molecular Imprinting: Green Perspectives and Strategies, Adv. Mater. 33 (2021) 2100543. https://doi.org/10.1002/adma.202100543.
- [21] A. Martín-Esteban, Green molecularly imprinted polymers for sustainable sample preparation, J. Sep. Sci. 45 (2022) 233–245. https://doi.org/10.1002/jssc.202100581.
- [22] A. Ostovan, M. Arabi, Y. Wang, J. Li, B. Li, X. Wang, L. Chen, Greenificated Molecularly Imprinted Materials for Advanced Applications, Adv. Mater. 34 (2022) 2203154. https://doi.org/10.1002/adma.202203154.
- [23] R.O. Martins, R.A. Bernardo, L.S. Machado, A C. Batista Junior, L.Í.L. Maciel, D.V.A. de Aguiar, F.O. Sanches Neto, J.V.A. Oliveira, R.C. Simas, A.R. Chaves, Greener molecularly imprinted polymers: Strategies and applications in separation and mass spectrometry methods, TrAC Trends Anal. Chem. 168 (2023) 117285. https://doi.org/10.1016/j.trac.2023.117285.
- [24] A.R. Bagheri, M. Ghaedi, Synthesis of chitosan based molecularly imprinted polymer for pipette-tip solid phase extraction of Rhodamine B from chili powder samples, Int. J. Biol. Macromol.139 (2019) 40–48. https://doi.org/10.1016/j.ijbiomac.2019.07.196.
- [25] M.E. Khalifa, I.M.M. Kenawy, Y.G. Abou El-Reash, A.B. Abdallah, Extractive separation of Profenofos as an organophosphorous insecticide from wastewater and plant samples using molecular imprinted cellulose, J. Environ. Chem. Eng. 5 (2017) 3447–3454. https://doi.org/10.1016/j.jece.2017.07.012.
- [26] A.R. Bagheri, M. Ghaedi, Green preparation of dual-template chitosan-based magnetic water-compatible molecularly imprinted biopolymer, Carbohydr. Polym. 236 (2020) 116102. https://doi.org/10.1016/j.carbpol.2020.116102.
- [27] A.M. Bossi, D. Maniglio, BioMIPs: molecularly imprinted silk fibroin nanoparticles to recognize the iron regulating hormone hepcidin, Microchim. Acta 189 (2022) 66. https://doi.org/10.1007/s00604-022-05165-0.
- [28] K. Booker, C.I. Holdsworth, C.M. Doherty, A.J. Hill, M.C. Bowyer, A. McCluskey, Ionic liquids as porogens for molecularly imprinted polymers: Propranolol, a model study, Org. Biomol. Chem. 12 (2014) 7201–7210. https://doi.org/10.1039/c4ob00547c.
- [29] G. Li, W. Wang, Q. Wang, T. Zhu, Deep Eutectic Solvents Modified Molecular Imprinted Polymers for Optimized Purification of Chlorogenic Acid from Honeysuckle, J. Chromatogr. Sci. 54 (2016) 271–279. https://doi.org/10.1093/chromsci/bmv138.
- [30] A. Monnier, M. Díaz-Álvarez, E. Turiel, A. Martín-Esteban, Evaluation of deep eutectic solvents in the synthesis of molecularly imprinted fibers for the solid-phase microextraction of triazines in soil samples, Anal. Bioanal. Chem. 416 (2024) 1337–1347. https://doi.org/10.1007/s00216-024-05164-5.
- [31] M. Marć, W. Wojnowski, F. Pena-Pereira, M. Tobiszewski, A. Martín-Esteban, AGREEMIP: The Analytical Greenness Assessment Tool for Molecularly Imprinted

Polymers Synthesis, ACS Sustainable Chem. Eng. 12 (2024) 12516–12524. https://doi.org/10.1021/acssuschemeng.4c03874.

- [32] M. Tobiszewski, J. Namieśnik, F. Pena-Pereira, A derivatisation agent selection guide, Green Chem. 19 (2017) 5911–5922. https://doi.org/10.1039/C7GC03108D.
- [33] T. Boontongto, R. Burakham, Eco-friendly fabrication of a magnetic dual-template molecularly imprinted polymer for the selective enrichment of organophosphorus pesticides for fruits and vegetables, Anal. Chim. Acta 1186 (2021) 339128. https://doi.org/10.1016/j.aca.2021.339128.
- [34] K. Banan, F. Ghorbani-Bidkorbeh, H. Afsharara, D. Hatamabadi, B. Landi, R. Keçili, B. Sellergren, Nano-sized magnetic core-shell and bulk molecularly imprinted polymers for selective extraction of amiodarone from human plasma, Anal. Chim. Acta 1198 (2022) 339548. https://doi.org/10.1016/j.aca.2022.339548.
- [35] X. Wu, J. Cao, S. Bao, G. Shao, Z. Wang, B. Qin, T. Wang, Y. Fu, Preparation and application of modified three-dimensional cellulose microspheres for paclitaxel targeted separation, J. Chromatogr. A 1655 (2021) 462487. https://doi.org/10.1016/j.chroma.2021.462487.
- [36] N. Surapong, Y. Santaladchaiyakit, R. Burakham, A water-compatible magnetic dualtemplate molecularly imprinted polymer fabricated from a ternary biobased deep eutectic solvent for the selective enrichment of organophosphorus in fruits and vegetables, Food Chem. 384 (2022) 132475. https://doi.org/10.1016/j.foodchem.2022.132475.
- [37] D. Rapacz, K. Smolińska-Kempisty, J. Wolska, A novel *green* molecularly imprinted polymers synthesized in an aqueous medium as S-metolachlor sensitive materials, Talanta 280 (2024) 126674. https://doi.org/10.1016/j.talanta.2024.126674.
- [38] E.J. Astuti, B. Permana, S. Ibrahim, M.A. Zulfikar, S. Damayanti, *In silico* and experimental study of functionalized monomer for molecularly imprinted-enoxaparin polymer: A novel green approach, React. Funct. Polym. 194 (2024) 105778. https://doi.org/10.1016/j.reactfunctpolym.2023.105778.
- [39] X. Guo, D. Yang, Y. Su, Y. Chen, J. Ding, L. Ding, D. Song, High selectivity molecularly imprinted polymer based on short amylose as bio-based functional monomers for selective extraction of λ-cyhalothrin, Int. J. Biol. Macromol. 271 (2024) 132566. https://doi.org/10.1016/j.ijbiomac.2024.132566.
- [40] N. Surapong, P. Pongpinyo, Y. Santaladchaiyakit, R. Burakham, A biobased magnetic dual-dummy-template molecularly imprinted polymer using a deep eutectic solvent as a coporogen for highly selective enrichment of organophosphates, Food Chem. 418 (2023) 136045. https://doi.org/10.1016/j.foodchem.2023.136045.
- [41] T. Boontongto, Y. Santaladchaiyakit, R. Burakham, Biomass waste-derived magnetic material coated with dual-dummy-template molecularly imprinted polymer for simultaneous extraction of organophosphorus and carbamate pesticides, Food Chem. 441 (2024) 138325. https://doi.org/10.1016/j.foodchem.2023.138325.
- [42] S. Farooq, L. Xu, S. Ullah, C. Qin, J. Ping, Y. Ying, Synthesis of green magnetic molecularly imprinted polymers for selective extraction of rifaximin in milk samples, Food Chem. 460 (2024) 140557. https://doi.org/10.1016/j.foodchem.2024.140557.
- [43] D.F. Vidal, C.F. Silva, M.M.C. Borges, C.S. Nascimento, K.B. Borges, Magnetic and mesoporous molecularly imprinted polymer synthesized by rational computation design: Sample preparation and analysis of ractopamine, J. Chromatogr. B 1227 (2023) 123843. https://doi.org/10.1016/j.jchromb.2023.123843.
- [44] M. Mehdipour, M. Ansari, M. Pournamdari, L. Zeidabadinejad, M. Kazemipour, Selective extraction of malathion from biological fluids by molecularly imprinted polymer coated on spinel ZnFe2O4 magnetic nanoparticles based on green synthesis, Sep. Sci. Technol. 56 (2021) 1899–1909. https://doi.org/10.1080/01496395.2020.1803912.

- [45] M. Arabi, A. Ostovan, A.R. Bagheri, X. Guo, J. Li, J. Ma, L. Chen, Hydrophilic molecularly imprinted nanospheres for the extraction of rhodamine B followed by HPLC analysis: A green approach and hazardous waste elimination, Talanta 215 (2020) 120933. https://doi.org/10.1016/j.talanta.2020.120933.
- [46] M. Arabi, M. Ghaedi, A. Ostovan, Development of a Lower Toxic Approach Based on Green Synthesis of Water-Compatible Molecularly Imprinted Nanoparticles for the Extraction of Hydrochlorothiazide from Human Urine, ACS Sustainable Chem. Eng. 5 (2017) 3775–3785. https://doi.org/10.1021/acssuschemeng.6b02615.
- [47] W. Lu, J. Liu, J. Li, X. Wang, M. Lv, R. Cui, L. Chen, Dual-template molecularly imprinted polymers for dispersive solid-phase extraction of fluoroquinolones in water samples coupled with high performance liquid chromatography, Analyst 144 (2019) 1292–1302. https://doi.org/10.1039/C8AN02133C.
- [48] S. Farooq, J. Nie, Y. Cheng, Z. Yan, S.A.S. Bacha, J. Zhang, R.A. Nahiyoon, Q. Hussain, Synthesis of core-shell magnetic molecularly imprinted polymer for the selective determination of imidacloprid in apple samples, J. Sep. Sci. 42 (2019) 2455–2465. https://doi.org/10.1002/jssc.201900221.
- [49] G. Zhu, W. Li, P. Wang, G. Cheng, L. Chen, K. Zhang, X. Li, One-step polymerization of hydrophilic ionic liquid imprinted polymer in water for selective separation and detection of levofloxacin from environmental matrices, J. Sep. Sci. 43 (2020) 639–647. https://doi.org/10.1002/jssc.201900813.
- [50] Y. Liu, W. Li, L. Liu, R. Chen, L. Wang, B. Li, R. Duan, G. Zhu, Highly effective and fast removal of bisphenol A from environmental samples using an eco-friendly surface molecularly imprinted polymer based on MIL-100(Fe), New J. Chem. 48 (2024) 13058– 13068. https://doi.org/10.1039/D4NJ01848F.
- [51] M. Wang, L. Zhou, F. Qiao, H. Yan, Facile and green synthesis of a hydrophilic imprinted resin in a deep eutectic solvent-water medium for the specific molecular recognition of tumor biomarkers in complex biological matrices, Green Chem. 26 (2024) 2000–2010. https://doi.org/10.1039/D3GC04207C.
- [52] D. Elfadil, F. Della Pelle, D. Compagnone, A. Amine, Green Synthesis of Molecularly Imprinted Polymers for Dispersive Magnetic Solid-Phase Extraction of Erythrosine B Associated with Smartphone Detection in Food Samples, Materials 15 (2022) 7653. https://doi.org/10.3390/ma15217653.
- [53] S. Chen, J. Fu, Z. Fu, Y. Li, X. Su, L. Zou, L. He, S. Liu, X. Ao, Y. Yang, Preparation and characterization of magnetic molecular imprinted polymers with ionic liquid for the extraction of carbaryl in food, Anal. Bioanal. Chem. 412 (2020) 1049–1062. https://doi.org/10.1007/s00216-019-02330-y.
- [54] S. Khulu, S. Ncube, T. Kgame, E. Mavhunga, L. Chimuka, Synthesis, characterization and application of a molecularly imprinted polymer as an adsorbent for solid-phase extraction of selected pharmaceuticals from water samples, Polym. Bull. 79 (2022) 1287–1307. https://doi.org/10.1007/s00289-021-03553-9.
- [55] L. Wang, J. Chen, X. Li, L. Chen, K. Zhang, X. Wang, G. Zhu, Eco-friendly ionic liquid imprinted polymer based on a green synthesis strategy for highly selective adsorption tylosin in animal muscle samples, Environ. Sci. Pollut. Res. 28 (2021) 16470–16479. https://doi.org/10.1007/s11356-020-11842-5.
- [56] J.-W. Zhang, L. Tan, J.-B. Yuan, R.-F. Qiao, C.-Z. Wang, F.-Q. Yang, L.-D. Zhou, Q.-H. Zhang, Z.-N. Xia, C.-S. Yuan, Extraction of activated epimedium glycosides *in vivo* and *in vitro* by using bifunctional-monomer chitosan magnetic molecularly imprinted polymers and identification by UPLC-Q-TOF-MS, Talanta 219 (2020) 121350. https://doi.org/10.1016/j.talanta.2020.121350.

- [57] W. Huang, Y. Qing, N. Wang, Y. Lu, T. Liu, T. Liu, W. Yang, S. Li, Novel Thermosensitive Core–Shell Surface Molecularly Imprinted Polymers Based on SiO2 for the Selective Adsorption of Sulfamethazine, Materials 11 (2018) 2067. https://doi.org/10.3390/ma11112067.
- [58] Y. Cao, Z. Huang, L. Luo, J. Li, P. Li, X. Liu, Rapid and selective extraction of norfloxacin from milk using magnetic molecular imprinting polymers nanoparticles, Food Chem. 353 (2021) 129464. https://doi.org/10.1016/j.foodchem.2021.129464.
- [59] S. Bhogal, I. Mohiuddin, K. Kaur, J. Lee, R.J.C. Brown, A.K. Malik, K.-H. Kim, Dualtemplate magnetic molecularly imprinted polymer-based sorbent for simultaneous and selective detection of phenolic endocrine disrupting compounds in foodstuffs, Environ. Pollut. 275 (2021) 116613. https://doi.org/10.1016/j.envpol.2021.116613.
- [60] Y. Ji, J. Zhao, L. Zhao, Fabrication and characterization of magnetic molecularly imprinted polymer based on deep eutectic solvent for specific recognition and quantification of vanillin in infant complementary food, Food Chem. 374 (2022) 131720. https://doi.org/10.1016/j.foodchem.2021.131720.
- [61] E. Paruli, T. Griesser, F. Merlier, C. Gonzato, K. Haupt, Molecularly imprinted polymers by thiol-yne chemistry: Making imprinting even easier, Polym. Chem. 10 (2019) 4732– 4739. https://doi.org/10.1039/c9py00403c.
- [62] N. Le Goff, I. Fomba, E. Prost, F. Merlier, K. Haupt, L. Duma, A. Fayeulle, A. Falcimaigne-Cordin, Renewable plant oil-based molecularly imprinted polymers as biopesticide delivery systems, ACS Sustainable Chem. Eng. 8 (2020) 15927–15935. https://doi.org/10.1021/acssuschemeng.0c05145.

## **Figure legends**

**Figure 1.** The fourteen principles of green molecular imprinting expressed as the mnemonic device "GREENIFICATION". Reproduced from ref. [20] with permission from John Wiley & Sons.



**Figure 2.** Pictograms obtained using AGREEMIP assessment of synthesis procedures for the obtainment of: (a) conventional magnetic MIP [43]; (b) magnetic MIP with ionic liquid as co-solvent [53]; (c) truly green MIP using sustainable monomers and water as porogen [38]; (d) hydrophilic MIP [45]; (e) water-compatible core-shell MIP [46]; (f) polydopamine-based MIP

[52].



Criterion No.	Criterion description	Weight
1	Removal of polymerization inhibitors	1
2	Functional monomer	2
3	Template	1
4	Cross-linking agent	3
5	Porogen/solvent	4
6	Other reagents, adjuvants, or carriers	3
7	Core/particles preparation and surface modification	2
8	Polymerization initiation	3
9	Size of polymer particles	1
10	Template elution solvent	4
11	Template elution technique	3
12	Final product reusability	3

**Table 1.** Weights for the MIP synthesis analysis \*

	* Reproduced fro	om Ref. [30] with	permission from Ar	nerican Chem	ical Society.		
lzy.pl							
<sup>00</sup> <b>Table</b> 2 stidentifi	2. Summary of A ed as more envir	GREEMIP analys	is performed for sel v or more economi	lected MIP pro	eparation proc	cedures	
wnloaded from mo	Functional monomer(s)	Template(s)	Cross-linker	Solvent	3 of the most challengin g factors in MIP preparatio n protocol	Final Agree MIP score	Re f
ST WIEDZY Dov	chitosan	valsartan; losartan	Lack of data or not used as a classical reagent	acetic acid	<ul> <li>6. Other reagents, adjuvants, or carriers</li> <li>7. Core/partic les preparation and surface</li> </ul>	0.48	[2 6]
WO			22				
$\lesssim$							

					-	
				modificatio n 10. Template elution solvent		
МАА	propazine	EGDMA	formic acid : L-menthol	1. Removal of polymeriza tion inhibitors 10. Template elution solvent	0.61	[3 0]
3-amino-1,2,4- triazole	azinphos-methyl; parathion methyl	EGDMA	water	7. Core/partic les preparation and surface modificatio n 10. Template elution solvent 12. Final product reusability <sup>a</sup>	0.46	[3 3]
МАА	amiodarone	EGDMA	acetonitrile	5. Porogen/so lvent 7. Core/partic les preparation and surface modificatio n 10. Template elution solvent	0.48	[3 4]
4-vinylpyridine	paclitaxel	EGDMA	acetonitrile	<ul> <li>6. Other reagents, adjuvants, or carriers</li> <li>7. Core/partic les preparation and surface modification</li> <li>n</li> <li>10. Template elution solvent</li> </ul>	0.45	[3 5]
caffeic acid;	azinphos-ethyl; parathion-ethyl	EGDMA	90% aqueous ethanol;	7. Core/partic	0.40	[3 6]

choline chloride; formic acid			polyethylene glycol	les preparation and surface modificatio n 10. Template elution solvent 11. Template elution technique 2		
acrylamide; acrylic acid; N- isopropylacryla mide	S-metolachlor	N,N'- methylenebis(acryl amide)	water	2. Functional monomer 11. Template elution technique 12. Final product reusability <sup>a</sup>	0.51	[3 7]
itaconic acid	enoxaparin	methylenebisacryla	water	product	0.80	[3 8]
short amylose	λ-cyhalothrin	tetrafluoroterephtha lonitrile	N, N'- dimethylforma mide	8. Polymeriza tion initiation 10. Template elution solvent 11. Template elution technique	0.38	[3 9]
caffeic acid; glutamic acid	T1 caffeine-H <sub>3</sub> PO <sub>4</sub> ; T2 N- (diethoxyphosphin othioyl)-L- phenylalanine	EGDMA	choline chloride; glycerol; 70% ethanol	10. Template elution solvent	0.52	[4 0]
L-tyrosine; L-tryptophan	T1N- (diethoxyphosphin othioyl)-L- tyrosine; T2 phenyl carbamate	EGDMA	ethanol:water	7. Core/partic les preparation and surface modificatio n 10. Template elution solvent	0.49	[4 1]
caffeic acid; choline chloride; formic acid; beta- cyclodextrin	rifampicin	EGDMA	methanol	5. Porogen/so Ivent 7. Core/partic les	0.34	[4 2]

				preparation and surface modificatio n 10. Template elution		
acrylic acid	ractopamine	EGDMA	acetonitrile	solvent 6. Other reagents, adjuvants, or carriers 7. Core/partic les preparation and surface modificatio n 10. Template elution solvent	0.28	[4 3]
MAA	malathion	EGDMA	chloroforme	5. Porogen/so Ivent 10. Template elution solvent 12. Final product reusability <sup>a</sup>	0.33	[4 4]
APTES	rhodamine B	TEOS	acetic acid	<ul> <li>4. Cross- linking agent</li> <li>12. Final product reusability<sup>a</sup></li> </ul>	0.64	[4 5]
APTES	hydrochlorothiazid e	TEOS	water	7. Core/partic les preparation and surface modificatio n	0.70	[4 6]
МАА	norfloxacin; enrofloxacin	EGDMA	acetonitrile:me thanol	5. Porogen/so lvent 10. Template elution solvent 12. Final product reusability <sup>a</sup>	0.47	[4 7]
methacryloyl chloride	imidacloprid	EGDMA	Lack of data or not used as a classical reagent	6. Other reagents, adjuvants, or carriers	0.38	[4 8]

				7. Core/partic les preparation and surface modificatio n 10. Template elution solvent		
2-hydroxyethyl methacrylate	levofloxacin; 1,6- hexa-3,3'-bis-1- vinylimidazolium bromine ([BVIM]Br)	N,N'-methylenebis- acrylamide	water	<ul> <li>4. Cross- linking agent</li> <li>10. Template elution solvent</li> <li>11. Template elution technique</li> </ul>	0.52	[4 9]
1-allyl-3- vinylimidazole bromide; 2-hydroxyethyl methacrylate	bisphenol A	N,N- methylenebis(acryl amide)	water	4. Cross- linking agent 10. Template elution solvent 11. Template elution technique	0.56	[5 0]
phloroglucinol	phenylephrine hydrochloride	hexamethylenetetra mine	DES and water	8. Polymeriza tion initiation	0.61	[5 1]
dopamine hydrochloride	erythrosine B	Lack of data or not used as a classical reagent	tris- (hydroxymeth yl)- aminomethane	6. Other reagents, adjuvants, or carriers	0.69	[5 2]
MAA; ionic liquid (BMIM <sup>+</sup> PF <sub>6</sub> <sup>-</sup> )	carbaryl	EGDMA	acetonitrile	5. Porogen/so lvent 7. Core/partic les preparation and surface modificatio n 10. Template elution solvent	0.34	[5 3]
p-vinyl benzoic acid	venlafaxine	EGDMA	dimethyl sulfoxide	10. Template elution solvent	0.61	[5 4]

				12. Final product reusability <sup>a</sup>		
1,4-butanediyl- 3,3-bis'-1-vinyl imidazolium chloride; 2-acrylamide-2- methylpropanes ulfonic acid	tylosin	N,N'- methylenebisacryla mide	water	10. Template elution solvent	0.63	[5 5]
chitosan; MAA	icariin	epichlorohydrin	2% acetic acid	<ul> <li>4. Cross- linking agent</li> <li>6. Other reagents, adjuvants, or carriers</li> <li>10. Template elution solvent</li> </ul>	0.32	[5 6]
MAA; N-Isopropyl acrylamide	sulfamethazine	EGDMA	acetonitrile	<ol> <li>Removal of polymeriza tion inhibitors</li> <li>Cross- linking agent</li> <li>Other reagents, adjuvants, or carriers</li> </ol>	0.36	[5 7]
dopamine	norfloxacin	dopamine	ethanol	<ul> <li>6. Other reagents, adjuvants, or carriers</li> <li>7. Core/partic les preparation and surface modificatio n</li> </ul>	0.54	[5 8]
APTES; phenyl trimethoxysilan e	bisphenol A; 4-cumylphenol	TEOS	ethanol	<ul> <li>7.</li> <li>Core/partic les</li> <li>preparation and surface</li> <li>modificatio</li> <li>n</li> <li>10.</li> <li>Template</li> <li>elution</li> <li>solvent</li> <li>11.</li> <li>Template</li> <li>elution</li> <li>technique</li> </ul>	0.55	[5 9]

choline chloride; MAA	vanillin	EGDMA	DMF	<ul> <li>5.</li> <li>Porogen/so lvent</li> <li>6. Other reagents, adjuvants, or carriers</li> <li>7.</li> <li>Core/partic les preparation and surface modificatio n</li> </ul>	0.33	[6 0]
-----------------------------	----------	-------	-----	--	------	----------

<sup>a</sup>Final product reusability – this point was highlighted due to the fact that in the paper there was a lack of information about the reusability of MIP. Therefore, the value for the worst-case scenario was adopted (single use of MIP)

Abbreviations: APTES - (3-Aminopropyl)triethoxysilane; DES – deep eutectic solvent (choline chloride and 1,4butanediol); DMF – Dimethylformamide; EDGMA - ethylene glycol dimethylacrylate; MAA - methacrylic acid; TEOS tetraethyl orthosilicate

ounderer

# **Graphical Abstract**



#### **Declaration of interests**

☑ The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

□ The authors declare the following financial interests/personal relationships which may be considered as potential competing interests: