

## szkła Natali


Author: Kuba  
Creation: 12/11/2013  
Sample Name: 15BaTiO3

**Area 1**

Notes:

EDS Spot 2

kV: 30      Mag: 9973      Takeoff: 33.7      Live Time(s): 30      Amp Time(μs): 12.8      Resolution:(eV) 127.3




**eZAF Smart Quant Results with Oxides and SEC (May 2013 )**

Element	Weight %	Atomic %	Net Int.	Error %
Ba O	8.83	12.46	294.83	3.04
Ti O2	3.3	8.94	197.4	6.6
V 2O5	52.1	61.99	2611.56	7.73
Bi 2O3	35.76	16.61	436.19	5.57

EDS Spot 3

kV: 30      Mag: 9973      Takeoff: 33.7      Live Time(s): 30      Amp Time(μs): 12.8      Resolution:(eV) 127.3



**eZAF Smart Quant Results with Oxides and SEC (May 2013 )**

Element	Weight %	Atomic %	Net Int.	Error %
Ba O	8.5	8.66	301.86	2.74
Ti O2	24.37	47.66	1569.96	5.97
V 2O5	40.42	34.72	2146.28	3.18
Bi 2O3	26.71	8.95	329.38	6.99