Postprint of: Świerczek L., Cieślik B., Konieczka P., Challenges and opportunities related to
 the use of sewage sludge ash in cement-based building materials – A review, JOURNAL OF
 CLEANER PRODUCTION, Vol. 287 (2021), 125054, DOI: <u>10.1016/j.jclepro.2020.125054</u>

© 2020. This manuscript version is made available under the CC-BY-NC-ND 4.0
license http://creativecommons.org/licenses/by-nc-nd/4.0/

### 1. Introduction

7 8

9

Sewage sludge (SS), produced in every sewage sludge treatment plant, can become a 10 significant source of energy, heat, or chemical substances e.g. fertilizers, macro- and 11 microelements. Due to the presence of mentioned nutrients, in many countries, SS constitutes 12 13 a valuable substrate for the improvement of arable land quality or remediation of degraded areas, which is a cost-effective and environmentally friendly solution. Annually, 14 around 11.5 Mt of SS dry matter (DM) is produced in European Union countries 15 16 (Vouk et al., 2018). It is estimated that the amount of SS produced in these countries by 2020 will have increased to about 13 Mt DM (D. Vouk et al., 2017). The available SS disposal 17 methods are limited by a series of constantly updated legal acts (Cieślik et al., 2015). For this 18 reason, existing methods are being replaced in favour of more modern ones, that are consistent 19 with new legal requirements. One of the legal act in the European Union regarding the SS is 20 Council Directive (91/271/EEC) of 21 May 1991 (European Commission, Council Directive of 21 22 21 May, 1991) according to which the SS should be treated as a product for further development. For this reason, some of the existing management techniques (e.g. storage, soil 23 24 reclamation, fertilizer production) are even forbidden (Kacprzak et al., 2017).

25 Sewage sludge management methods can be divided into two main groups: biological and 26 thermal. Biological methods such as composting or anaerobic digestion are used less frequently due to the increasing legal requirements for the quality of the processed SS which usually 27 requires further processing (Cieślik et al., 2015). Thermal methods that become a promising 28 alternative include the incineration, pyrolysis and vitrification. The treatment of SS by pyrolysis 29 generates less pollution than incineration, but the main barrier is the complexity of the process, 30 which generates significant maintenance costs. Vitrification, belonging to the high-temperature 31 process (1000-1600 °C), ensures the production of completely environment-neutral material. 32 However, due to high energy consumption, it also requires high financial expenditures 33 (Samolada and Zabaniotou, 2014). In addition, during the vitrification, specific elements 34 species which could be described as volatile in certain conditions (As, Cd, Pb, Se, Hg) 35 (Elled et al., 2007), can be released into the environment so there is a need for continuous 36

monitoring of the process. Moreover, the variety of by-products streams, which have to be
managed, also should be considered (Hernandez et al., 2011).

Due to the diverse composition of SS and significant amounts of potentially harmful 39 substances contained in it (drugs, pharmaceuticals (Díaz-Cruz et al., 2009; Nieto et al., 2010)) 40 and heavy metals (Lu et al., 2016; Yang et al., 2017)), this waste is usually utilized by 41 42 incineration. The process ensures complete decomposition of pathogens, organic matter, and odoriferous substances. Additionally, the volume of SS is significantly reduced, 43 even by 90 - 95%, and its mass by about 70% compared to the state before the process 44 (Lewkowska et al., 2016; Lynn et al., 2015; Tashima et al., 2017). The disadvantage of the 45 incineration process is the concentration of potentially harmful elements and unavoided 46 production of solid residues (dust and ash), which must be properly managed. 47

48 Positive aspects related to the incineration process make it an increasingly common management technique. Around 22% of SS in the European Union is incinerated 49 (D. Vouk et al., 2017) which gives about 0.77 Mt solid waste per year. Germany itself produces 50 about 0.3 Mt of SSA (Krüger and Adam, 2014). It was estimated that the amount of SSA 51 generated in the USA is about 0.54 Mt (Cyr et al., 2007) while in Japan, the management 52 problem is related to significant quantities of obtained SSA (about 0.24 Mt per year) and limited 53 54 land availability (Donatello and Cheeseman, 2013). It is worth noting that the presented values refer only to the amount of the produced ash, i.e. one of the solid residue fractions produced 55 56 during the thermal utilization process. As a result of the exhaust gas stream purification, because of the use of various sorbents (Kijo-Kleczkowska et al., 2015; Liu et al., 2015) a second waste 57 58 fraction is also formed – dust. The dust to ash ratio may vary from 5% to 60%, depending on the technology (Lapa et al., 2007; Marani et al., 2003), and in most publications, related to SSA 59 60 management, the problem of dust management is usually completely neglected.

The quantities of generated SSA in comparison to ash from the energy industry (coal 61 combustion residuals) are about 100 times smaller (about 115 Mt for UE and US countries) 62 (Belviso, 2018; Cyr et al., 2007). However, the management of significant amounts of coal 63 combustion residuals is not considered as a problem, because it is a commonly used mineral 64 addition in cementitious binders. Due to many similarities in SSA production and similar 65 composition to coal fly ash, research on the use of SSA in the construction industry is often 66 carried out. Sewage sludge ash is treated often as a replacement for a binder (Chen et al., 2018; 67 Kappel et al., 2017; Dražen Vouk et al., 2017) or as a mineral addition (Baeza-Brotons et al., 68 2014; Jamshidi et al., 2012; Záleská et al., 2018) to both mortars and concretes. Mentioned 69 70 waste can be also used in alkali-activated binder mixtures as a reaction precursor.

(Chakraborty et al., 2017; Istuque et al., 2016; Tashima et al., 2017). Bricks and tiles 71 (Lin et al., 2017, 2016; Mozo and Gomez, 2016), ceramics (Zhang et al., 2015), glassy materials 72 (Borowski, 2015; Celary and Sobik-Szołtysek, 2014) and lightweight aggregates (Cheeseman 73 74 and Virdi, 2005; Chiou et al., 2006; Lin, 2006) belonging to sintered materials can be also produced with the contribution of SSA, however, these processes also require significant energy 75 demand. The manufactured products, despite eliminating the risk of heavy metals entering the 76 environment, are often characterized by inferior properties e.g. lower compressive strength or 77 78 higher shrinkage. In addition, the production of such materials requires additional gas treatment 79 systems due to the possible presence of volatile heavy metals and other elements species.

Due to the variety of research presented in publications, the complexity of the used waste 80 and the various conclusions regarding the impact of SSA on the properties of cement-based 81 construction products, this article summarizes and presents the latest literature reports related 82 to the use of SSA in cementitious materials. Considering the disadvantages of selected 83 development techniques of both SS and SSA and the fact that SS incineration is currently 84 85 considered as the Best Available Technology (Kijo-Kleczkowska et al., 2016), the article focuses exclusively on the management of SSA in concretes and mortars based on hydraulic 86 binders. This approach eliminates the possible emission of heavy metals to the environment 87 (which is confirmed by leaching tests) and does not require complicated facilities. However, it 88 is difficult to estimate the cost and profitability of such management technique, because it 89 depends on local situation and circumstances, such as raw materials availability, economy or 90 91 geography (Spinosa et al., 2011).

Literature reports have been described in detail in two main groups: cementitious materials 92 (mortars or concretes), in which SSA is an additive and materials in which SSA is a substitute 93 for the main binder. It was also indicated which of the factors may affect the properties of the 94 95 end products e.g. the proportion and type of binder, the method of sample preparation as well as the impact of SSA quality on durability properties. Due to the difficulty in clearly 96 determining whether toxic heavy metals contained in SSA are safely immobilized in a cement 97 98 matrix, results of leaching heavy metals from hardened products are also described. The presented information can be particularly helpful during the design of modern building 99 100 materials and the analysis of the environmental impact of these materials. Some critical issues 101 are also considered.

## 103 **1. Methods and scope**

This study focuses on describing SSA management methods and presents the advantages and disadvantages of including mentioned wastes into building materials based on cement binders. A thorough assessment of selected approaches available in the literature has been carried out. Since the subject is still developing in some countries, the review is based on literature from the entire world. The article is based on the scientific literature but not exclusively. Research published in technical journals and book sections was also used.

The article briefly presents the variety of research on the use of SSA in cement building materials, the research on the cement hardening process, the impact of mineral additives on the properties of mortars and concretes, as well as the use of other waste materials in the construction industry. A thorough analysis of the influence of various factors on cement building materials was performed to simplify condensed information on the impact of SSA wastes uses in building materials.

- 116
- 117

118

119 120

## 2. The SSA potential in materials based on cement binders

# 2.1. Characteristics of SSA

Sewage sludge is a residue left after a primary (physical), secondary (biological) and tertiary 121 (chemical) wastewater treatment (Fytili and Zabaniotou, 2008). Some of the produced residues, 122 especially in municipal wastewater treatment plants processing significant amounts of 123 wastewater, are processed by anaerobic digestion. Before incineration, the produced SS is 124 125 dewatered and dried in order to remove as much water as possible. If the SS calorific value is low (e.g. due to high water content), additional fuel can be used in the incineration process 126 (Wzorek and Tańczuk, 2015). The properly prepared SS is most commonly incinerated in 127 fluidized bed furnaces at a temperature of 850 °C in order to utilize potentially harmful organic 128 fractions. The process can be carried out at higher temperatures to degrade e.g. polychlorinated 129 substances (Wey et al., 2008). Exhaust gases are dedusted in a multi-stage cyclone system, bag 130 filters or electrostatic precipitators, which results in the separation of ash (fly ash). Further gas 131 purification with the use of sorbents, for example, sodium bicarbonate, lime and activated 132 carbon (used for neutralization and removal of harmful organic substances and volatile 133 elemental fractions) generate another fraction of waste - dust or fine fly ash. Both streams of 134 solid residues due to the presence of heavy metals and metalloids have to be properly managed 135 136 (Kacprzak et al., 2017; Samolada and Zabaniotou, 2014). An example diagram of a sewage

137 sludge incineration system is presented in Figure 1. It is worth noting that the type of used 138 sorption media may cause differences in the composition of dust obtained during exhaust gas 139 purification. The elemental composition of dehydrated SS and SSA are also significantly 140 different, therefore ash fraction constitutes a completely different product (Świerczek and 141 Cieślik, 2018).

142



143 144

145

Figure 1. A simplified diagram of a SS thermal treatment plant.

The main oxides found in SSA, determined mostly using X-ray fluorescence technique 146 (XRF) include SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, CaO, Fe<sub>2</sub>O<sub>3</sub>, NaO, MgO and P<sub>2</sub>O<sub>5</sub> (Lynn et al., 2015). Silicone 147 oxide minerals (e.g. quartz), whitlockite, mullite, calcium sulphate minerals (e.g. anhydrite), 148 magnetite, feldspars, and micas belong to the crystalline minerals (shown in Fig. 3) present in 149 SSA. However, the amorphous phase constitutes about 45 % of the SSA mass (Chen and Poon, 150 2017; Cyr et al., 2007; Halliday et al., 2012). In addition to the aforementioned main oxides, 151 SSA contains a number of inorganic heavy metal compounds. Based on the analysis of many 152 test results, it has been shown that solid residues contain Cd, Cu, Ni, Pb, Cr, Mn, Fe, As, Sb, 153 Hg at various concentrations. Reduction of the SS volume and mass as a result of incineration 154 155 increases the content of heavy metals in the obtained solid residues (Van de Velden et al., 2008). 156

## 2.2. Possibilities and limitations related to the use of SSA in cement-based materials

The main silicate compounds in cement clinker that are responsible for its hardening are alite (tricalcium silicate  $3CaO\cdot SiO_2$ ) and belite ( $\beta$ -dicalcium silicate -  $2CaO\cdot SiO_2$ ). Alite constitutes about 50%, while belite about 20% of the total mass of clinker. The remainder of the mass are mostly tricalcium aluminate ( $3CaO\cdot Al_2O_3$ ), and tetracalcium aluminoferrite

(4CaO·A1<sub>2</sub>O3·Fe<sub>2</sub>O<sub>3</sub>) (Li et al., 2018; MacKenzie and Smith, 2002). As a result of the reaction 162 of these substances with water, calcium silicate hydrate and calcium hydroxide are formed. The 163 hydrated calcium silicates commonly described as C-S-H phase (where: C-CaO, S-SiO<sub>2</sub>, 164 H-H<sub>2</sub>O) may have a various composition, morphology, and degree of crystallization. 165 The introduction of e.g. supplementary cementitious materials (SCM) e.g., fly ash, slags, 166 calcined clays containing aluminium causes the formation of calcium aluminosilicate hydrate 167 168 C-A-S-H (where: A-Al<sub>2</sub>O<sub>3</sub>) (Geng et al., 2017; Li et al., 2019). Both mentioned phases are 169 responsible for the strength of the cement paste. However, some minerals from the calcium aluminate hydration system (e.g. CAH<sub>10</sub>, C<sub>3</sub>AH<sub>6</sub>) have been shown to have even higher 170 mechanical properties than the C-S-H phases. Despite the low density of C-A-S-H minerals, 171 172 similar or higher mechanical properties are mainly related to the topology of the mineral network (Geng et al., 2018). 173

It should be noted that the use of SCM is becoming a more and more common procedure 174 aimed at reducing CO<sub>2</sub> emissions and cement consumption. Due to the use of new types of 175 SCM or their blends, the methods for determining technical standards and specific criteria for 176 determining their suitability in building materials also need to be modified/updated. 177 In accordance with ASTM C 618-19, pozzolanic material that can be used in concrete should 178 contain SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, and Fe<sub>2</sub>O<sub>3</sub> in an amount of 50 - 70% of the total mass of the material. 179 Additionally, such materials generally do not exhibit binding properties, but form stable bonds 180 in the presence of water and Ca(OH)<sub>2</sub> (ASTM, 2003). However, as emphasized by R. Snellings 181 182 methods for determining SCM activity based on the measurement of the lime consumption or measuring only the strength of the SCM - cement mixture are insufficient. The authors propose 183 the measurement of cumulated heat release, chemical shrinkage, or bound water content, which 184 allows treating a wider range of SCMs as active materials in cement mixtures. 185 (Snellings et al., 2019). The differences in the methods of determining SCM activity in cement 186 mixtures may be related to the lack of uniformity regarding the activity of SSA in research on 187 its use in building materials. 188

The physicochemical characteristics, composition and production technology of SSA, make it similar to the coal ash residuals thus SSA is used as a binder or fine aggregates substitute which has its advantages and disadvantages. The presence of active oxides in SSA, mainly SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Fe<sub>2</sub>O<sub>3</sub>, CaO can have a positive effect on the hardening of building materials (Chen and Poon, 2017; Sara Naamane et al., 2016). Figure 2 presents a comparison of the main oxides percentage content found in SSA, Portland cement and coal fly ash. The coal fly ash, similar to SSA, includes more Al<sub>2</sub>O<sub>3</sub> compared to Portland cement. The presence of this oxide, as well as sulfate and calcium ions, contribute to the formation of calcium sulfoaluminate
hydrates (AFt) e.g. ettringite and calcium aluminate hydrates (AFm) e.g. monosulfoaluminate
(Avet et al., 2019; Balonis, 2019). The AFm phase is characterized by significant chloride
sorption potential, therefore the presence of SSA in concrete may increase its resistance to the
harmful effects of chlorides (Balonis, 2019; Lynn et al., 2015). It is worth noting that SSA in
mortar or concrete can also increase the number of nucleation sites for C-S-H phase formation
(Scrivener et al., 2015).

An additional benefit associated with the use of SSA is the possibility of immobilizing heavy metals in the matrix of hydrated phases (K.Kazberuk, 2011; Li et al., 2017). Due to the characteristic particle-size distribution of SSA ( $2.5 - 250.0 \mu m$ ), it can be used as a filler or substitute for fine aggregate in concrete (Lynn et al., 2015).



⊠ SiO<sub>2</sub> ■ Al<sub>2</sub>O<sub>3</sub> N Fe<sub>2</sub>O<sub>3</sub> Z CaO ■ P<sub>2</sub>O<sub>5</sub> Z SO<sub>3</sub> □ Na<sub>2</sub>O Ш K<sub>2</sub>O ⊡ MgO ⊡ Remaining

Figure 2. Mass percentage of main oxides in SSA, Portland cement and coal combustion ash; 1 -(Cyr et al., 2007), 2 - (Tay and Show, 1994), 3 - (Pan et al., 2003), 4 - (Garcés et al., 2008), 5 - Rutkowska et al., 2018), 6 - (Li and Poon, 2017), 7 - (Tay and Show, 1994), 8 - (Monzo et al., 1997), 9 - (Yusuf et al., 2012), 10 - (Monzó et al., 1996), 11 - (Chen and Poon, 2017), 12 - (Fernández-Jiménez and Palomo, 2005), 13 - (Jang and Lee, 2016), 14 - (Suksiripattanapong et al., 2015), 15 - (Richardson et al., 2016).

Despite the similar ratio of  $SiO_2$  /  $Al_2O_3$  to coal fly ash, the sum of oxides in SSA on the basis of which material can be classified as pozzolan material is often lower (Fig. 2). It was reported that SSA exhibit lower pozzolanic activity than ash from coal combustion (Chen and Poon, 2017; Rutkowska et al., 2020) or other conventional supplementary cementitious material

(Mejdi et al., 2020). Figure 3 presents the differences in mineralogical composition between
SSA and coal fly ash. The higher ash activity compared to SSA is associated with a different
composition and the occurrence of an amorphous phase. It is worth adding that the SSA's
mineralogical composition is primarily influenced by the processing temperature of the SS.
That basically means that it is impossible to substitute fly ash with SSA without at least a slight
change in product properties.



226 227

232

Figure 3. Comparison of the content of the main mineral phases determined by the XRF technique in SSA and ash from coal combustion (Chen and Poon, 2017; Cyr et al., 2007; Hadi et al., 2018; Halliday et al., 2012; Jang and Lee, 2016; Mádai et al., 2015; Rentsenorov et al., 2018; Schöler et al., 2015; Yan et al., 2018; Záleská et al., 2018).

Unfortunately, some of the researches are based on the use of SSA obtained in the laboratory 233 (S Naamane et al., 2016; Dražen Vouk et al., 2017), while other use SSA which is taken from 234 the SS incineration facilities (Chen and Poon, 2017; Kappel et al., 2017; Li et al., 2017; Piasta 235 and Lukawska, 2016). Similar elements present in ash and dust obtained during technological 236 scale incineration makes it impossible to compare with SSA incinerated in the laboratory 237 238 furnace. It should be remembered that when SS is processed in incineration plants, it could be pre-stabilized by adding lime. The SSA obtained from lime-stabilized SS can be much more 239 active than SSA prepared in the laboratory (Mejdi et al., 2020). Moreover, the technological 240 processing of SS is different from the laboratory processing because some of the analytes are 241 lost during the SS firing in the laboratory furnace (Tang et al., 2008; Youcai et al., 2004). 242

In addition, the laboratory production of SSA causes differences in the mineralogical composition, therefore, a sample of SSA produced on a simple, laboratory procedure is unrepresentative which may cause significant differences, e.g. instability or differences in durability, between cementitious materials containing technological or laboratory ash.

247

# **3.** Sewage sludge ash in mortars as a partial binder or aggregate substitute

Sewage sludge ash can be treated as a substitute for the main binder or an additive in the 249 250 mortar. The purpose of partial binder replacement is mainly to reduce its demand. The second 251 type of research considered in the review paper is the use of SSA as an additive with and without removal of aggregate. Despite the differences in the description of the methodology itself, the 252 253 presented approaches are similar. The average binder content based on the fresh weight of the 254 mortar is 20% while SSA amounts 4.5% (Fig. 4). In general, partial substitution of the main 255 binder or aggregate on SSA causes deterioration of mortar durability even after long curing time (Chang et al., 2010; Chen and Poon, 2017; Piasta and Lukawska, 2016). Table 1 presents 256 257 the impact of SSA on the basic parameters of mortars with its addition. The deterioration of the strength properties is related to the lack of pozzolan reaction between the binder components 258 as well as reduction of the total binder mass content in the mixture (Chen and Poon, 2017; 259 Li et al., 2017; S Naamane et al., 2016). 260

Type of	The share of	Type of aggregate	W	S	WA	CS	Reference
cement	SSA* [%]						
OPC	2.9	Glass <5mm	7	n.d.	1	7	(Li et al., 2017)
OPC	4.7	Sand +	7	n.d.	n.d.	=	(Chen and Poon,
		superplasticizer					2017)
OPC	4.6	Sand	7	n.d.	n.d.	У	(Pan et al., 2003)
CEM I	4.6-6.9	Sand	У	7	n.d.	У	(Chang et al., 2010)
OPC	3.3	Sand	У	n.d.	n.d.	=	(Monzo et al., 1997)
OPC	4.7	Sand	n.d.	7	n.d.	7	(Mejdi et al., 2020)
CEM II/BL-	2.2 - 6.5	Sand	n.d.	n.d.	7	7	(Baeza-Brotons et
32,5R							al., 2014)
CEM II 42.5	2.2	Aggregate 0-4	7	У	n.d.	=	(Dražen Vouk et al.,
		mm					2017);

262 Table 1. Characteristic of mortar samples containing SSA.

CEM III 32.5	4.4	Aggregate 0-4	7	7	n.d.	7	(Dražen Vouk et al.,
		mm + 5%					2017);
		metakaolin					
CP-IV-RS-32	7	Quartz sand	7	n.d.	7	7	(Durante Ingunza et
							al., 2018);
CEM I 42.5 R	2.2	Quartz sand	n.d.	7	n.d.	7	(Piasta and
							Lukawska, 2016)
CEM I 42.5 R	5.1	Aggregate 0-2	n.d.	n.d.	n.d.	=	(Záleská et al.,
		mm					2018)
CEM I 52,5	6.7	Silica sand	7	n.d.	n.d.	7	(Alcocel et al.,
							2006)
CEM I 52,5R	5.6 -11.1	Quartz sand 0-2	7	7	n.d.	7	(Cyr et al., 2007)
		mm					
CEM I 52,5N	2.2-6.7	Sand 0.516mm	7	n.d.	7	7	(Krejcirikova et al.,
							2019)
CEM II/A-LL	4.4	River sand 2-	7	n.d.	n.d.	=	(Kappel et al.,
52.5R		4mm					2017).

264 \* - in a fresh state

265 W – workability

S - setting time

267 WA – water absorption of hardened samples

268 CS – compressive strength after 28-day of curing

269  $\searrow$  – deterioration of the parameter relative to the control sample

270  $\land$  – improvement of the parameter relative to the control sample

271 = - no significant change in the parameter relative to the control sample

272 n.d. – no data

Particles of SSA are characterized by considerable porosity causing the intensive water absorption. The amount of SSA in the mortar mixture is a factor determining its workability (Chang et al., 2010; Chen and Poon, 2017; S Naamane et al., 2016; Dražen Vouk et al., 2017). The problem related to the deterioration of workability can be solved by milling, thanks to which SSA particles become smoother, spherical-like and less porous (Chen et al., 2018; Kappel et al., 2017; Monzo et al., 1997; Pan et al., 2003; Rutkowska et al., 2018).

This phenomenon is called "lubricant effect" because the interlocking and friction between SSA 280 particles are reduced (Pan et al., 2003). It is worth noting that the improvement of mortar 281 workability by SSA milling is less significant compared to using a plasticizer 282 (Monzo et al., 1997). Milling also can change the colour of the mortar to slight red if SSA 283 contains significant amounts of Fe<sub>2</sub>O<sub>3</sub> (Kappel et al., 2017). Colour change, as well as 284 significant shrinkage of the SSA-mortar during curing, may be limiting factors for its 285 286 application (Li et al., 2017). The problem of workability can also be mitigated by water/binder 287 (W / B) ratio reduction, but such solution can be used mainly for the production of prefabricates or soil stabilization approaches and not of joint mortar. 288

The presence of SSA in the mortar also affects its setting time. It was observed that the 289 290 prolongation of the setting time is related to the amount of SSA in the mixture (Chang et al., 2010; Mejdi et al., 2020; S Naamane et al., 2016; Piasta and Lukawska, 2016). 291 292 Extending the setting time (which is also longer compared to coal fly ash) is related to the presence of phosphates in SSA. Formation of insoluble calcium phosphate limits the access of 293 294 water to the cement particles inhibiting the hydration reaction (Mejdi et al., 2020; Piasta and Lukawska, 2016). Sewage sludge ash milling which is performed to reduce excessive water 295 absorption can also increase the setting time. The highly developed surface of SSA particles 296 absorbs calcium ions thus the hydration process is inhibited (Pan et al., 2003). 297

The use of SSA in mortar mixtures may also cause corrosion of the reinforcement due to the high content of salts easily soluble in water. Alcocel et al. presented that the content of chlorides and sulfates in SSA was 7.8 mg/g SSA and 37.2 mg/g SSA respectively. Of course, the presented ratio will always strongly depend on the SS quality. However, it has been shown that the SSA rinsing and subsequent drying process limits its negative effect on the corrosion of reinforcement elements (Alcocel et al., 2006).

304 As mentioned, SSA obtained in the laboratory may show significant differences in both the oxide and mineralogical composition. The improvement of binding properties of mortars 305 containing SSA with low CaO or amorphous phase content can be obtained by adding CaO to 306 307 the mixture in the form of e.g. lime or pozzolanic cement. It was shown that mortar based on pozzolanic cement with the SSA addition (5.8% CaO in SSA mass) is water-tight, and thus 308 309 capillary water absorption decreases with the share of SSA in the hardened mixture. The increase in mortar density, as well as the filling of free spaces between aggregate particles, 310 improves mortar resistance to water and its mechanical properties. It was observed that samples 311 containing 7% of SSA (in total fresh mortar mass) have 39% higher compressive strength in 312 313 comparison to the control sample (Durante Ingunza et al., 2018).

314 The mechanical properties of the mortars based on ordinary Portland cement even with a 5% addition of SSA with moderate CaO content (up to 20%) and a high proportion of the 315 active amorphous phase did not differ significantly from the control samples. During mortar 316 curing, the content of portlandite is reduced, but the pozzolanic reaction is not a factor 317 conditioning the final properties of the material (Záleská et al., 2018). A slight decrease in the 318 compressive strength of the mortar sample in relation to the control sample can be observed 319 320 when SSA constitutes a greater proportion in the binder. Mejdi et al. reported that after 28 days 321 of curing mortar with 20% cement replacement to SSA (containing 20,1% CaO) compressive strength of SSA-mortar was reduced by approximately 9% in comparison to control sample 322 (Mejdi et al., 2020). Similar observations were made for mortar with high CaO content 323 (31.3 - 52.2%), based on ordinary Portland cement. The presence of SSA in the mixture does 324 not significantly reduce the compressive strength of mortars comparing to control samples. 325 The use of SSA with high CaO content and maintaining an appropriate W / B ratio (0.5) by 326 using plasticizer means that the mechanical properties of mortars are similar to reference 327 328 samples, therefore there is no need for additional mineral materials or binders to improve mechanical properties (Monzo et al., 1997; Dražen Vouk et al., 2017). 329

Another solution to reduce the negative impact of SSA on the mechanical properties of 330 331 mortars is the use of mineral additives (metakaolin, nano-silica) or multi-component cement. Nano-silica increases hydrates nucleation and crystal growth as well as accelerate the hydration 332 333 reaction, which can improve the negative effects caused by SSA addition to mortars (Lin et al., 2008). Satisfactory strength properties are also obtained using multicomponent 334 binders (e.g. CEM II, CEM III). These types of binders enhance the occurring pozzolan reaction 335 thus obtained mortars are characterized by good mechanical properties 336 337 (Baeza-Brotons et al., 2014; Kappel et al., 2017). Garcés et al. indicate that cement CEM II / B-M (V-LL) 42.5R is the most suitable binder for mortars containing SSA (Garcés et al., 2008), 338 however, the use of additives or special cement must be preceded by an analysis of the SSA 339 340 composition, because such solutions may not always be effective.

Replacing the main binder in mortars is usually limited to a small share of SSA. The production of mortars based on high-strength cement is an interesting solution. Despite the use of washed SSA (to remove corrosive ions), it was shown that with increased W / B ratio (0.7) and 60% cement (CEM I 52.5) replacement, a material with a compression strength of 13.0 MPa was obtained. Therefore the management of significant amounts of SSA is economically and environmentally justified and the resulting material could be used in construction (Alcocel et al., 2006). The use of SSA with a moderate CaO content, without prior

removal of corrosive ions, as well as maintaining an appropriate W / B ratio results in a material 348 with satisfactory mechanical properties. Despite the deterioration of strength in the early 349 hardening phase, the mortar based on high-strength cement (CEM I 52.5) with 50 % binder 350 substitution has a strength of only 16 % lower than the reference sample. However, it should 351 be remembered that the final compressive strength of the mortar is not limited only to the use 352 of high-class cement. Krejcirikova et al. presented research on the replacement of lime cement 353 with SSA from two different SS incineration plants. Despite the use of SSA's with medium 354 355 CaO content (23.4 and 36.4%) and high strength class cement, a significant decrease in strength was recorded with a 10% binder replacement (aprox. 25 and 20% respectively). It can be 356 assumed that the SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio in both SSA's was high, therefore the deterioration of the 357 358 compressive strength was mainly caused by the dilution effect and more porous structure formation (Krejcirikova et al., 2019). 359

360 As mentioned before, the hydrated structure of mortar or concrete can immobilize heavy metal cations (Záleská et al., 2018). It has been proven that the binding ability of  $Pb^{2+}$  ions is 361 connected with the content of SSA in the mortar. A high proportion of SSA in the mortar results 362 in the reduction of the concentration of  $Pb^{2+}$  ions in the leachate after washing the hardened 363 samples (Li and Poon, 2017). The effect of immobilizing heavy metal ions in a hydrated cement 364 matrix is related to the highly developed specific surface area, the porosity of the hardened 365 material and the ion exchange effect induced by SSA particles. It has been observed that 366 phosphates from SSA react with Pb<sup>2+</sup> ions from the contaminated aggregate. The reaction 367 product of both mentioned substrates is a crystalline lead phosphate (Li et al., 2017). 368

Most of the research on leaching heavy metals from hardened products are based on rinsing 369 monolithic hardened mortar samples. In the case of crushed samples, it is obvious that the 370 leachability of heavy metals is greater due to the larger contact surface. It has been reported that 371 372 the increase in heavy metal concentration in crushed samples increased from 3 to 6 times compared to reference samples. However, the leaching behaviour of samples with SSA was of 373 the same order of magnitude as the reference samples without residue (Cyr et al., 2007). It was 374 375 shown that 25 % replacement of cement (CEM I 52,5 R) for SSA resulted in a 15 % reduction in the total mortar soluble fraction. The incorporation of SSA in mortar did increase the average 376 377 concentration of heavy metals, but this difference in relation to the control sample is not 378 statistically significant. Based on the analysis of the results, it was determined that the metal 379 concentrations in the leachate: Ti, V, Cr, Ni, Cu, Zn, As, Cd, Sn, Sb and Pb meet the 380 requirements for drinking water quality presented by the World Health Organization (WHO)

- 381 (Coutand et al., 2006). However, it is important to perform other elements leaching analysis to
- 382 prove full environmental safety of such an approach.



Figure 4. Compressive strength and shares of binders and SSA in mortars based on various cement binders after 28 days of curing. 1 - (Li et al., 2017); 2- (Chen and Poon, 2017); 3 - (Pan et al., 2003); 4, 5 - (Chang et al., 2010); 6 - (Monzo et al., 1997); 7 - (Mejdi et al., 2020); 8, 9, 10 - (Baeza-Brotons et al., 2014); 11, 13 - (Dražen Vouk et al., 2017); 12 - (Durante Ingunza et al., 2018); 14 - (Piasta and Lukawska, 2016); 15 - (Záleská et al., 2018); 16, 17 - (Alcocel et al., 2006); 18, 19 - (Cyr et al., 2007); 20, 21 - (Krejcirikova et al., 2019); 22 - (Kappel et al., 2017).

- Figure 4. shows the compressive strength of mortar samples in which SSA is present. Due to the diversity in the designed research, the Figure also shows the share of the binder as well as its type. To estimate the impact of SSA quality on the mechanical properties of mortars, the sum content of pozzolanic oxides (SiO<sub>2</sub> + Al<sub>2</sub>O<sub>3</sub> + Fe<sub>2</sub>O<sub>3</sub>), the SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio as well as the percentage content of CaO in SSA was also presented.
- Based on the analysis of the data presented in Figure 4 it can be concluded that the 354 355 quality of SSA has a significant impact on the mortars mechanical properties. When using 356 Ordinary Portland Cement (OPC) and SSA with a low CaO content and high SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio (despite the high content of pozzolanic oxides), a material with low compressive strength was 357 obtained (Chen and Poon, 2017; Li et al., 2017; Pan et al., 2003) despite the significant 358 359 proportion of main binder (samples 1-3). In the case of using SSA with a moderate amount of CaO (approx. 20-30%) the mechanical properties of OPC-based mortars depend on the share 360 of SSA and the SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio (samples 4-6) (Chang et al., 2010; Mejdi et al., 2020; 361 Monzo et al., 1997). The deterioration of the mechanical properties of mortars may also be 362 363 associated with the dilution effect, especially in the case of substitution of the main binder or SSA addition to the mixture without partial aggregate removing. 364
- Pozzolanic cement as a source of CaO has a positive effect on the properties of mortars containing SSA. Durante Ingunza et al. presented that mortar compressive strength containing 7 % SSA was 24.7 % higher. Compared to the data presented in the Figure 4, mortar based on pozzolanic cement (sample 12) may seem unsuitable for this type of management methods, however, it obtains satisfying mechanical properties after longer curing time.
- Mortars based on CEM II / BL-32.5R cement do not show significant loss of mechanical properties, even when significant amounts of SSA (over 5 %) are included in the mortar mass, which confirms the suitability of use multi-component cement as binders (samples 8-10) (Baeza-Brotons et al., 2014; Garcés et al., 2008).
- As mentioned, the high content of CaO in the used SSA does not cause a significant loss of strength properties of the samples. The effect is more visible if the  $SiO_2 / Al_2O_3$  ratio is similar to the fly ash oxides ratio (approx. 2.4) (Fernández-Jiménez and Palomo, 2005; Jang and Lee, 2016; Richardson et al., 2016; Suksiripattanapong et al., 2015). Despite the low content of pozzolanic oxides in SSA and the different binders used (samples 11 and 13), satisfactory mechanical properties were obtained.
  - Based on the results presented by Piasta and Lukawska and Záleská et al. (samples 14 and 15) the addition of SSA with high  $SiO_2 / Al_2O_3$  ratio did not show a significant effect on the properties of the sample. The SSA used in the research can be treated more like a fine

381

aggregate and not as an active mineral material (Piasta and Lukawska, 2016;
Záleská et al., 2018).

In mortars based on high-strength cement (e.g. CEM I 52.5, CEM II 52.5), the SSA quality has the greatest impact on their properties, i.e. the amount of active oxides and their ratio (samples 16-22). The use of SSA with a moderate amount of CaO and ratio of oxides similar to coal fly ash allows to the incorporation of significant amounts of SSA (over 10 %) without significant loss of mechanical properties which in the context of waste management is the most appropriate solution.

391

#### 392 4. Sewage sludge ash in concretes as a partial binder or fine aggregate substitute

393 Concrete is the second most commonly used material in construction after mortar. Research on the impact of SSA on concretes involves: main binder substitution, direct addition 394 395 of SSA without removing the fine aggregate and partial replacement of the fine aggregate. The presence of SSA in concrete as well as in mortar reduces its durability (Chen et al., 2018; 396 397 Fontes et al., 2016; Halliday et al., 2012). The SSA concrete strength loss is mainly proportional to SSA content (Jamshidi et al., 2013). Deterioration of mechanical properties is observed when 398 SSA with a low CaO or amorphous phases content is introduced into the OPC concrete mixture 399 (Fontes et al., 2016). It has been shown that substitution of 10 % of the main binder for SSA 400 resulted in a slight deterioration of strength (4-8 %) compared to the control. Further increasing 401 the SSA share (20 %) results in a 23-29 % strength reduction (Halliday et al., 2012). 402 As presented by Lu et al. replacing the binder in 20% causes the binder dilution effect, therefore 403 404 the compressive strength of the SSA concrete was lower than that of the control sample 405 (Lu et al., 2019). It is worth adding that the introducing of significant amounts of SSA is associated with a significant loss of workability of the mix, therefore achieving homogeneity 406 407 of concrete may become difficult (Halliday et al., 2012; Rutkowska et al., 2020). Changes in the basic parameters caused by the presence of SSA in the concrete mix are presented in 408 Table 2. 409

410

411

412

413

414

415

Type of	The share of	Type of aggregate	W	S	WA	CS	Reference
cement	SSA* [%]						
OPC	2.3-4.6	Granite <5mm	n.d.	n.d.	7	7	(Chen et al., 2018)
CEM I	1.5-4.5	Fine + 10 mm +	n.d.	n.d.	n.d.	7	(Halliday et al.,
		20 mm aggregate					2012)
OPC	1.8	Sand + gravel	n.d.	n.d.	n.d.	=	(Barbosa and Filho,
							2004)
CEM I 32,5	0.7-2.2	Natural aggregate	n.d.	n.d.	n.d.	=	(Rutkowska et al.,
		0.125-16 mm					2018)
CEM I 32,5	0.8-3.9	Natural aggregate	n.d.	n.d.	n.d.	=	(Rutkowska et al.,
		0.125-16 mm					2020)
CEM II	1.6	Gravel and sand	n.d.	n.d.	=	7	(Jamshidi et al.,
							2012)
CP II F-32	1.2	River sand 2.8	n.d.	n.d.	7	7	(Fontes et al., 2016)
		mm +					
		granite gravel 9.5					
		mm					
PC 32	2.9	Quartz sand +	7	n.d.	7	7	(Lima et al., 2015)
		granite gravel					
CEM I 42,5N	7.9-15.8	Sand 0/2, natural	n.d.	n.d.	=	7	(K.Kazberuk, 2011)
- HSR/NA		aggregate 2/4 and					
		4/8					
CEM II BM	0.6-1.2	F-0/4 and F-2/8	n.d.	n.d.	У	У	(Baeza-Brotons et
(S-LL)-42.5R		aggregates					al., 2014).
CEM II BM	6.0	F-0/4 and F-2/8	n.d.	n.d.	У	7	(Baeza-Brotons et
(S-LL)-42.5R		aggregates					al., 2014).
CEM I 52,5	1,7	Natural aggregate	n.d.	n.d.	n.d.	7	(Lu et al., 2019)
		5-10 mm,					
		recycled					
		aggregates waste					
		glass aggregate 0-					
		5mm					

417 Table 2. Characteristic of concrete samples containing SSA.

418 \* - in a fresh state

419 W – workability

- 420 S setting time
- 421 WA water absorption of hardened samples
- 422 CS compressive strength after 28-day of curing
- 423  $\gamma$  deterioration of the parameter relative to the control sample
- 424  $\land$  improvement of the parameter relative to the control sample
- 425 = no significant change in the parameter relative to the control sample
- 426 n.d. no data

427 The presence of amorphous phase in SSA may enhance pozzolanic reaction in the later 428 stages of concrete hardening, but mainly high CaO content and active oxide ratio in SSA 429 intensify this reaction (Halliday et al., 2012). As the curing time increases, the compressive 430 strength of the concrete sample increases, however, this increase is also observed for the control sample without the addition of SSA. By extending the curing time sufficiently long, the 431 432 differences between the durability of SSA concrete and the control samples are insignificant (Rutkowska et al., 2020). This phenomenon can be related to the slight pozzolanic activity of 433 434 SSA. Moreover, the SSA particles constituting additional nucleation sites during cement 435 hydration (Jamshidi et al., 2012).

Sewage sludge ash obtained in an incineration plant with high CaO content can be successfully used as a partial binder substitute in concretes. It was shown that replacing 10 % of cement with SSA resulted in a 25 % improvement in compressive strength compared to control samples. It is possible that such products can be used in construction because their properties, e.g. strength, thermal conductivity or water resistance meet the requirements (e.g. EN 771-3 standard) (Pérez-Carrión et al., 2014).

The use of CaO-rich SSA, even if it is produced in a laboratory, as a partial replacement 442 of fine aggregate increases the density of concrete, which results in increased strength. It has 443 444 been observed that compressive strength of the concrete in which a part of the fine aggregate 445 was replaced with SSA (30 % CaO) is twice higher than the samples in which the aggregate was not removed in favour of SSA (Baeza-Brotons et al., 2014). Rutkowska et al. reported that 446 447 SSA containing a moderate amount of CaO (about 20%) can positively affect concrete 448 properties. After 28 days of hardening of the concrete sample with the 20% SSA replacement, the compressive strength increased by 2.9% compared to the control (Rutkowska et al., 2020). 449

450 The influence of SSA on the strength properties of concrete is probably caused by the pozzolanic reaction, since the substances contained in SSA and cement together may constitute 451 452 a binder, which total amount is significantly higher. The problem associated with low CaO content in SSA can be solved by using pozzolanic cement to concrete preparation. It was found 453 454 that the 3% SSA (6.2% CaO) addition (in total fresh concrete mass) without aggregate removal to concrete based on pozzolanic cement caused the hardened samples to be almost twice as 455 456 durable as the control sample (Lima et al., 2015). Alternatively, CaO content can be increased 457 directly in SSA, as mentioned before in section related to the SSA mortar quality.

The improvement of the mechanical properties of concretes is mostly observed in the 458 case of a small proportion of SSA in the total mass of the cement mixture. Further increasing 459 the content of SSA in the mixture results in high water demand during preparation and 460 significant shrinkage of the products during curing (Chen and Poon, 2017; Rutkowska et al., 461 2018). Increasing the W / B ratio to improve the workability of the fresh concretes causes 462 reduction in durability properties due to the formation of a more porous matrix. The use of 463 plasticizer as well as milling or changing the W / B ratio is a good solution for the elimination 464 of high SSA water absorption (Fontes et al., 2016; Halliday et al., 2012; Lima et al., 2015; 465 Rutkowska et al., 2020, 2018). Ensuring homogeneity and water access to the binder particles 466 does not significantly reduce the mechanical properties of SSA concrete (Jamshidi et al., 2013). 467 It is worth adding that the SSA can increase concrete porosity, despite maintaining the 468 appropriate W / B ratio and using a plasticizer. It has been shown that the porosity of concrete 469 increases with the proportion of SSA in the mix, especially when low active SSA is used 470 471 (Lu et al., 2019), however, the pores in the matrix are closed. The improvement of water-472 tightness makes concrete more durable because it is more resistant to aggressive environments and frost (Baeza-Brotons et al., 2014; Barbosa and Filho, 2004). Moreover, SSA used as an 473 admixture in concrete prefabricated/blocks, cause the thermal conductivity decrease due to 474 reduced mix porosity and compactness (Lu et al., 2019).

The binding capacity of heavy metals by SSA is also confirmed with respect to the Commission Decision of 18 December 2014 (2014/955/EU) on the list of waste concerning, inter alia, the leaching of heavy metals from waste (Commission Decision of 18 December, 2014). For concrete in which cement was substituted with SSA in an amount of 15%, the sum content of elements in the leachate (Cd, Cr, Cu, Ni, Pb, Zn, As, Sb, Se, Ba, Hg, Mo) was 1.2 mg/L. A similar observation was recorded for 25% cement substitution, where the sum of mentioned leached heavy metals was 1.5 mg/L. In accordance with Commission Decision, the maximum concentration of each mentioned element in leachates cannot exceed 10 mg/l (Cieślik et al., 2018; Rutkowska et al., 2020, 2018). K.Kazberuk presented that replacing 25%
of the binder in concrete for SSA, in addition to obtaining satisfactory strength properties,
concrete can be regarded as safe and does not cause any environmental risk
(K.Kazberuk, 2011). Based on heavy metal leaching tests (Toxicity Characteristic Leaching
Procedure (TCLP Method 1311, 1992)) it was confirmed that the leachability of heavy metals
from SSA-containing concrete was lower than in the case of coal fly ash-containing ones
(Cieślik et al., 2018).

491 Figure 5. presents the compressive strength of concrete samples in which SSA is present as well as CaO content, the sum of active oxides and its ratio. Despite the high share of 492 pozzolanic oxides and similar SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio to coal fly ash, the mechanical properties of 493 concretes (labelled as 1 and 2) are mostly determined by the share of binder and SSA, which in 494 495 this case exhibits pozzolanic properties (Chen et al., 2018). Increasing active SSA content in concrete causes slight decrease in compressive strength, while lower SiO<sub>2</sub> / Al<sub>2</sub>O<sub>3</sub> ratio in SSA 496 causes more drastic strength loss with the increase of SSA's share (Halliday et al., 2012). 497 The moderate content of CaO in SSA (about 20 %) may also contribute to the fact that the 498 499 decrease in strength is less intense with the increasing share of SSA in concrete 500 (samples 6, 7, 8).

501 Due to the limited data on the effect of SSA on CEM II-based concrete, its impact is 502 difficult to determine. Considering the differences in SSA's composition (samples 9, 10), it can 503 be assumed that the share of the main binder has the greatest impact on the concrete mechanical 504 properties. Sewage sludge ash consisting mostly of  $SiO_2$  has poor binding properties thus the 505 decrease in strength is associated with a decrease in the overall binder content.

The results presented by Lima et al. where the concrete was based on pozzolanic cement, confirm that the external addition of CaO positively affects the SSA-concretes strength. It was shown that after 28 days of curing, in concrete with 10 % (in relation to the weight of cement) addition of SSA, the strength value improved by 44 % (Lima et al., 2015).

MOST WIEDZY Downloaded from mostwiedzy.pl

510

511

512



Figure 5. Compressive strength and shares of binders and SSA in concretes based on various cement binders after 28 days of curing.
1, 2 - (Chen et al., 2018); 3, 4 - (Halliday et al., 2012); 5 - (Barbosa and Filho, 2004); 6, 7 - (Rutkowska et al., 2018); 8 - (Rutkowska et al., 2020);
9 - (Jamshidi et al., 2012); 10 - (Fontes et al., 2016); 11 - (Lima et al., 2015); 12, 13 - (K.Kazberuk, 2011); 14, 15, 16 - (Baeza-Brotons et al., 2014); 17 - (Lu et al., 2019).

The use of special binders (bridge and airport cement) in concrete with the addition of low-active SSA (samples 12 and 13) results in a drastic decrease in strength during the increasing share of SSA. It is worth noting that the values shown in Figure 5 relate to compressive strength after 28 days of curing. K.Kazberuk presented that after 180 days of curing, the samples are characterized by about twice as high strength as those after 28 days of curing (K.Kazberuk, 2011).

509 The test results labelled as 14-17 concern the use of SSA in concrete intended for the 510 production of prefabricated elements. The nearly double increase in concrete strength may be associated with the pozzolanic reaction between SSA components and multi-component 511 cement, causing secondary hydration phases formation, however, the increased density and 512 filling the free spaces between aggregate particles by SSA was the decisive effect on final 513 mechanical properties (Baeza-Brotons et al., 2014). Lu et al. indicate that such products do not 514 require high durability, and therefore other waste materials can be included in the concrete 515 mixture. In addition, production of partition blocks is a novel and eco-friendly approach for 516 517 SSA utilization. (Lu et al., 2019).

It is worth mentioning that difficulty in estimating the impact of SSA on the physicochemical properties of hardened concretes is the variety of used aggregates. Stiffness and compressive strength of concrete depend also on the aggregate type as well as its particle size, therefore, differences between mechanical properties may occur (Ćosić et al., 2015).

522

### 523 **5.** Conclusions

Due to the increase in the popularity of SS thermal utilization methods, more and more 524 ecological concepts of using SSA are being created. As a result of some similarities of SSA to 525 coal fly ash, commonly used in the construction industry, SSA can be utilized in mortars or 526 concretes mixtures. In such products, this waste is treated as an active pozzolanic additive or 527 528 the main binder substitute. One of the greatest limitations of using SSA in cementitious building 529 materials is the fact that SS from different incineration facilities may differ significantly. Regardless of the method of SS incineration, obtained SSA should always be treated as a 530 material similar in properties to fine aggregate rather than a binder. Due to very diverse 531 characteristics of SS, and its processing methods, SSA obtained from different sources should 532 be thoroughly characterized separately before implementing the most appropriate utilization 533 method. Moreover, the problem of the significant differences in the characteristics of SSA 534 obtained at laboratory scale and SSA obtained at technical scale is crucial for developing of 535 536 suitable waste management approach. Any strong statements regarding the possibilities of using SSA in the construction industry should be supported by at least SSA incineration industrial-scale trials.

Based on the analysis of the results collected in this article, it could be stated that SSA, 505 as a mineral component, has a negative impact on almost all mortar or concrete materials 506 parameters. The activity of SSA in cement-based products depends mainly on its oxide and 507 mineralogical composition as well as the type of used binder. The deterioration of mechanical 508 509 properties is observed when low-active SSA even in small amounts is used. However, the 510 negative impact of the presence of SSA on cement mixtures can be reduced by modifying the ratio of active oxides. The high share of CaO and pozzolanic oxides (SiO<sub>2</sub>, Fe<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>) in 511 SSA may contribute to the pozzolanic reaction in a cementitious mixture based on OPC, thus 512 compressive strength decrease is smaller. The discussed problem can be omitted at the stage of 513 SS incineration. Addition of Ca, Si, Fe and Al species to SS is a trivial approach which could 514 515 be an effective solution for the implementation of new waste management approach directly in the sewage sludge treatment plant or in the incineration facility. On the other hand, the use of 516 517 low CaO content SSA could be more suitable when specific binders (e.g. multi-component cement) or additional source of CaO (lime or pozzolanic cement) are used. It is worth noting 518 that the smallest parameters deterioration of SSA-containing samples is observed when high-519 strength binders (e.g. CEM I 52.5 or CEM II 52.5) are used. It is especially important in case 520 of planning a possible increase of CaO content in SSA by simple technological operations at 521 the stages of wastewater treatment or SS incineration. 522

The presence of SSA in cement mixtures, in addition to the deterioration of the 523 524 mechanical characteristics, is also often associated with deterioration of workability, prolongation of setting time and product shrinkage. Worse workability parameter can be 525 compensated by changing the W / B ratio, milling SSA or using a plasticizer. However, 526 527 SSA milling can cause significant shrinkage of products during curing, while an increase in the W / B ratio is associated with an increase in porosity. The use of plasticizer is the most suitable, 528 however, it can generate additional costs, especially when SSA constitutes a significant share 529 530 in the product.

The last parameter determining both, durability and environmental safety of mortar and concrete is water absorption by cured samples. In the case of mortars, an increase in the water absorption capacity is observed while the concrete becomes more watertight. Therefore, the use of SSA in building materials should be limited mainly to applications in concrete mixtures.

It is also important to mention that the main advantage of incorporating SSA into building materials is the fact that the toxic heavy metals present in SSA are safely immobilized, and

MOST WIEDZY Downloaded from mostwiedzy.pl

531

532

533

534

535

therefore do not pose a risk to the environment. Moreover, it gives the opportunity to minimize 503 the amount of unmanaged solid residues production for many sewage sludge treatment plants. 504 It must be kept in mind that strength, workability, setting time or water absorption are not the 505 only ones of the characteristic features that are affected by the presence of SSA in the cement 506 mixture. For a detailed assessment, other aspects, such as environmental safety or other 507 mechanical properties, should also be considered. Before considering any technological scale 508 509 application, the laboratory-scale test should always be supported by data obtained during 510 industrial-scale trials.

511 Despite the many negative aspects associated with the use of SSA in building materials, 512 it is possible to reduce them by simple solutions but there is an urgent need for further research 513 to optimize existing ones.

514

### 515 6. Acknowledgements

This research did not receive any specific grants from funding agencies in the public,commercial, or not-for-profit sectors.

518

# 519 7. Literature

Alcocel, E.G., Garces, P., Martínez, J.J., Andión, L.G., Payá, J., Garcés, P., Martínez, J.J.,
Payá, J., Andión, L.G., 2006. Effect of sewage sludge ash (SSA) on the mechanical
performance and corrosion levels of reinforced Portland cement mortars.
Mater. Constr. 56, 31–43.

- ASTM, 2003. ASTM C618. Standard specification for coal fly ash and raw or calcined natural
  pozzolan for use in concrete. American society for testing and materials. West
  Conshohocken, PA, USA: ASTM International; 2003.
- Avet, F., Boehm-Courjault, E., Scrivener, K., 2019. Investigation of C-A-S-H composition, 527 528 morphology and density in Limestone Calcined Clay Cement (LC3). Cem. Concr. Res. 115, 70–79. 529 https://doi.org/https://doi.org/10.1016/j.cemconres.2018.10.011 530
- Baeza-Brotons, F., Garcés, P., Payá, J., Saval, J.M., 2014. Portland cement systems with
  addition of sewage sludge ash. Application in concretes for the manufacture of blocks.
  J. Clean. Prod. 82, 112–124. https://doi.org/10.1016/j.jclepro.2014.06.072
- Balonis, M., 2019. Thermodynamic modelling of temperature effects on the mineralogy of
  Portland cement systems containing chloride. Cem. Concr. Res. 120, 66–76.
  https://doi.org/https://doi.org/10.1016/j.cemconres.2019.03.011

- Barbosa, M.C., Filho, R.D.T., 2004. Potentiality of Sewage Sludge Ash As Mineral Additive
  in Cement Mortar and High Performance. Int. RILEM Conf. Use Recycl. Mater. Build.
  Struct. 797–806.
- Belviso, C., 2018. State-of-the-art applications of fly ash from coal and biomass: A focus on
  zeolite synthesis processes and issues. Prog. Energy Combust. Sci. 65, 109–135.
  https://doi.org/10.1016/j.pecs.2017.10.004
- Borowski, G., 2015. Using vitrification for sewage sludge combustion ash disposal.
  Polish J. Environ. Stud. 24, 1889–1896. https://doi.org/10.15244/pjoes/36080
- 511 Celary, P., Sobik-Szołtysek, J., 2014. Vitrification as an alternative to landfilling of tannery
  512 sewage sludge. Waste Manag. 34, 2520–2527.
  513 https://doi.org/10.1016/j.wasman.2014.08.022
- Chakraborty, S., Jo, B.W., Jo, J.H., Baloch, Z., 2017. Effectiveness of sewage sludge ash
  combined with waste pozzolanic minerals in developing sustainable construction material:
  An alternative approach for waste management. J. Clean. Prod. 153, 253–263.
  https://doi.org/10.1016/j.jclepro.2017.03.059
- Chang, F.C., Lin, J.D., Tsai, C.C., Wang, K.S., 2010. Study on cement mortar and concrete
  made with sewage sludge ash. Water Sci. Technol. 62, 1689–1693.
  https://doi.org/10.2166/wst.2010.459
- 521 Cheeseman, C.R., Virdi, G.S., 2005. Properties and microstructure of lightweight aggregate
  522 produced from sintered sewage sludge ash. Resour. Conserv. Recycl. 45, 18–30.
  523 https://doi.org/10.1016/j.resconrec.2004.12.006
- Chen, Z., Li, J.S., Poon, C.S., 2018. Combined use of sewage sludge ash and recycled glass
  cullet for the production of concrete blocks. J. Clean. Prod. 171, 1447–1459.
  https://doi.org/10.1016/j.jclepro.2017.10.140
- 527 Chen, Z., Poon, C.S., 2017. Comparative studies on the effects of sewage sludge ash and fly
  528 ash on cement hydration and properties of cement mortars. Constr. Build. Mater. 154,
  529 791–803. https://doi.org/10.1016/j.conbuildmat.2017.08.003
- Chiou, I.-J., Wang, K.-S., Chen, C.-H., Lin, Y.-T., 2006. Lightweight aggregate made from
  sewage sludge and incinerated ash. Waste Manag. 26, 1453–61.
  https://doi.org/10.1016/j.wasman.2005.11.024
- Cieślik, B.M., Namieśnik, J., Konieczka, P., 2015. Review of sewage sludge management:
  standards, regulations and analytical methods. J. Clean. Prod. 90, 1–15.
  https://doi.org/10.1016/j.jclepro.2014.11.031
  - Cieślik, B.M., Zając, M., Gałuszka, A., Konieczka, P., 2018. Comprehensive stabilization of

all streams of solid residues formed during sewage sludge thermal treatment – Case study.

504 J. Clean. Prod. 178, 757–767. https://doi.org/10.1016/j.jclepro.2018.01.069

- Commission Decision of 18 December, 2014. Commission Decision of 18 December 2014
  amending Decision 2000/532/EC on the list of waste pursuant to Directive 2008/98/EC of
  the European Parliament and of the Council Text with EEA relevance.
- Cosić, K., Korat, L., Ducman, V., Netinger, I., 2015. Influence of aggregate type and size on
  properties of pervious concrete. Constr. Build. Mater. 78, 69–76.
  https://doi.org/10.1016/j.conbuildmat.2014.12.073
- 511 Council Directive of 21 May, 1991. European Commission, Directive of 21 May concerning
  512 urban waste water treatment.
- Coutand, M., Cyr, M., Clastres, P., 2006. Use of sewage sludge ash as mineral admixture in
  mortars. Proc. Inst. Civ. Eng. Constr. Mater. 159, 153–162.
  https://doi.org/10.1680/coma.2006.159.4.153
- 516 Cyr, M., Coutand, M., Clastres, P., 2007. Technological and environmental behavior of sewage
  517 sludge ash (SSA) in cement-based materials. Cem. Concr. Res. 37, 1278–1289.
  518 https://doi.org/10.1016/j.cemconres.2007.04.003
- Díaz-Cruz, M.S., García-Galán, M.J., Guerra, P., Jelic, A., Postigo, C., Eljarrat, E., Farré, M.,
  López de Alda, M.J., Petrovic, M., Barceló, D., 2009. Analysis of selected emerging
  contaminants in sewage sludge. TrAC Trends Anal. Chem. 28, 1263–1275.
  https://doi.org/10.1016/j.trac.2009.09.003
- Donatello, S., Cheeseman, C.R., 2013. Recycling and recovery routes for incinerated sewage
  sludge ash (ISSA): A review. Waste Manag. 33, 2328–2340.
  https://doi.org/10.1016/j.wasman.2013.05.024
- Durante Ingunza, M. del P., Camarini, G., Murilo Silva da Costa, F., 2018. Performance of
  mortars with the addition of septic tank sludge ash. Constr. Build. Mater. 160, 308–315.
  https://doi.org/10.1016/j.conbuildmat.2017.11.053
- Elled, A.L., Åmand, L.E., Leckner, B., Andersson, B.Å., 2007. The fate of trace elements in
  fluidised bed combustion of sewage sludge and wood. Fuel 86, 843–852.
  https://doi.org/10.1016/j.fuel.2006.08.014
- Fernández-Jiménez, A., Palomo, A., 2005. Composition and microstructure of alkali activated
  fly ash binder: Effect of the activator. Cem. Concr. Res. 35, 1984–1992.
  https://doi.org/10.1016/j.cemconres.2005.03.003
  - Fontes, C.M.A., Toledo Filho, R.D., Barbosa, M.C., 2016. Sewage sludge ash (SSA) in high performance concrete: characterization and application. Rev. IBRACON Estruturas e

535

Mater. 9, 989–1006. https://doi.org/10.1590/s1983-41952016000600009

- Fytili, D., Zabaniotou, A., 2008. Utilization of sewage sludge in EU application of old and new
  methods-A review. Renew. Sustain. Energy Rev. 12, 116–140.
  https://doi.org/10.1016/j.rser.2006.05.014
- Garcés, P., Pérez Carrión, M., García-Alcocel, E., Payá, J., Monzó, J., Borrachero, M. V., 2008.
  Mechanical and physical properties of cement blended with sewage sludge ash. Waste
  Manag. 28, 2495–2502. https://doi.org/10.1016/j.wasman.2008.02.019
- Geng, G., Li, J., Zhou, Y., Liu, L., Yan, J., Kunz, M., Monteiro, P.J.M., 2018. A high-pressure
  X-ray diffraction study of the crystalline phases in calcium aluminate cement paste. Cem.
  Concr. Res. 108, 38–45. https://doi.org/10.1016/j.cemconres.2018.03.004
- Geng, G., Myers, R.J., Li, J., Maboudian, R., Carraro, C., Shapiro, D.A., Monteiro, P.J.M.,
  2017. Aluminum-induced dreierketten chain cross-links increase the mechanical
  properties of nanocrystalline calcium aluminosilicate hydrate. Sci. Rep. 7, 44032.
  https://doi.org/10.1038/srep44032
- Hadi, M.N.S., Al-Azzawi, M., Yu, T., 2018. Effects of fly ash characteristics and alkaline
  activator components on compressive strength of fly ash-based geopolymer mortar.
  Constr. Build. Mater. https://doi.org/10.1016/j.conbuildmat.2018.04.092
- Halliday, J.E., Jones, M.R., Dyer, T.D., Dhir, R.K., 2012. Potential use of UK sewage sludge
  ash in cement-based concrete. Proc. Inst. Civ. Eng. Waste Resour. Manag. 165, 57–66.
  https://doi.org/10.1680/warm.2012.165.2.57
- Hernandez, A.B., Ferrasse, J.H., Chaurand, P., Saveyn, H., Borschneck, D., Roche, N., 2011.
  Mineralogy and leachability of gasified sewage sludge solid residues. J. Hazard. Mater.
  191, 219–227. https://doi.org/10.1016/j.jhazmat.2011.04.070
- Istuque, D.B., Reig, L., Moraes, J.C.B., Akasaki, J.L., Borrachero, M. V., Soriano, L., Payá, J., 526 Malmonge, J.A., Tashima, M.M., 2016. Behaviour of metakaolin-based geopolymers 527 incorporating sewage sludge ash Mater. Lett. 180, 192–195. 528 (SSA). https://doi.org/10.1016/j.matlet.2016.05.137 529
- Jamshidi, A., Jamshidi, M., Mehrdadi, N., Shasavandi, A., Pacheco-Torgal, F., 2013.
  Mechanical performance of concrete with partial replacement of sand by sewage sludge
  ash from incineration. Mater. Sci. Forum 730–732, 462–467.
  https://doi.org/10.4028/www.scientific.net/MSF.730-732.462
  - Jamshidi, M., Jamshidi, A., Mehrdadi, N., Pacheco-Torgal, F., 2012. Mechanical performance and capillary water absorption of sewage sludge ash concrete (SSAC). Int. J. Sustain. Eng. 5, 228–234. https://doi.org/10.1080/19397038.2011.642020

534

535

- Jang, J.G., Lee, H.K., 2016. Effect of fly ash characteristics on delayed high-strength
  development of geopolymers. Constr. Build. Mater. 102, 260–269.
  https://doi.org/10.1016/j.conbuildmat.2015.10.172
- K.Kazberuk, M., 2011. Application of SSA as partial replacement of aggregate in concrete.
  Polish J. Environ. Stud. 20, 365–370.
- Kacprzak, M., Neczaj, E., Fijałkowski, K., Grobelak, A., Grosser, A., Worwag, M., Rorat, A.,
  Brattebo, H., Almås, Å., Singh, B.R., 2017. Sewage sludge disposal strategies for
  sustainable development. Environ. Res. 156, 39–46.
  https://doi.org/10.1016/j.envres.2017.03.010
- Kappel, A., Ottosen, L.M., Kirkelund, G.M., 2017. Colour, compressive strength and
  workability of mortars with an iron rich sewage sludge ash. Constr. Build. Mater. 157,
  1199–1205. https://doi.org/10.1016/j.conbuildmat.2017.09.157
- 515 Kijo-Kleczkowska, A., Środa, K., Kosowska-Golachowska, M., Musiał, T., Wolski, K., 2016.
- 516 Combustion of pelleted sewage sludge with reference to coal and biomass. Fuel 170, 141–
  517 160. https://doi.org/10.1016/j.fuel.2015.12.026
- Kijo-Kleczkowska, A., Środa, K., Kosowska-Golachowska, M., Musiał, T., Wolski, K., 2015.
  Mechanisms and kinetics of granulated sewage sludge combustion. Waste Manag. 46, 459–471. https://doi.org/10.1016/j.wasman.2015.08.015
- 521 Krejcirikova, B., Ottosen, L.M., Kirkelund, G.M., Rode, C., Peuhkuri, R., 2019.
  522 Characterization of sewage sludge ash and its effect on moisture physics of mortar. J.
  523 Build. Eng. 21, 396–403. https://doi.org/10.1016/j.jobe.2018.10.021
- Krüger, O., Adam, C., 2014. Recovery potential of German sewage sludge ash. Waste Manag.
  45, 400–406. https://doi.org/10.1016/j.wasman.2015.01.025
- Lapa, N., Barbosa, R., Lopes, M.H., Mendes, B., Abelha, P., Gulyurtlu, I., Santos Oliveira, J.,
  2007. Chemical and ecotoxicological characterization of ashes obtained from sewage
  sludge combustion in a fluidised-bed reactor. J. Hazard. Mater. 147, 175–183.
  https://doi.org/10.1016/j.jhazmat.2006.12.064
- Lewkowska, P., Cieślik, B., Dymerski, T., Konieczka, P., Namieśnik, J., 2016. Characteristics
  of odors emitted from municipal wastewater treatment plant and methods for their
  identification and deodorization techniques. Environ. Res. 151, 573–586.
  https://doi.org/10.1016/j.envres.2016.08.030
- Li, J., Geng, G., Myers, R., Yu, Y.-S., Shapiro, D., Carraro, C., Maboudian, R., Monteiro,
  P.J.M., 2019. The chemistry and structure of calcium (alumino) silicate hydrate: A study
  by XANES, ptychographic imaging, and wide- and small-angle scattering. Cem. Concr.

- 503 Res. 115, 367–378. https://doi.org/https://doi.org/10.1016/j.cemconres.2018.09.008
- Li, J., Geng, G., Zhang, W., Yu, Y.-S., Shapiro, D.A., Monteiro, P.J.M., 2018. The Hydration
  of β-and α' H-Dicalcium Silicates: An X-ray Spectromicroscopic Study. ACS Sustain.
  Chem. Eng. 7, 2316–2326.
- Li, J., Poon, C.S., 2017. Innovative solidification/stabilization of lead contaminated soil using
  incineration sewage sludge ash. Chemosphere 173, 143–152.
  https://doi.org/10.1016/j.chemosphere.2017.01.065
- Li, J.S., Guo, M.Z., Xue, Q., Poon, C.S., 2017. Recycling of incinerated sewage sludge ash and
  cathode ray tube funnel glass in cement mortars. J. Clean. Prod. 152, 142–149.
  https://doi.org/10.1016/j.jclepro.2017.03.116
- Lima, F. de, Ingunza, D., Pilar, M. del, 2015. Effects of Sewage Sludge Ashes Addition in
  Portland Cement Concretes, in: Proceedings of the 2nd International Conference on Civil,
  Materials and Environmental Sciences. Atlantis Press, Paris, France, pp. 189–191.
  https://doi.org/10.2991/cmes-15.2015.55
- Lin, D.F., Lin, K.L., Chang, W.C., Luo, H.L., Cai, M.Q., 2008. Improvements of nano-SiO2
  on sludge/fly ash mortar. Waste Manag. 28, 1081–1087.
  https://doi.org/10.1016/j.wasman.2007.03.023
- Lin, D.F., Lin, K.L., Luo, H.L., Xu, J.Q., 2016. Acid-alkali resistance of new reclaimed tiles
  containing sewage sludge ash and waste glass. Materials (Basel). 9, 546.
  https://doi.org/10.3390/ma9070546
- Lin, D.F., Luo, H.L., Lin, K.L., Liu, Z.K., 2017. Effects of waste glass and waste foundry sand
  additions on reclaimed tiles containing sewage sludge ash. Environ. Technol. 38, 1679–
  1688. https://doi.org/10.1080/09593330.2017.1296891
- Lin, K.L., 2006. Mineralogy and microstructures of sintered sewage sludge ash as lightweight
  aggregates. J. Ind. Eng. Chem. 12, 425–429.
- Liu, J., Huang, S., Sun, S., Ning, X., He, R., Li, X., Chen, T., Luo, G., Xie, W., Wang, Y., Zhuo,
  Z., Fu, J., 2015. Effects of sulfur on lead partitioning during sludge incineration based on
  experiments and thermodynamic calculations. Waste Manag. 38, 336–348.
  https://doi.org/10.1016/j.wasman.2014.11.021
- Lu, J.-X., Zhou, Y., He, P., Wang, S., Shen, P., Poon, C.S., 2019. Sustainable reuse of waste
  glass and incinerated sewage sludge ash in insulating building products: Functional and
  durability assessment. J. Clean. Prod. 236, 117635.
  https://doi.org/10.1016/j.jclepro.2019.117635
- Lu, T., Yuan, H., Wang, Y., Huang, H., Chen, Y., 2016. Characteristic of heavy metals in

- biochar derived from sewage sludge. J. Mater. Cycles Waste Manag. 18, 725–733.
  https://doi.org/10.1007/s10163-015-0366-y
- Lynn, C.J., Dhir, R.K., Ghataora, G.S., West, R.P., 2015. Sewage sludge ash characteristics and
  potential for use in concrete. Constr. Build. Mater. 98, 767–779.
  https://doi.org/10.1016/j.conbuildmat.2015.08.122
- MacKenzie, K.J.D., Smith, M.E.B.T.-P.M.S. (Eds.), 2002. Chapter 4 29Si NMR, in:
  Multinuclear Solid-State NMR of Inorganic Materials. Pergamon, pp. 201–268.
  https://doi.org/https://doi.org/10.1016/S1470-1804(02)80005-0
- 511 Mádai, F., Kristály, F., Mucsi, G., 2015. Microstructure, mineralogy and physical properties of
  512 ground fly ash based geopolymers. Ceram. Silikaty.
- Marani, D., Braguglia, C.M., Mininni, G., Maccioni, F., 2003. Behaviour of Cd, Cr, Mn, Ni,
  Pb, and Zn in sewage sludge incineration by fluidised bed furnace. Waste Manag. 23,
  117–124. https://doi.org/10.1016/S0956-053X(02)00044-2
- Mejdi, M., Saillio, M., Chaussadent, T., Divet, L., Tagnit-Hamou, A., 2020. Hydration
  mechanisms of sewage sludge ashes used as cement replacement. Cem. Concr. Res. 135,
  106115. https://doi.org/10.1016/j.cemconres.2020.106115
- Monzó, J., Paya, J., Borrachero, M. V., Córcoles, A., 1996. Use of sewage sludge ash (SSA)cement admixtures in mortars. Cem. Concr. Res. 26, 1389–1398.
  https://doi.org/10.1016/0008-8846(96)00119-6
- Monzo, J., Paya, J., Borrachero, M. V, Bellver, A., Peris-Mora, E., 1997. Study of cementbased mortars containing Spanish ground sewage sludge ash, in: Studies in Environmental
  Science. Elsevier, pp. 349–354.
- Mozo, W., Gomez, A., 2016. Biosolids and biosolid ashes as inputs for producing construction
  materials such as bricks-like Construction Materials. Tecciencia 11, 45–51.
  https://doi.org/10.18180/tecciencia.2016.21.8
- Naamane, Sara, Rais, Z., Taleb, M., 2016. The effectiveness of the incineration of sewage
  sludge on the evolution of physicochemical and mechanical properties of Portland cement.
  Constr. Build. Mater. 112, 783–789. https://doi.org/10.1016/j.conbuildmat.2016.02.121
- Naamane, S, Rais, Z., Taleb, M., Mtarfi, N.H., Sfaira, M., 2016. Sewage sludge ashes:
  Application in construction materials. J. Mater. Environ. Sci. 7, 67–72.
  - Nieto, A., Borrull, F., Pocurull, E., Marcé, R.M., 2010. Pressurized liquid extraction: A useful technique to extract pharmaceuticals and personal-care products from sewage sludge. TrAC - Trends Anal. Chem. 29, 752–764. https://doi.org/10.1016/J.TRAC.2010.03.014
  - Pan, S.C., Tseng, D.H., Lee, C.C., Lee, C., 2003. Influence of the fineness of sewage sludge

534

535

- ash on the mortar properties. Cem. Concr. Res. 33, 1749–1754.
  https://doi.org/10.1016/S0008-8846(03)00165-0
- Pérez-Carrión, M., Baeza-Brotons, F., Payá, J., Saval, J.M., Zornoza, E., Borrachero, M. V.,
  Garcés, P., 2014. Potential use of sewage sludge ash (SSA) as a cement replacement in
  precast concrete blocks. Mater. Construcción 64, e002.
  https://doi.org/10.3989/mc.2014.06312
- 509 Piasta, W., Lukawska, M., 2016. The effect of sewage sludge ash on properties of cement
- 510 composites. Procedia Eng. 161, 1018–1024. https://doi.org/10.1016/j.proeng.2016.08.842
- 511Rentsenorov, U., Davaabal, B., Temuujin, J., 2018. Synthesis of zeolite a from mongolian coal
- fly ash by hydrothermal treatment, in: Solid State Phenomena. Trans Tech Publ, pp. 1–8.
  https://doi.org/10.4028/www.scientific.net/SSP.271.1
- Richardson, I.G., Girão, A. V., Taylor, R., Jia, S., 2016. Hydration of water- and alkali-activated
  white Portland cement pastes and blends with low-calcium pulverized fuel ash.
  Cem. Concr. Res. 83, 1–18. https://doi.org/10.1016/j.cemconres.2016.01.008
- Rutkowska, G., Wichowski, P., Franus, M., Mendryk, M., Fronczyk, J., 2020. Modification of
  Ordinary Concrete Using Fly Ash from Combustion of Municipal Sewage Sludge.
  Materials (Basel). 13, 487. https://doi.org/10.3390/ma13020487
- Rutkowska, G., Wichowski, P., Fronczyk, J., Franus, M., Chalecki, M., 2018. Use of fly ashes
  from municipal sewage sludge combustion in production of ash concretes.
  Constr. Build. Mater. 188, 874–883. https://doi.org/10.1016/j.conbuildmat.2018.08.167
- Samolada, M.C., Zabaniotou, A.A., 2014. Comparative assessment of municipal sewage sludge
  incineration, gasification and pyrolysis for a sustainable sludge-to-energy management in
  Greece. Waste Manag. 34, 411–420. https://doi.org/10.1016/j.wasman.2013.11.003
- Schöler, A., Lothenbach, B., Winnefeld, F., Zajac, M., 2015. Hydration of quaternary Portland
  cement blends containing blast-furnace slag, siliceous fly ash and limestone powder.
  Cem. Concr. Compos. 55, 374–382. https://doi.org/10.1016/j.cemconcomp.2014.10.001
- Scrivener, K.L., Juilland, P., Monteiro, P.J.M., 2015. Advances in understanding hydration of
  Portland cement. Cem. Concr. Res. 78, 38–56.
  https://doi.org/10.1016/j.cemconres.2015.05.025
- Snellings, R., Li, X., Avet, F., Scrivener, K., 2019. A Rapid, Robust, and Relevant (R3)
  Reactivity Test for Supplementary Cementitious Materials. ACI Mater. J. 116.
  https://doi.org/10.14359/51716719

- Spinosa, L., Ayol, A., Baudez, J.-C., Canziani, R., Jenicek, P., Leonard, A., Rulkens, W.,
  Xu, G., Van Dijk, L., 2011. Sustainable and innovative solutions for sewage sludge
  management. Water 3, 702–717. https://doi.org/10.3390/w3020702
  Suksiripattanapong, C., Horpibulsuk, S., Boongrasan, S., Udomchai, A., Chinkulkijniwat, A.,
- Arulrajah, A., 2015. Unit weight, strength and microstructure of a water treatment sludgefly ash lightweight cellular geopolymer. Constr. Build. Mater. 94, 807–816.
  https://doi.org/10.1016/j.conbuildmat.2015.07.091
- Świerczek, L., Cieślik, B., 2018. Determination of metal content in sewage sludge and sewage
  sludge ash to find opportunities to use them in the construction industry. World Sci. News
  110, 227–235.
- Tang, P., Zhao, Y.C., Chen, D.Z., Xia, F.Y., 2008. Volatility of heavy metals during
  incineration of tannery sludge in the presence of chlorides and phosphoric acid. Waste
  Manag. Res. 26, 369–376. https://doi.org/10.1177/0734242X08092024
- Tashima, M.M., Reig, L., Santini, M.A., B Moraes, J.C., Akasaki, J.L., Payá, J., Borrachero,
  M. V., Soriano, L., 2017. Compressive strength and microstructure of alkali-activated blast
  furnace slag/sewage sludge ash (GGBS/SSA) blends cured at room temperature. Waste
  and Biomass Valorization 8, 1441–1451. https://doi.org/10.1007/s12649-016-9659-1
- Tay, J.H., Show, K.Y., 1994. Municipal wastewater sludge as cementitious and blended cement
   materials. Cem. Concr. Compos. 16, 39–48.
   https://doi.org/10.1016/0958-9465(94)90029-9
- 524 TCLP Method 1311, 1992. Toxicity Characteristic Leaching Procedure, DC: U.S.
  525 Environmental Protection Agency (EPA).
- Van de Velden, M., Dewil, R., Baeyens, J., Josson, L., Lanssens, P., 2008. The distribution of
  heavy metals during fluidized bed combustion of sludge (FBSC). J. Hazard. Mater. 151,
  96–102. https://doi.org/10.1016/j.jhazmat.2007.05.056
- Vouk, D., Nakic, D., Štirmer, N., Baricevic, A., 2017. Effect of lime addition during sewage
  sludge treatment on characteristics of resulting SSA when it is used in cementitious
  materials. Water Sci. Technol. 75, 856–863. https://doi.org/10.2166/wst.2016.554

Vouk, D., Nakic, D., Stirmer, N., Cheeseman, C., 2018. Influence of combustion temperature on the performance of sewage sludge ash as a supplementary cementitious material.
J. Mater. Cycles Waste Manag. 20, 1458–1467. https://doi.org/10.1007/s10163-018-0707-8

532

533

534

- Vouk, Dražen, Serdar, M., Vučinić, A.A., 2017. Use of incinerated sewage sludge ash in cement
  mortars: case study in Croatia. Teh. Vjesn. Tech. Gaz. 24.
  https://doi.org/10.17559/TV-20150901095705
- Wey, M.Y., Liu, K.Y., Yu, W.J., Lin, C.L., Chang, F.Y., 2008. Influences of chlorine content
  on emission of HCl and organic compounds in waste incineration using fluidized beds.
  Waste Manag. 28, 406–415. https://doi.org/10.1016/j.wasman.2006.12.008
- 510 Wzorek, M., Tańczuk, M., 2015. Production of biosolid fuels from municipal sewage sludge:
  511 Technical and economic optimisation. Waste Manag. Res. 33, 704–714.
  512 https://doi.org/10.1177/0734242X15588584
- Yan, K., Guo, Y., Ma, Z., Zhao, Z., Cheng, F., 2018. Quantitative analysis of crystalline and
  amorphous phases in pulverized coal fly ash based on the Rietveld method. J. Non. Cryst.
  Solids 483, 37–42.
- Yang, T., Huang, H., Lai, F., 2017. Pollution hazards of heavy metals in sewage sludge from
  four wastewater treatment plants in Nanchang, China. Trans. Nonferrous Met. Soc. China
  27, 2249–2259. https://doi.org/10.1016/S1003-6326(17)60251-6
- Youcai, Z., Stucki, S., Ludwig, C., Wochele, J., 2004. Impact of moisture on volatility of heavy
  metals in municipal solid waste incinerated in a laboratory scale simulated incinerator.
  Waste Manag. 24, 581–587. https://doi.org/10.1016/j.wasman.2004.01.004
- Yusuf, R.O., Noor, Z.Z., Moh', N.A., Moh', d F., Din, D., Abba, A.H., 2012. Use of sewage
  sludge ash (SSA) in the production of cement and concrete a review. Int. J. Glob.
  Environ. Issues 12, 214. https://doi.org/10.1504/IJGENVI.2012.049382
- Záleská, M., Pavlík, Z., Pavlíková, M., Scheinherrová, L., Pokorný, J., Trník, A., Svora, P., 525 Fořt, J., Jankovský, O., Suchorab, Z., Černý, R., 2018. Biomass ash-based mineral 526 admixture prepared from municipal sewage sludge and its application in cement 527 composites. Clean Technol. Environ. Policy 20, 159–171. 528 https://doi.org/10.1007/s10098-017-1465-3 529
- Zhang, Z., Zhang, L., Yin, Y., Liang, X., Li, A., 2015. The recycling of incinerated sewage
  sludge ash as a raw material for CaO-Al2O3-SiO2-P2O5 glass-ceramic production.
  Environ. Technol. 36, 1098–103. https://doi.org/10.1080/09593330.2014.982208