

Chitosan-based modalities with multifunctional attributes for adsorptive mitigation of hazardous metal contaminants from wastewater



Shan E.Zehra Syeda*, Muhammad Shahzeb Khan, Anna Maria Skwierawska

Department of Chemistry and Technology of Functional Materials, Faculty of Chemistry, Gdańsk University of Technology, 11/12 Narutowicza Street, 80-233 Gdańsk, Poland

ARTICLE INFO

Keywords:

Water pollution
Heavy metals
Chitosan-based adsorbents
Environmental toxicity

ABSTRACT

The increase in population and industrialization has intensified water scarcity and stress, and contaminated water bodies. Therefore, the development of advanced water and wastewater treatment technologies has gained global attention from researchers. Adsorption, using natural materials (nano, polymer, and bio) is one of the most cost-effective, less challenging, and well-known technologies for wastewater treatment and improving water quality. Among them, chitosan (CS) has demonstrated a set of unique features, such as biodegradability, eco-friendliness, availability, low cost, and biocompatibility. Hence, this review provides an overview of some recent advancements in the removal of heavy metals, including As (III) and (V), Cd (II), Cu (II), Cr (VI), and Pb (II) by CS-based adsorbents, and their potential effects on human health. It also covers the synthesis of CS-based adsorbents for the elimination of mentioned contaminants in recently reported studies. In addition, this study recommends encountering potential drawbacks by enhancing the adsorption capacity by incorporating functional groups, nanoparticles, and other materials. These modifications may help increase selectivity for specific metal contaminants and synthesize adsorbents that can perform better over a wide range of pH. Insights gained from this study will guide researchers in the future toward optimal water treatment and pollutant elimination strategies.

1. Introduction

The world is now more concerned with the simultaneous problems of water scarcity and contamination than ever before. These are complex issues that require a variety of approaches to solve. The urgent challenges of both quantity and quality have become more linked as growing populations and expanding industrial activity increase the burden on water resources [1]. Pollutants including heavy metals, industrial effluents, and agricultural runoff contaminate water, making a large amount of available water sources unfit for human consumption and exacerbating the scarcity issue. A critical turning point has been reached in the navigation of the complicated terrain of water management: improved water treatment technology. These technologies have become essential in lessening the effects of contamination on water resources as a result of the realization that focused and effective cleanup solutions are required. Now, let us examine this groundbreaking trip from the general problems of water scarcity and contamination to the field of cutting-edge water treatment technologies, clarifying the rationale for our work and its contributions. Researchers from across the globe have been trying to resolve water-related issues

and remove the contamination from the water. Water contamination has caused many human health issues, and about 0.7 million people die from water-related diseases around the globe [2]. The most common water contaminants include dyes, heavy metals, and phenols [3]. Heavy metal's presence in water has gained more attention due to their higher toxic levels and carcinogenic effects on the health of human beings at even lower concentrations [4]. They lead to acute and chronic effects such as different kinds of cancers, improper development of organs, nerve damage, and even death [5]. After the industrial revolution, the world has seen drastic growth in industrial and economic sectors that has also contributed to the heavy metals accumulation on the surface and groundwater which has sought global attention [6–9]. As a consequence, the researchers have shifted their focus to the quantification of heavy metals and their overall effects on human life [8,10–13]. The heavy metals have different toxic levels due to their chemical properties and characteristics, and they pose different health implications discussed later in this review.

Within the broad field of water treatment techniques, various technologies are essential in tackling the intricate problems related to water quality. Among them are processes such as membrane filtration,

* Corresponding author.

E-mail address: abc@123.com (S.E.Z. Syeda).

chemical precipitation, electrochemical reactions, and others that are noteworthy due to their unique mechanisms and uses.

Membrane filtration uses semi-permeable membranes to filter impurities and particles from water according to their molecular weight and size. Chemical precipitation is the process of adding chemicals to create precipitates that are insoluble and readily separated from water. Electrical current is used in electrochemical processes to create reactions that help remove or change pollutants. Although there is a wide range of water treatment technologies available, this article deliberately focuses its discussion on one aspect: adsorption. One well-known and adaptable technology that is particularly notable for its effectiveness in reducing water pollution is adsorption. It has gained recognition for its low cost, easy operation [14] and modifications, high effectiveness, sludge-free operation, easy recovery, and regeneration capacity [15]. For the removal of heavy metal ions (HMIs), activated carbon has been widely used; however, it has limitations due to its high cost, and it also causes secondary pollution [16]. Several other adsorbents have been used to eliminate HMIs, including nanomaterial adsorbents, bio adsorbents, industrial by-products, and their composite.

The adsorbents prepared using CS exhibit commendable efficiency in removing dyes, heavy metals, pesticides, and pharmaceutical pollutants from water. They have distinctive features, helping with selective adsorption, and are very versatile for environmental applications [17–23]. Many efforts have been in progress on using CS and its derivatives for dye removal and HMI removal from water and wastewater [24–31]. However, there is still a gap to be filled, and we believe this critical review helps researchers to work more efficiently in this field of study. This review includes the synthesis of CS-based adsorbents, their mechanism and characteristics for removing heavy metals from the environment, their interaction with human health, and the reasons for deteriorating the human body with several diseases. This article also discussed the major heavy metal ions and their chemical interaction with CS-based adsorbents. In this era of development, research plays a significant part in the progress of academic society and institutions. Moreover, this review will open doors of knowledge for the researcher and provide the gap in this field of research, and it will create pathways to achieve sustainable development goals (SDGs) and bring opportunities for better living on the planet Earth.

CS is derived from the partial deacetylation of chitin (Fig. 1) and is the second ample natural polymer in shrimp shells, crab shells, and

some fungi [32]. CS is obtained by removing acetyl groups from chitin to the extent of about 50%. The resulting structure is heterogeneous and consists of both 1–4 linked 2-acetamido-2-deoxy- β -D-glucopyranoses and 2-amino-2-deoxy- β -D-glucopyranoses as well as 2-amino-2-deoxy- β -D-glucopyranose (as shown in Fig. 2a and b).

Given structure, CS is similar to cellulose; as hydroxyl in cellulose is replaced by amino or acetamido groups in CS at carbon-2 [33]. CS and its derivatives have shown extraordinary results in the fields of pharmacy [34], medicine [35], chemistry [36], and environment [37] because they have specific characteristics that include low toxicity, high adsorption capability, biocompatibility, and biodegradability. Environmental engineers have reported successful results in removing heavy metals and treating water. CS derivatives have been found to remove pigments [38], fluorides [39], and phenols [40]. CS has not only shown remarkable results for the removal of HMIs but also has shown antibacterial properties [41]. The preparation of CS and its derivatives-based adsorbents, adsorption mechanism, and application studies have been discussed briefly in detail in this review.

2. Chitosan-based adsorbents

CS was first obtained by Rouget in 1859 when boiling chitin in the concentrated potassium hydroxide (KOH) [42,43], and later, Hoppe-Seyler named it in 1894. CS has been considered one of the most useful cationic adsorbents for removing aromatic compounds, highly toxic organic dyes, heavy metals, anions, pharmaceutical residues, and oil spills [44–48]. It holds several advantages, such as hydrophilicity, high reactivity, biodegradability, biocompatibility, and nontoxicity [49]. It is a multifunctional biopolymer and has unique properties that make it useful for treating water, especially in adsorption operations. It is environmentally friendly because it is naturally biocompatible and biodegradable. Because positively charged amino groups on CS and negatively charged ions have a favorable interaction, CS's cationic composition allows for the effective adsorption of anionic pollutants, like heavy metals. Its adsorption capacity is enhanced by its high surface area and porous structure, which offer a multitude of active sites for pollutant binding. Amino and hydroxyl functional groups, for example, contribute to a variety of interactions with different pollutants. The capacity to produce films makes it possible to create coatings that function as efficient adsorption layers. Because it can be easily




Fig. 1. Representation of CS recovery from shrimps.




Fig. 2. a. Chemical structure of Chitin, Fig. 2b. Chemical structure of chitosan.,.




Fig. 2. (continued)

altered, customized improvements can be made, and because it is inexpensive and frequently derived from crustacean shells, water treatment procedures become more financially feasible. To summarize, it is a valuable and sustainable adsorbent for water treatment applications due to its unique mix of biocompatibility, cationic nature, high surface area, and adaptability. Moreover, Table 1 presents several conventional and non-conventional adsorbents and their features for removing contaminants from the water.

Table 1

Various conventional and non-conventional adsorbents with their features.

Adsorbents	Features	Type of adsorbent	Ref
Activated alumina	<ul style="list-style-type: none"> - Efficient for the removal of organic pollutants and bacteria - Commercially available 	Conventional	[56]
Agricultural waste	<ul style="list-style-type: none"> - Efficient - Rapid 	Conventional	[57]
Biomass obtained via microorganism	<ul style="list-style-type: none"> - More selective & effective from the ionic adsorbent 	Non-Conventional	[58]
Chitin/CS (Chitosan based derivatives)	<ul style="list-style-type: none"> - Biodegradable - Cheap - Abundant - Renewable - Exemplary diffusion properties - High Swelling properties 	Non-Conventional	[59]
Coconut waste (shell)	<ul style="list-style-type: none"> - Works in the granular form - Wastewater treatment 	Conventional	[60]
Cross-linked polymers	<ul style="list-style-type: none"> - Surface area is more - Mechanical strength is high - Has chelating properties 	Conventional	[61]
Hydrogel	<ul style="list-style-type: none"> - Efficient for metal recovery (not all types) 	Non-Conventional	[62]
Polysaccharide	<ul style="list-style-type: none"> - Low-cost and highly selective 	Non-Conventional	[63]
Resins	<ul style="list-style-type: none"> - Wastewater treatment 	Conventional	[64]
Silica gel	<ul style="list-style-type: none"> - Efficient for removing organics 	Conventional	[65]
Solid waste from the forest industry	<ul style="list-style-type: none"> - Possible degeneration - Cheap - Effective 	Non-Conventional	[66]
Wood waste	<ul style="list-style-type: none"> - Efficient for large-scale pollutants - Good surface phenomenon 	Conventional	[67]
Zeolites	<ul style="list-style-type: none"> - Good adsorbent for organic solvents and dyes - High Ion exchange capacity 	Conventional	[68]

Furthermore, CS has a linear polyamine structure with free amine groups accessible for modifications and crosslinking [50]. Several chemical and physical modification techniques have been applied to improve its adsorption selectivity and characteristics for removing heavy metals, including amination, sulfonation, and carboxymethylation [51–55].

3. Chitosan for HMI removal

They have been proven efficient for absorbing toxic heavy metal ions from water and wastewater due to various chelation sites and hydroxyl and amino functional groups that attract heavy metals using ion exchange methods or coordination bonds [69,70]. Many researchers have analyzed and evaluated the adsorption capacities of CS and their derivatives to remove HMIs as their application studies [71–73]. Fig. 3 shows the mechanism of CS-based adsorbent for the removal of heavy metals from the water.

This study includes various studies on removing metals (As, Cd, Cr, Cu, and Pb) from the wastewater through an adsorption mechanism using CS-based adsorbents. The complex relationship between CS-based adsorbents and different heavy metal ions requires a careful analysis of their interactions. Arsenic compounds, such as arsenic (III) and arsenic (V), use their hydroxyl and amino groups to form complexes and create hydrogen bonds, respectively. Lead ions (II) mostly stick to the amino




Fig. 3. Schematic diagram for the removal of heavy metals by CS-based adsorbents.

groups of CS through coordination bonds, highlighting the need to assess the density and accessibility of these amino groups. Chromium (VI) binding to CS may include redox reactions, emphasizing the need to understand electron transfer mechanisms. Cobalt ions (II) show preferential adsorption aided by the amino groups of CS, requiring a comprehensive study of its ability to form chelation complexes and coordinate bonds. Likewise, copper ions (II) bind with the amino groups of CS, which requires examination of the surface charge and the kinetics of complex formation. Comprehending these complex interactions is crucial for improving CS-based adsorbents in order to improve their effectiveness in reducing heavy metal pollution in the waste water

treatment applications. Fig. 4 shows the adsorption mechanism of heavy metals on CS-based adsorbents.

Understanding the details of the heavy metal adsorption on CS-based adsorbents requires a thorough examination of kinetics, isotherms, and thermodynamics. Kinetic studies provide vital information on the time-dependent behavior of adsorption processes, giving important details about the speed and mechanisms that control the absorption of metal ions. Methods include being influenced by time batch adsorption tests and the use of kinetic models help to understand adsorption kinetics and determine the time needed to reach equilibrium. This information is important for designing and optimizing systems.




Fig. 4. Adsorption mechanism.

Isotherm analyses define the balance between the concentration of metal ions and their adsorption onto CS. This provides important information on the maximal capacity for adsorption, the characteristics of the surface, and the affinity of the adsorbent for different metal ions. Using well-known isotherm models, such as Langmuir, Freundlich, and Dubinin-Radushkevich, allows for the determination of important isotherm parameters from experimental data, which improves the ability to predict adsorption behavior in different settings.

In addition, thermodynamic studies offer a basic understanding of the spontaneity, possibility, and energy involved in metal adsorption onto CS. By conducting experiments at various temperatures and utilizing thermodynamic models like the Van't Hoff equation, important thermodynamic values like as standard enthalpy (ΔH°), standard entropy (ΔS°), and Gibbs free energy (ΔG°) can be determined. These factors provide information about the stability of metal-chitosan complexes and the impact of temperature on adsorption behavior, helping to optimize operational settings for practical use. To summarize, a thorough analysis of the speed of reactions, temperature effects, and energy changes is essential for improving the efficiency of removing heavy metals from water using CS-based adsorbents. This analysis provides important guidance for designing water treatment systems and implementing effective environmental cleanup strategies.

3.1. Removal of Arsenic

Arsenic (As) is a metalloid in the air, rocks, organisms, soil, and water. It has been a source of environmental pollution using natural processes and a combination of anthropogenic activities, including biological actions, weathering reactions, and vehicular and other emissions [74]. Fig. 5 elucidates the natural and anthropogenic sources of As contamination. Moreover, it is among the elements that are multivalent and cannot be easily removed, though, it can convert into several different forms or combine with other elements [75]. However, the most dominant and toxic forms of arsenic include arsenite and arsenate [76].

Due to its toxicity, the World Health Organization (WHO) in 1993 reduced the exposure limit of arsenic from 50 to 10 μg^{-1} [78]. Until today, many researchers have used advanced adsorbents to remove As from wastewater [70], however, many drawbacks need to be addressed.

Recently, CS has gained drastic attention for its exceptional characteristics for arsenic removal application from the waters [79]. Utilizing gel, microsphere, and cross-linker of CS are a few advanced techniques that help to enhance mechanical strength, stability, and its

reusability; embedding molybdenum or iron, etc., into CS microsphere is an efficient technique to increase the adsorption property of CS [80–82]. Furthermore, iron (Fe) is always considered an arsenic lover as it possesses excellent adsorption properties towards As. Interestingly, the Fe-CS composite has gained attention for adsorption from water; Fe-CS granules (ICSB) and Fe-CS flakes (ICSF) have also been studied and reported [83].

Among several studies in the last decade that were carried out to analyze the adsorption capacity and efficiency of As (III); graphene oxide (GO), GO-modified CS derivative is recognized as a cost-effective (cheap) and efficient adsorbent [84–86], and graphene oxide-chitosan (GO-CS) has various application studies other than As. In a study, both toxic forms of As were removed from contaminated water with clays or zeolite CS-based adsorbents. In addition to other research, Wang and coauthors experimented with the CS coating biopolymer on iron oxide nanoparticles, showing a significant increase in As adsorption (V) [87]. Table 2 summarizes the q_{max} for arsenic on several CS-based adsorbents.

CS-based adsorbents have a remarkable ability to adsorb arsenic thanks to their positive charge, which allows them to interact with negatively charged arsenic species. In addition, these materials have a high level of compatibility with biological systems and are also environmentally friendly, which helps to minimize any potential risks to both human health and the environment. Nevertheless, the relatively sluggish adsorption kinetics of these substances may necessitate longer contact durations, while the pH dependence may present difficulties in upholding ideal conditions. In addition, the restricted surface area of CS matrices may limit their adsorption capacity in comparison to other materials.

3.2. Removal of Cadmium

Cadmium (Cd) is among the extremely toxic elements due to its teratogenic and carcinogenic effects on human life [95]. It is disposed of majorly into the environment through human-made activities due to mining operations, industrial effluent, waste incineration, and coal and oil combustion. Fig. 6 shows the different sources of cadmium contamination. According to WHO, the maximum permissible limit of Cd in potable water is 3–5 ppb [96]. Among several other adsorbents utilized to remove cadmium, hydrogels, and CS-based composites have acquired great attention [97].

Babakhani and coauthors reported an efficient, low-cost, and effective technique for removing Cd (II) from wastewater using a benign




Fig. 5. Schematic diagram of As contamination and health effects [77].

Table 2
Chitosan-based adsorbents for the removal of Arsenic (As).

Adsorbent	Arsenic (III/V)	Maximum Adsorption Capacity (mg g^{-1})	Isotherms model	Kinetics model	Surface area	Contact time (min)	pH	Ref
Iron (III)-Chitosan	(III)	19.7	Langmuir	-	-	-	6	[88]
Fe CS Microspheres	(V)	120.7	Langmuir	2nd Order	1.3 mm (dia)	1440	4 – 9	[89]
α -FeO(OH)/GO/CS	(III)	289.4	Freundlich & Sips	2nd Order	-	3000	3 – 10	[85]
Magnetic CS-coated GO	(III)	45.0	Langmuir	2nd Order	$152 \text{ m}^2 \text{ g}^{-1}$	-	7.3	[84]
Chitosan coated Iron magnetite nanoparticles	(V)	10.8	Langmuir	2nd Order	-	120	7	[90]
MCS/GO with ethylenediamine tetraacetic acid (EDTA)	(III)	43.0	Langmuir	2nd Order	$81.36 \text{ m}^2 \text{ g}^{-1}$	660	8.0	[91]
Chitosan coated Iron magnetite	(III)	10.5	Langmuir	2nd Order	10 nm (dia)	90	9	[92]
Magnetite nanoparticles impregnated chitosan beads	(V)	35.7	Langmuir	2nd Order	$50.20 \text{ m}^2 \text{ g}^{-1}$	1500	6.8	[93]
CCM	(V)	3.4	Freundlich	2nd Order	$5.1 \text{ m}^2 \text{ g}^{-1}$	-	3 – 9	[94]
Iron-Chitosan composite	(III)	16.2	Langmuir	-	$96.8 \text{ m}^2 \text{ g}^{-1}$	-	7.0	[83]
Iron-CS composite	(V)	22.5	Langmuir	-	$96.8 \text{ m}^2 \text{ g}^{-1}$	-	7.0	[83]




Fig. 6. Different sources of Cd contamination.

adsorbent. Sodium tripolyphosphate CS beads (STPP-CLCS) were fabricated to access cross-linked CS adsorption capacity and behavior. In the experiment, the lower cross-linked beads revealed a higher concentration of adsorption when the concentration of Cd was low; consequently, the lower CS beads had higher adsorption even at a higher concentration [98]. In a recent study, a hollow nanofibrous membrane (HNM) was synthesized from CS, polyvinyl alcohol (PVA), and polyvinylpyrrolidone (PVP) through electrospinning. It was analyzed on lead, nickel, cadmium, and copper, and maximum adsorption capacities were 87.8 , 97.5 , 88.1 , and 106.7 mg g^{-1} [99]. In another study, biocomposites based on clay minerals and CS have gained interest in removing cadmium, and Vilela reported the maximum adsorption capacity was 234.8 mg g^{-1} onto the CS-based hydrogel [100]. In a study, Chen et al., 2012 prepared an effective new composite of CS with thiourea, modified it to a magnetic ion, and imprinted it on CS/TiO₂ (MICST). Later, results found that the MICST's efficiency in removing Cd (II) decreased barely after the fifth cycle.

In another attempt, Chen and coauthors prepared CS-vermiculite (CS-VMT) in reaction with epichlorohydrin and used it for the removal of Cd (II) from water. The results showed that on the external surface, CS was cross-linked but could not intercalate in the vermiculite [104]. Also, Wang and coauthors (2020) also synthesized a low-cost and novel cobalt ferrite@SiO₂-CS/EDTA composite with higher adsorption capacity of cadmium and recyclability using sol-gel and solvothermal process [102]. Table 3 summarizes q_{max} for Cd on CS-based adsorbent.

CS-based adsorbents have been found to exhibit remarkable selectivity for cadmium, thanks to the strong metal-ligand interactions they form. This property effectively reduces interference from other ions, making them highly effective in Cd removal. Its remarkable versatility enables the creation of customized adsorbents that exhibit a heightened affinity for cadmium ions. Additionally, its biodegradability helps minimize any potential negative effects on the environment. Nevertheless, the adsorption behavior that is dependent on pH and the limited surface area may necessitate optimization in order to achieve

Table 3
Several CS-based adsorbents for the removal of Cadmium (Cd).

Adsorbent	Maximum Adsorption Capacity (mg g^{-1})	Isotherms model	Kinetics model	Surface area	Contact time	pH	References
Chitosan/PVP/PVA-HNM	88.1	Langmuir	2nd Order	$17.16 \text{ m}^2 \text{ g}^{-1}$	-	7	[99]
Chitosan and pectin beads	177.6	Langmuir	2nd Order	$23.66 \text{ m}^2 \text{ g}^{-1}$	380	7	[101]
STPP-CLCS	99.8	Langmuir	-	-	-	4 – 8.5	[98]
CoFe_2O_4 @ SiO_2 -CS/EDTA	127.8	Langmuir	-	$17.57 \text{ m}^2 \text{ g}^{-1}$	180	2 – 7	[102]
Chitosan/PVA/PEL	11.1	Langmuir	2nd Order	$0.95 \text{ m}^2 \text{ g}^{-1}$	-	6	[103]
Chitosan-VMT composite	58.5	Langmuir	2nd Order	$7.91 \text{ m}^2 \text{ g}^{-1}$	1400	4	[104]
Chitosan@NZVI	142.8	Freundlich	2nd Order	$78.3 \text{ m}^2 \text{ g}^{-1}$	180	4 – 9	[105]
Vermiculite (Vm) blended with CS	169.0	Langmuir	2nd Order	-	300	5.0 – 5.5	[106]
$\text{Ca}_5(\text{PO}_4)_3/\text{CS}$	81.1	Langmuir	2nd Order	-	1440	9	[107]
MICST	256.4	Langmuir	2nd Order	-	360	6 – 7	[108]

efficient removal. Furthermore, the process of regenerating after cadmium adsorption may pose challenges, affecting the potential for reusability and potentially leading to higher operational costs.

3.3. Removal of Chromium

Chromium (Cr) is naturally present in two oxidation states, such as chromium (III) and (VI), whereas, Cr (III) is relatively less threatening to animals and plants as compared to Cr (VI). It is widely used in various industries, including textile dyeing, steel and automobile manufacturing, leather tanning, and electroplating, and it causes a potential threat [109,110]. Fig. 7 presents the sources of chromium contamination. According to the International Agency for Research in Cancer (IRCA), Cr (VI) is carcinogenic to human beings and considered in group 1, while Cr (III) is not classified as carcinogenic [111,112].

Another study describes the synthesis of CS/polyethyleneimine fixed hydrophobic sodium alginate composite (MCPS) for sorptions of dyes and heavy metals. The maximum adsorption capacities were 351.0 for Cu, 87.5 for Cr (VI), 66.4 for methyl orange, and 286.5 mg g^{-1} for methylene blue [113]. Table 4 summarizes the maximum adsorption capacities for Cr on CS-based adsorbent.

In a study, Omer and coauthors (2021) examined the adsorption characteristics of aminated CS (AmCS)-modified MOF to remove

chromium (VI). Moreover, the result depicted that the induction of amine groups made CS neat and strengthened the cationic nature, which is more helpful in removing anionic Cr (VI) [117]. In another study, the attapulgite clay and magnetic Fe_3O_4 modified with AmCS (ATP@ Fe_3O_4 -AmCS composite) was developed by Eltaweil and co-authors in 2021 to remove anionic Cr (VI). The examination depicts rapid and efficient adsorption, and q_{max} was achieved at 294.1 mg g^{-1} [127]. Dinh (2020) reported an effective and rapid adsorption process for Cr (VI) ions onto MnO_2/CS nanocomposite. At pH 2.0 and in an hour, the adsorption efficiency reached 92% [118]. In one of the studies, fabricated CS-Fe (III) was proven efficient in removing Cr (VI) more rapidly. Furthermore, the q_{max} for removing Cr (VI) on the prepared complex was 173.1 mg g^{-1} within 10 min [125].

Chromium, specifically hexavalent chromium [Cr(VI)], is strongly attracted to CS-based adsorbents because of their exceptional ability to form robust complexes with metal ions. Due to their versatility, these substances can be easily modified to improve their ability to selectively adsorb chromium species. In addition, the matrices are biocompatible and environmentally friendly, reducing potential health and ecological hazards. Nevertheless, the effectiveness of CS-based adsorbents may be influenced by the pH of the solution, which requires precise adjustment of the solution conditions to achieve optimal chromium removal. In addition, the small size of its particles may limit their ability to adsorb




Fig. 7. Sources of Cr contamination.

Table 4
Various Chitosan-based adsorbents for the removal of Chromium (Cr).

Adsorbent	Maximum Adsorption Capacity (mg g^{-1})	Isotherm model	Kinetics model	Surface area	Contact time	pH	Ref
CS-based hydrogel	234.8	Langmuir	2nd Order	-	1440	4.5	[114]
Magnetic CS/polyethyleneimine sodium alginate	87.5	Langmuir	2nd Order	$0.0506 \text{ m}^2 \text{ g}^{-1}$	-	3	[113]
Chitosan/g- $\text{C}_3\text{N}_4/\text{TiO}_2$ nanofibers	68.9	Langmuir	2nd Order	-	1440	1–7	[115]
Citratw-cross linked Zn-MOF/chitosan composite	225.0	Langmuir	2nd Order	$16.28 \text{ m}^2 \text{ g}^{-1}$	-	5.0	[116]
zeolite imidazolate framework–67-MOF@Am-chitosan	119.1	Langmuir & Freundlich	2nd Order	$220.76 \text{ m}^2 \text{ g}^{-1}$	60	2–9	[117]
CS-MnO ₂ nanocomposite	61.6	Sips	Intra diffusion	$17.80 \text{ m}^2 \text{ g}^{-1}$	120	2	[118]
Aerogel from nano-bentonite/Nano-cellulose/chitosan	98.9	Halsey	2nd Order	-	1440	2–8	[119]
Fe ₃ O ₄ /SiO ₂ /chitosan-TETA composite	254.6	Langmuir	2nd Order	$131.4 \text{ m}^2 \text{ g}^{-1}$	-	2–8	[120]
CA- $\text{C}_6\text{H}_{10}\text{O}_2$ /chitosan nanofiber	126.0	Freundlich	2nd Order	$249.1 \text{ m}^2 \text{ g}^{-1}$	360	2–7	[121]
Fe ₃ O ₄ @SiO ₂ -chitosan	96.2	Johnson-Mehl-Avrami-Kolmogorov	2nd Order	-	-	-	[122]
Mchitosan/GO	270	Langmuir	2nd Order	$74.35 \text{ m}^2 \text{ g}^{-1}$	600	2	[123]
Chitosan/Montmorillonite- Fe ₃ O ₄ microsphere	58.8	Langmuir	2nd Order	-	180	2	[124]
Chitosan-Iron (III) complex	173.1	-	-	-	-	-	[125]
Polyethyleneimine-magnetic CS microspheres	134.9	Langmuir	2nd Order	-	300	1–8	[126]

substances, which could mean that larger amounts of the adsorbent are needed for effective treatment. In addition, the regeneration of CS matrices following chromium adsorption may present difficulties, impacting their reusability and leading to higher operational expenses.

3.4. Removal of Copper

According to the World Health Organization (WHO), Copper (Cu) is among the essential nutrients in the water for all human beings if the concentration is below 0.05 ppm [128], but if the concentration is higher, it may lead to water pollution, especially heavy metals contamination. If the concentration of Cu (II) ions gets higher in the human body, it affects the nervous system, damages the liver, and can cause cancer by triggering several mutations [129,130]. Due to anthropogenic activities, the concentration of Cu (II) is increasing in water bodies and a few reasons include electrical combustion, dyes, mining,

printing, and electroplating; hence, researchers have given great attention to the treatment of industrial effluent [102,131]. Fig. 8 shows the copper contamination and its bioaccumulation in the food chain.

In an experimental study, He et al. fabricated amidoxime-functionalized CS (AM/AO/AEBI-CS) for the removal of Cu (II). After the complete investigation, the Cu (II) adsorption capacity on the synthesized material was 190.7 mg g^{-1} [132]. In a recent study, magnetic CS hydrogel beads (MCHB) were prepared with different ratios to remove Cu (II) by blending magnetite (Fe_3O_4) and CS in the solution of sodium alginate. The highest removal efficiency for Cu (II) was 56.51 % by MCHB-0.5 and determined by several parameters (pH, contact time, and various ratios of adsorbent) [133]. Zhang et al. examined the formation of a CS membrane that was stacking and based on an electro-spinning technique and greatly enhanced the efficiency of Cu (II) adsorption on CS via multi-layer. The electro-spinning technique boosted the surface area, and the q_{max} was 276.2 mg g^{-1} [134].




Fig. 8. Flow diagram of copper contamination.

Table 5
Various Chitosan-based adsorbents for the removal of Copper (Cu).

Adsorbent	Maximum Adsorption Capacity (mg g^{-1})	Isotherm model	Kinetics model	Surface area	Contact time	pH	Ref
Chitosan/PVP/PVA-HNM	106.7	Freundlich	2nd Order	17.16	-	-	[99]
Magnetic CS/polyethyleneimine sodium alginate	351.0	Langmuir	2nd Order	0.0506	-	6	[113]
AM/AO/AEBI-CS	190.7	Sips	2nd Order	247.4 $\text{m}^2 \text{g}^{-1}$	360	2–6	[132]
DTPA-chitosan/PEO nanofibers	177.0	Langmuir	2nd Order	-	90	5	[135]
CNTs-CHO-Chitosan	115.8	Langmuir	2nd Order	-	90	2–11	[136]
Chitosan-g-MA composite	312.4	Langmuir	2nd Order	-	180	6	[137]
Chitosan/PVA/PEL membrane	86.1	Langmuir	2nd Order	0.95 $\text{m}^2 \text{g}^{-1}$	720	6	[103]
MSC/GO gel beads	55.0	Langmuir	2nd Order	-	-	1–7	[138]
Magnetic bentonite/Carboxymethyl Chitosan/SA hydrogel beads	56.8	Langmuir	2nd Order	-	240	2.0–6.3	[134]
MSC/GO	217.0	Langmuir	2nd Order	132.9 $\text{m}^2 \text{g}^{-1}$	75	7	[131]
TEPA/Chitosan/CoFe ₂ O ₄	168.1	Langmuir	2nd Order	-	50	5	[139]
MChitosan/GO with EDTA	207	Langmuir	2nd Order	81.36 $\text{m}^2 \text{g}^{-1}$	300	5.5	[91]
Chitosan-MMT hydrogel	132.7	Freundlich	2nd Order	-	-	5	[140]
Chitosan/TEOS/APTES nanofiber	640.5	Langmuir	1st Order	-	60	2–7	[141]
Zeolite X/Chitosan hybrid microspheres	152.0	Langmuir	2nd Order	406 $\text{m}^2 \text{g}^{-1}$	-	5.5	[142]
Silica/Chitosan composite	870.0	Freundlich	-	119.29 $\text{m}^2 \text{g}^{-1}$	30	1–6	[143]
Chitosan-g-PAA/APT	303.0	Langmuir	2nd Order	1.83 $\text{m}^2 \text{g}^{-1}$	180	5.85	[144]

Wang & Li prepared three-dimensional porous CS aerogels for copper ions. The CS aerogel showed low adhesion, super hydrophilicity, and selectivity. The maximum adsorption capacity was 116.7 mg g^{-1} [145]. In another experimental study, He et al. synthesized the beads of EDTA on a polyvinyl alcohol (PVA)-CS surface. In addition, newly prepared beads exhibited much better adsorption than the previously prepared beads and q_{max} was reported 127.8 mg g^{-1} of Cu (II) [146]. Wang et al., CS-g-poly modified attapulgite (CS-g-PAA/APT) for removing Cu (II) from contaminated water. This combined formation enhanced the specific porous surface and surface area; in 15 min, 90 % efficiency was reported [144]. Table 4 summarizes the q_{max} for Cu on CS-based adsorbent.

CS-based adsorbents have a remarkable ability to selectively bind copper ions, thanks to the strong interactions between the metal and the ligand. This property helps to minimize any unwanted interference from other ions present in the solution. Their compatibility with living organisms and their positive impact on the environment help mitigate the health and environmental hazards linked to copper removal procedures. In addition, the versatile nature of CS enables easy modifications to improve its capacity and selectivity for copper adsorption. CS-based adsorbents have been found to show adsorption behavior that is dependent on pH. This means that it is important to carefully adjust the solution conditions to achieve optimal copper removal. The surface area of CS particles is limited, which can restrict their adsorption capacity. As a result, higher doses of adsorbent may be necessary for effective treatment. In addition, the regeneration of CS matrices following copper adsorption could present difficulties, affecting their reusability and leading to higher operational expenses.

3.5. Removal of Lead

Lead (Pb(II)) is a persistent heavy metal that can deteriorate ecosystem and human health when it is introduced to more than 10 ppb in potable water as authorized by WHO [147,148], whereas the United States Environmental Protection Agency (US-EPA) allows 15 ppb concentration in drinking water [149,150]. Lead contamination sources are mentioned in Fig. 9.

Many studies have been reported on the development of adsorbents, such as CS, for the adsorption of Pb. In a recent study, CS and PVA were combined to remove Zn, Pb, and Fe. The maximum adsorption capacities were 4.0 for Pb, 135.1 for Fe, and 222.2 mg g^{-1} for Zn [151]. Gao and coauthors prepared alginate/melamine/chitosan (SA/ME/CS) aerogel for Lead (II) adsorption in this context. The results showed high

adsorption between pH 5–6 with a maximum adsorption capacity of 1331.6 mg g^{-1} towards Pb (II) [78]. Amin et al., synthesized magnetite nanoparticles via a thermal decomposition process and coated them with silica (mesoporous) layers using cetyltrimethylammonium bromide (CTAB) as a surfactant agent. The prepared adsorbent exhibited a maximum capacity of 150.3 mg g^{-1} for Pb^{2+} and 126.3 mg g^{-1} for Cd^{2+} [152]. Table 6 summarizes q_{max} for Pb on CS-based adsorbent.

In another research, Dinh and coworkers (2018) fabricated CS-loaded manganese dioxide (MnO_2/CS) nanoparticles where the pores surface area of MnO_2/CS was larger than the lead ions, proposing the possibility of Pb (II) ions to enter in the surface of the beads [156]. In one attempt, Guo et al. examined the utilization of CS-PDA aerogel for Pb (II) adsorption from the wastewater. The q_{max} was reported to be 441.2 mg g^{-1} , and the chemisorption process occurred [157]. Li et al. examined the adsorption of Pb (II) onto yeast biomass modified with ethylenediamine and coated with magnetic-CS micro-particles (EYMCS). The q_{max} was reported to be 134.9 mg g^{-1} at 40°C [158]. Furthermore, Liang et al. experimented with beads that were solid and synthesized MOF and CS via the solvothermal method, and as a cross-linker, sodium tripolyphosphate (Na-TPP) was utilized. The q_{max} of 406.5 mg g^{-1} was found at normal room temperature [159].

CS-based adsorbents have proven to be highly effective in the removal of lead contaminants. This effectiveness can be attributed to the strong interactions that occur between lead ions and the functional groups present on the surfaces of CS. Their compatibility with living organisms and their positive impact on the environment help alleviate health and environmental issues related to lead removal methods. In addition, its versatility allows for easy modifications to improve its ability to absorb lead and selectivity. CS-based adsorbents have been found to show pH-dependent adsorption behavior. Therefore, it is important to carefully control the solution conditions in order to achieve optimal lead removal. The surface area of CS particles is limited, which can limit their adsorption capacity. This means that higher doses of adsorbent may be needed for effective treatment. In addition, the regeneration of CS matrices following lead adsorption presents a potential challenge, as it may affect reusability and lead to higher operational costs.

4. Regeneration of CS-based adsorbents

The regeneration of CS-based adsorbents is an important aspect in assessing their practical feasibility and sustainability for removing heavy metals from wastewater and there are several factors to examine.



Fig. 9. Several sources of Pb contamination.

To begin with, the conversation focuses on the ability to use these adsorbents multiple times and their cost-efficiency, and CS is a cheap source [160]. It underscores their potential for repeated use and the financial considerations of the regeneration process. Additionally, it is important to optimize the circumstances for regeneration, including elements such as the kind and concentration of the regenerating agent, temperature, and contact time [161]. Elution with an eluent is the most used method in the literature to regenerate chitosan-based adsorbents. The proportion used of eluents was in the sequence of salts, alkalis, chelators, and acids. The HCl, EDTA, NaOH, and NaCl solutions are frequently employed to remove substances [162]. This is necessary to develop effective protocols and improve desorption efficiency. Moreover, focus is given to the stability and durability of the adsorbent, examining any changes in structure or alterations in functional groups that may occur over repeated regeneration cycles to appropriately assess long-term performance. Studying how desorption works provides information about how metals and CS interact, which helps improve methods for regeneration. Environmental factors, such as the possible creation of additional pollutants and the impact on the environment

caused by regenerating agents, are important for assessing the overall environmental impact of the adsorption-desorption cycle. Finally, including actual uses, like continuous-flow systems or large-scale water treatment procedures, requires dealing with scaling issues and suggesting methods to match regeneration elements with real-life situations. Fig. 10 shows the regeneration of CS-based adsorbents for the metals.

5. Effect of heavy metals on human health

Heavy metals are available naturally in the environment, and a few are vital for living on Earth, but when they bioaccumulate in the food chain, they become hazardous [163] and seriously harm human health. Arsenic is an extremely toxic metalloid. Long-term exposure to As has been linked to a number of health problems, such as skin lesions, bladder, lung, and skin cancers, as well as cardiovascular disorders [164]. Long-term consumption of water tainted with As has been connected to the emergence of several malignancies, making it a serious public health risk. Furthermore, exposure to arsenic has been linked to

Table 6

Various CS-based adsorbents for the removal of Lead (Pb),.

Adsorbent	Maximum Adsorption Capacity (mg g ⁻¹)	Isotherm model	Kinetics model	Surface area	Contact time	pH	Ref
Alginate/Melamine/Chitosan aerogel	1331.6	Langmuir	2nd Order	-	850	5.5	[78]
Chitosan/PVP/PVA-HNM	87.81	Langmuir	2nd Order	17.16 m ² g ⁻¹	-	-	[99]
Chitosan-pectin beads	266.5	Langmuir	2nd Order	23.66 m ² g ⁻¹	160	1 – 9	[101]
Chitosan/Polyvinyl alcohol	4.02	Langmuir	2nd Order	1.96 m ² g ⁻¹	720	3.64	[151]
Cross-linked carboxylated Chitosan/ carboxylated nano-cellulose hydrogel beads	334.9	Langmuir	2nd Order	-	30	4 – 4.5	[153]
Magnetic-Chitosan-Peracetic acid nano-composite	204.9	Langmuir	2nd Order	-	120	2 – 5	[154]
Chitosan-Polyvinyl alcohol nano-fibers	266.12	Langmuir	2nd Order	-	240	2 – 11	[155]
Magnese oxide/Chitosan nano-particles	126.1	Langmuir	2nd Order	15.75 m ² g ⁻¹	240	2 – 15	[156]
Polydopamine-modified Chitosan aerogels	441.2	Langmuir	2nd Order	77.3 m ² g ⁻¹	900	2 – 8	[157]
Hydroxyapatite/Chitosan composite	132.1	Langmuir	2nd Order	-	240	6	[107]




Fig. 10. Regeneration of CS-based adsorbents for metals.




Fig. 11. Adverse effects on human health by toxic heavy metals.

neurological diseases and other effects on the nervous system, including the ability to reproduce. To lessen these harmful effects on health, the World Health Organization (WHO) and other regulatory agencies have set strict limits for arsenic in drinking water.

Cadmium is naturally present and released into the atmosphere by manmade activities (mainly released into the air via tainted food, drink, and tobacco smoke), and it has different effects on humans and animals. Chronic exposure to cadmium has been linked to kidney damage, which can result in painful and incapacitating illnesses like Itai-Itai disease, a form of osteomalacia. In addition, cadmium has been linked to cardiovascular problems, pulmonary problems, and a higher risk of some cancers, especially prostate and lung cancer. Cadmium can also have a detrimental effect on bone health, increasing the incidence of fractures and reducing bone density. Also, a study reported that cadmium hinders in plant metabolic processes and growth [165].

The metal chromium can be found in a number of oxidation states, the most dangerous of which is hexavalent chromium [Cr(VI)]. Long-

term exposure to high concentrations of hexavalent chromium, which are frequently present in industrial effluent, has been connected to lung cancer and other respiratory problems. Skin disorders, renal damage, and irritation of the nose and gastrointestinal tract can also be brought on by hexavalent chromium ingestion or inhalation [166]. Because of its link to lung cancer, hexavalent chromium has been categorized as a Group 1 human carcinogen by the International Agency for Research on Cancer (IARC). Even though copper is a trace element vital to human health, too much of it can have negative effects. Severe copper poisoning in drinking water can lead to nausea and vomiting as well as other gastrointestinal problems. Copper poisoning is especially dangerous for those with Wilson's disease, a hereditary illness that affects copper metabolism. Chronic exposure to high copper concentrations may also aggravate the kidneys and liver. Copper is routinely monitored in drinking water to ensure that levels stay within acceptable limits for human consumption, despite any potential health hazards. Fig. 11 shows the human health effects of contaminated water with toxic heavy metals.

Table 7
Different toxic heavy metals and their human health impacts.

Heavy Metal	Diseases	Research Published
Arsenic	Skin lesion lung cancer diabetes skin cancer Cardiovascular dysfunction Liver damage Changes in hair	[174–176]
Lead	CNS injury GI colic Liver damage Lungs dysfunction Reduced pulmonary function Hematological changes (Anemia)	[177–180]
Mercury	CNS injuries Renal dysfunction GL ulceration Hepatotoxicity Minamata disease	[181–184]
Cadmium	Kidney dysfunction GI disorders Cancer Lungs injuries Degenerative bone disease Itai-itai disease	[185–188]
Chromium	Kidney dysfunction Dermal diseases GI disorders Cancers (lung, bone, thyroid, kidneys, testicular, bladder, and larynx)	[189,190]

Mercury is present in the biosphere and is a highly hazardous heavy metal. It converts to methyl-mercury when it comes in contact with aquatic sediments, which is highly toxic [167]. Manganese is the most abundant toxic heavy metal found naturally in several oxidation states. It is required in many physiological activities, and its excessive consumption results in high levels of toxicity [168,169]. It has adverse human health effects and causes lung and nasal cancer, kidney disorders, cardiovascular diseases, and allergies via inhalation of nickel in the air [170–172], whereas cobalt usually has no negative impacts on human life but may cause death when massive discharges into the environment [173]. It is a very poisonous heavy metal and may possess negative effects on the body's organs. Exposure to lead throughout childhood has the greatest health hazards as it can disrupt cognitive development and result in behavioral issues. Adults who are exposed to Pb have a higher chance of developing hypertension, cardiovascular illnesses, and decreased renal function. It can also build up in bones, which presents long-term health hazards. Strict laws limiting lead exposure have been implemented due to the negative consequences of lead, especially in paint, drinking water, and other consumer goods.

Moreover, copper and zinc are considered vital nutrients for human life and plants, and their toxicity makes them lethal. The deficiency of copper alters vital metabolic processes [191]. Zinc affects ecosystems when emitted into the environment [192].

6. Conclusion and recommendations

Adsorbents based on CS demonstrate remarkable characteristics in the removal of environmental pollutants, demonstrating significant adsorption capacities and efficiencies against a variety of pollutants. This review focuses on the incorporation of different materials with CS, including forms like beads, hydrogels, membranes, etc., that greatly reduce the separation difficulties that come with CS. According to analysis, CS can be modified with promising materials to increase its adsorption capacity. These materials include clays, carbon materials,

metal-organic frameworks, layered double hydroxides, etc., which help to overcome the low adsorption complexity that CS naturally possesses. Moreover, adding the right functional groups to CS improves its electrostatic interaction with contaminants, making it a very powerful method for increasing CS selectivity.

This thorough analysis investigates the adsorption phenomena of CS toward extremely harmful heavy metals, such as As(III) & (V), Cd(II), Cu(II), Cr(VI), and Pb(II), and clarifies the implications for human health. Notwithstanding these positive qualities, disadvantages of CS-based adsorbents are noted; they include problems with reusability, pH dependence, restricted surface area, cost and scalability, and low adsorption capacity. The authors acknowledge that pollutant selectivity is a crucial component in the assessment of CS-based adsorbents and stress its vital importance in the investigation of actual wastewater.

However, this review includes future recommendations to address the drawbacks:

- Enhanced Adsorption Capacity:** Researchers can investigate CS-based adsorbents with various modifications to improve their adsorption capacity. This may incorporate functional groups, nanoparticles, or materials to increase efficiency.
- pH Tolerant Adsorbents:** Synthesis of adsorbents that can efficiently perform over a diverse pH range would improve their practical applicability.
- Selectivity:** Synthesis of CS-based adsorbent with surface modification or specific functional group could help improve selectivity for targeted metal contaminants.
- Thermodynamic Constraints:** The thermodynamic capability of heavy metal adsorption onto CS is governed by parameters such as temperature and pressure. It is essential to comprehend the thermodynamic parameters, such as enthalpy, entropy, and Gibbs free energy changes, in order to forecast the feasibility and spontaneity of the adsorption process under various circumstances.
- Influence of Ionic Strength:** Its adsorption capacity for metals is sensitive to differences in ionic strength. Concentrated solutions can reduce the electrostatic attraction resulting in the overall lower adsorption.
- Diffusion Limitations:** When heavy metal ions diffuse slowly into CS matrices, equilibrium may not be reached in a reasonable amount of time. This constraint is linked to the necessity for mass transfer across the aqueous outer layer and the internal pores of the adsorbent, demanding longer contact durations.

By addressing these challenges and implementing recommendations, CS-based adsorbents can potentially improve in terms of selectivity, cost-effectiveness, and environmentally friendly metal removal solutions.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgments

The authors are grateful for the financial support provided by the Gdansk University of Technology, SB 036277.

References

- Syeda SEZ, Nowacka D, Khan MS, Skwierawska AM. Recent advancements in cyclodextrin-based adsorbents for the removal of hazardous pollutants from waters. *MDPI*, Jun. 01 *Polymers* 2022;vol. 14(12). <https://doi.org/10.3390/polym14122341>.
- "Deaths from Dirty Water."
- Suba V, Rathika G. Novel adsorbents for the removal of dyes and metals from aqueous solution—a review. *J Adv Phys* 2016;vol. 5(4):277–94. <https://doi.org/10.1166/JAP.2016.1269>.

- [4] Fallahzadeh RA, Ghaneian MT, Miri M, Dashti MM. Spatial analysis and health risk assessment of heavy metals concentration in drinking water resources. *Environ Sci Pollut Res* 2017;vol. 24(32):24790–802. <https://doi.org/10.1007/s11356-017-0102-3>.
- [5] Khan Muhammad Shahzaband Syeda SEZSAM. Recent advancements in molecularly imprinted polymers for the removal of heavy metal ions and dyes. 2023;vol. 289:123–44. <https://doi.org/10.5004/dwt.2023.29458>.
- [6] Li S, Zhang Q. Spatial characterization of dissolved trace elements and heavy metals in the upper Han River (China) using multivariate statistical techniques. *J Hazard Mater* 2010;vol. 176(1–3):579–88. <https://doi.org/10.1016/j.jhazmat.2009.11.069>.
- [7] Lu SY, Zhang HM, Sojinu SO, Liu GH, Zhang JQ, Ni HG. Trace elements contamination and human health risk assessment in drinking water from Shenzhen, China. *Environ Monit Assess* 2015;vol. 187(1). <https://doi.org/10.1007/s10661-014-4220-9>.
- [8] Hu B, Jia X, Hu J, Xu D, Xia F, Li Y. Assessment of heavy metal pollution and health risks in the soil-plant-human system in the Yangtze river delta, China. *Int J Environ Res Public Health* 2017;vol. 14(9). <https://doi.org/10.3390/ijerph14091042>.
- [9] Ma R, Zhou X, Shi J. Heavy metal contamination and health risk assessment in critical zone of luan river catchment in the North China Plain. *Geochem: Explor, Environ, Anal* 2018;vol. 18(1):47–57. <https://doi.org/10.1144/geochem2017-010>.
- [10] Li S, Zhang Q. Risk assessment and seasonal variations of dissolved trace elements and heavy metals in the Upper Han River, China. *J Hazard Mater* 2010;vol. 181(3):1051–8. <https://doi.org/10.1016/j.jhazmat.2010.05.120>.
- [11] Sekhar C, Chary NS, Kamala CT, Shanker, Frank H. Environmental pathway and risk assessment studies of the Musi River's heavy metal contamination - A case study. *Hum Ecol Risk Assess* 2005;vol. 11(6):1217–35. <https://doi.org/10.1080/10807030500278594>.
- [12] Pertsemli E, Voutsas D. Distribution of heavy metals in Lakes Doirani and Kerkini, Northern Greece. *J Hazard Mater* 2007;vol. 148(3):529–37. <https://doi.org/10.1016/j.jhazmat.2007.03.019>.
- [13] He L, et al. Health risk assessment of heavy metals in surface water near a uranium tailing pond in Jiangxi Province, South China. *Sustain (Switz)* 2018;vol. 10(4). <https://doi.org/10.3390/su10041113>.
- [14] Poshina DN, Raik SV, Poshin AN, Skorik YA. Accessibility of chitin and chitosan in enzymatic hydrolysis: a review. *Polym Degrad Stab* 2018;vol. 156:269–78. <https://doi.org/10.1016/j.polyimdegradstab.2018.09.005>.
- [15] Guimarães Ruesmão KA, Alves Gurgel LV, Sacramento Melo TM, Gil LF. Application of succinylated sugarcane bagasse as adsorbent to remove methylene blue and gentian violet from aqueous solutions - Kinetic and equilibrium studies. *Dyes Pigments* 2012;vol. 92(3):967–74. <https://doi.org/10.1016/j.dyepig.2011.09.005>.
- [16] Zhang Y, et al. Research progress of adsorption and removal of heavy metals by chitosan and its derivatives: a review. *Chemosphere* 2021;vol. 279(March):130927. <https://doi.org/10.1016/j.chemosphere.2021.130927>.
- [17] Bilal M, Iqbal HMN, Hu H, Wang W, Zhang X. Enhanced bio-catalytic performance and dye degradation potential of chitosan-encapsulated horseradish peroxidase in a packed bed reactor system. *Sci Total Environ* 2017;vol. 575:1352–60. <https://doi.org/10.1016/j.scitotenv.2016.09.215>.
- [18] Bilal M, Jing Z, Zhao Y, Iqbal HMN. Immobilization of fungal laccase on glutaraldehyde cross-linked chitosan beads and its bio-catalytic potential to degrade bisphenol A. *Biocatal Agric Biotechnol* 2019;vol. 19:101174. <https://doi.org/10.1016/j.cbab.2019.101174>.
- [19] Bilal M, Rasheed T, Zhao Y, Iqbal HMN. Agarose-chitosan hydrogel-immobilized horseradish peroxidase with sustainable bio-catalytic and dye degradation properties. *Int J Biol Macromol* 2019;vol. 124:742–9. <https://doi.org/10.1016/j.ijbiomac.2018.11.220>.
- [20] Ali N, Khan A, Malik S, Badshah S, Bilal M, Iqbal HMN. Chitosan-based green sorbent material for cations removal from an aqueous environment. *J Environ Chem Eng* 2020;vol. 8(5):104064. <https://doi.org/10.1016/j.jece.2020.104064>.
- [21] Ali N, et al. Characterization and deployment of surface-engineered chitosan-triethylenetetramine nanocomposite hybrid nano-adsorbent for divalent cations decontamination. *Int J Biol Macromol* 2020;vol. 152:663–71. <https://doi.org/10.1016/j.ijbiomac.2020.02.218>.
- [22] Ali N, Khan A, Bilal M, Malik S, Badshah S, Iqbal HMN. Chitosan-based bio-composite modified with thiocarbamate moiety for decontamination of cations from the aqueous media. *Molecules* Jan. 2020;vol. 25(1). <https://doi.org/10.3390/molecules25010226>.
- [23] Khan A, Ali N, Bilal M, Malik S, Badshah S, Iqbal HMN. Engineering functionalized chitosan-based sorbent material: Characterization and sorption of toxic elements. *Appl Sci (Switz)* Dec. 2019;vol. 9(23). <https://doi.org/10.3390/app9235138>.
- [24] Bailey SE, Olin TJ, Bricka RM, Adrian DD. A review of potentially low-cost sorbents for heavy metals. *Water Res* 1999;vol. 33(11):2469–79. [https://doi.org/10.1016/S0043-1354\(98\)00475-8](https://doi.org/10.1016/S0043-1354(98)00475-8).
- [25] Owlad M, Aroua MK, Daud WAW, Baroutian S. Removal of hexavalent chromium-contaminated water and wastewater: a review. *Water Air Soil Pollut* 2009;vol. 200(1–4):59–77. <https://doi.org/10.1007/s11270-008-9893-7>.
- [26] Bhatnagar A, Sillanpää M. Applications of chitin- and chitosan-derivatives for the detoxification of water and wastewater - a short review. *Adv Colloid Interface Sci* 2009;vol. 152(1–2):26–38. <https://doi.org/10.1016/j.cis.2009.09.003>.
- [27] Dragan ES. Design and applications of interpenetrating polymer network hydrogels. a review. *Chem Eng J* 2014;vol. 243(May 2014):572–90. <https://doi.org/10.1016/j.cej.2014.01.065>.
- [28] Miretzky P, Cirelli AF. "Hg(II) removal from water by chitosan and chitosan derivatives: a review,". *J Hazard Mater* 2009;vol. 167(1–3):10–23. <https://doi.org/10.1016/J.JHAZMAT.2009.01.060>.
- [29] Pontoni L, Fabbriano M. Use of chitosan and chitosan-derivatives to remove arsenic from aqueous solutions - a mini review. *Carbohydr Res* 2012;vol. 356:86–92. <https://doi.org/10.1016/j.carres.2012.03.042>.
- [30] Wan Ngah WS, Teong LC, Hanafiah MAKM. Adsorption of dyes and heavy metal ions by chitosan composites: a review. *Carbohydr Polym* 2011;vol. 83(4):1446–56. <https://doi.org/10.1016/j.carbpol.2010.11.004>.
- [31] Wu FC, Tseng RL, Juang RS. A review and experimental verification of using chitosan and its derivatives as adsorbents for selected heavy metals. *J Environ Manag* 2010;vol. 91(4):798–806. <https://doi.org/10.1016/j.jenvman.2009.10.018>.
- [32] Lee MY, Hong KJ, Kajiuchi T, Yang JW. Synthesis of chitosan-based polymeric surfactants and their adsorption properties for heavy metals and fatty acids. *Int J Biol Macromol* 2005;vol. 36(3):152–8. <https://doi.org/10.1016/j.ijbiomac.2005.05.004>.
- [33] Ibrahim M, Osman O, Mahmoud AA. Spectroscopic analyses of cellulose and chitosan: FTIR and modeling approach. *J Comput Theor Nanosci* 2011;vol. 8(1):117–23. <https://doi.org/10.1166/JCTN.2011.1668>.
- [34] Singla AK, Chawla M. Chitosan: some pharmaceutical and biological aspects? an update. *J Pharm Pharmacol JPP* 2001;vol. 53:1047–67. <https://doi.org/10.1211/0022357011776441>.
- [35] Dutta PK. Chitin and Chitosan for Regenerative Medicine. *Chitin Chitosan Regen Med* 2015:1–389. <https://doi.org/10.1007/978-81-322-2511-9>.
- [36] Rubentheren V, Ward TA, Chee CY, Nair P. Physical and chemical reinforcement of chitosan film using nanocrystalline cellulose and tannic acid. *Cellulose* 2015;vol. 22(4):2529–41. <https://doi.org/10.1007/s10570-015-0650-y>.
- [37] Xiao G, Su H, Tan T. Synthesis of core-shell bioaffinity chitosan-TiO₂ composite and its environmental applications. *J Hazard Mater* 2015;vol. 283:888–96. <https://doi.org/10.1016/j.jhazmat.2014.10.047>.
- [38] Gao R, et al. Removal of off-flavours from radish (*Raphanus sativus* L.) anthocyanin-rich pigments using chitosan and its mechanism(s). *Food Chem Mar*. 2014;vol. 146:423–8. <https://doi.org/10.1016/j.foodchem.2013.09.107>.
- [39] Annour S, Moufti A, Mountadar S, Mountadar M, Soufiane A. The influences of the presence of ions counter on the removal capacity fluorides ions by chitosane. *Orient J Chem* 2016;vol. 32(1):399–406. <https://doi.org/10.13005/ojc/320145>.
- [40] Nthunya LN, Masheane ML, Malinga SP, Nxumalo EN, Mhlanga SD. Electrospun chitosan-based nanofibres for removal of phenols from drinking water. *Water SA* 2018;vol. 44(3):377–86. <https://doi.org/10.4314/wsa.v44i3.05>.
- [41] Mohanasrinivasan V, et al. Studies on heavy metal removal efficiency and anti-bacterial activity of chitosan prepared from shrimp shell waste. *3 Biotech* 2014;vol. 4(2):167–75. <https://doi.org/10.1007/s13205-013-0140-6>.
- [42] Omer AM, et al. Fabrication of a novel low-cost superoleophilic nonanil chitosan-poly (butyl acrylate) grafted copolymer for the adsorptive removal of crude oil spills. *Int J Biol Macromol* 2019;vol. 140:588–99. <https://doi.org/10.1016/J.IJBIOMAC.2019.08.169>.
- [43] Muzzarelli RAA, Tanfani F. The N-permethylation of chitosan and the preparation of N-trimethyl chitosan iodide. *Carbohydr Polym* 1985;vol. 5(4):297–307. [https://doi.org/10.1016/0144-8617\(85\)90037-2](https://doi.org/10.1016/0144-8617(85)90037-2).
- [44] Solano RA, De León LD, De Ávila G, Herrera AP. Polycyclic aromatic hydrocarbons (PAHs) adsorption from aqueous solution using chitosan beads modified with thiourea, TiO₂ and Fe₃O₄ nanoparticles. *Environ Technol Innov* 2021;vol. 21:101378. <https://doi.org/10.1016/J.ETI.2021.101378>.
- [45] Liakos EV, et al. Chitosan adsorbent derivatives for pharmaceuticals removal from effluents: a review. *Macromol* 2021, Vol 1, Pages 130-154 2021;vol. 1(2):130–54. <https://doi.org/10.3390/MACROMOL1020011>.
- [46] Asgari E, Sheikhmohammadi A, Yeganeh J. Application of the Fe₃O₄-chitosan nano-adsorbent for the adsorption of metronidazole from wastewater: Optimization, kinetic, thermodynamic and equilibrium studies. *Int J Biol Macromol* 2020;vol. 164:694–706. <https://doi.org/10.1016/J.IJBIOMAC.2020.07.188>.
- [47] Mu R, Liu B, Chen X, Wang N, Yang J. Adsorption of Cu (II) and Co (II) from aqueous solution using lignosulfonate/chitosan adsorbent. *Int J Biol Macromol* 2020;vol. 163:120–7. <https://doi.org/10.1016/J.IJBIOMAC.2020.06.260>.
- [48] Tanhaei B, Ayati A, Iakovleva E, Sillanpää M. Efficient carbon interlayered magnetic chitosan adsorbent for anionic dye removal: Synthesis, characterization and adsorption study. *Int J Biol Macromol* 2020;vol. 164:3621–31. <https://doi.org/10.1016/J.IJBIOMAC.2020.08.207>.
- [49] Omer AM, Elgarhy GS, El-Subriti GM, Khalifa RE, Eltaweil AS. Fabrication of novel iminodiacetic acid-functionalized carboxymethyl cellulose microbeads for efficient removal of cationic crystal violet dye from aqueous solutions. *Int J Biol Macromol* 2020;vol. 148:1072–83. <https://doi.org/10.1016/J.IJBIOMAC.2020.01.182>.
- [50] E. M.M, O. A, W. M, T. T, A.-E. M, and I. S, "Novel smart pH sensitive chitosan grafted alginate hydrogel microcapsules for oral protein delivery: II. evaluation of the swelling behavior | Request PDF." 2015.
- [51] Kyzas GZ, Bikiaris DN. Recent modifications of chitosan for adsorption applications: a critical and systematic review. *Mar Drugs* 2015;vol. 13(1):312–37. <https://doi.org/10.3390/MD13010312>.
- [52] Eltaweil AS, et al. Chitosan based adsorbents for the removal of phosphate and nitrate: a critical review. *Carbohydr Polym* 2021;vol. 274:118671. <https://doi.org/10.1016/J.CARBPOL.2021.118671>.
- [53] Shankar P, Gomathi T, Vijayalakshmi K, Sudha PN. Comparative studies on the removal of heavy metals ions onto cross linked chitosan-g-acrylonitrile copolymer. *Int J Biol Macromol* 2014;vol. 67:180–8. <https://doi.org/10.1016/J.IJBIOMAC.2014.03.010>.
- [54] Shebl A, Omer AM, Tamer TM. Adsorption of cationic dye using novel O-amine functionalized chitosan schiff base derivatives: Isotherm and kinetic studies. "

- Desalin Water Treat* 2018;vol. 130:132–41. <https://doi.org/10.5004/DWT.2018.22986>.
- [55] Yuvaraja G, et al. Preparation of novel aminated chitosan schiff's base derivative for the removal of methyl orange dye from aqueous environment and its biological applications. *Int J Biol Macromol* 2020;vol. 146:1100–10. <https://doi.org/10.1016/J.IJBIOMAC.2019.09.236>.
- [56] Kumari U, Siddiqi H, Bal M, Meikap BC. Calcium and zirconium modified acid activated alumina for adsorptive removal of fluoride: Performance evaluation, kinetics, isotherm, characterization and industrial wastewater treatment. *Adv Powder Technol* 2020;vol. 31(5):2045–60. <https://doi.org/10.1016/J.APT.2020.02.035>.
- [57] Dai Y, et al. Utilizations of agricultural waste as adsorbent for the removal of contaminants: a review. *Chemosphere* 2018;vol. 211:235–53. <https://doi.org/10.1016/J.CHEMOSPHERE.2018.06.179>.
- [58] Kalaimurugan D, Durairaj K, Kumar AJ, Senthilkumar P, Venkatesan S. "Novel preparation of fungal conidiophores biomass as adsorbent for removal of phosphorus from aqueous solution." *Environ Sci Pollut Res* 2020;vol. 27(17):20757–69. <https://doi.org/10.1007/S11356-020-08307-0/TABLES/10>.
- [59] Ngah WSW, Teong LC, Hanafiah MAKM. Adsorption of dyes and heavy metal ions by chitosan composites: A review. *Carbohydr Polym* 2011;vol. 83(4):1446–56. <https://doi.org/10.1016/J.CARBPOL.2010.11.004>.
- [60] Rahim ARA, et al. Effective carbonaceous desiccated coconut waste adsorbent for application of heavy metal uptakes by adsorption: equilibrium, kinetic and thermodynamics analysis. *Biomass–Bioenergy* 2020;vol. 142:105805. <https://doi.org/10.1016/J.BIOMBIOE.2020.105805>.
- [61] Hu A, et al. Magnetically hyper-cross-linked polymers with well-developed mesoporous: a broad-spectrum and highly efficient adsorbent for water purification." *J Mater Sci* 2019;vol. 54(3):2712–28. <https://doi.org/10.1007/S10853-018-2967-Z/FIGURES/8>.
- [62] Duman O, Polat TG, Diker CÖ, Tunç S. Agar/κ-carrageenan composite hydrogel adsorbent for the removal of Methylene Blue from water. *Int J Biol Macromol* 2020;vol. 160:823–35. <https://doi.org/10.1016/J.IJBIOMAC.2020.05.191>.
- [63] Qi X, Wei W, Su T, Zhang J, Dong W. Fabrication of a new polysaccharide-based adsorbent for water purification. *Carbohydr Polym* 2018;vol. 195:368–77. <https://doi.org/10.1016/J.CARBPOL.2018.04.112>.
- [64] Nakakubo K, et al. Dithiocarbamate-modified cellulose resins: A novel adsorbent for selective removal of arsenite from aqueous media. *J Hazard Mater* 2019;vol. 380:120816. <https://doi.org/10.1016/J.JHAZMAT.2019.120816>.
- [65] Xu Z, et al. A bifunctional adsorbent of silica gel-immobilized Schiff base derivative for simultaneous and selective adsorption of Cu(II) and SO42–. *Sep Purif Technol* 2018;vol. 191:61–74. <https://doi.org/10.1016/J.JSEPUPUR.2017.09.019>.
- [66] Silva B, et al. Waste-based biosorbents as cost-effective alternatives to commercial adsorbents for the retention of fluoxetine from water. *Sep Purif Technol* 2020;vol. 235:116139. <https://doi.org/10.1016/J.JSEPUPUR.2019.116139>.
- [67] Tan Y, Wang K, Yan Q, Zhang S, Li J, Ji Y. Synthesis of Amino-Functionalized Waste Wood Flour Adsorbent for High-Capacity Pb(II) Adsorption. *ACS Omega* 2019;vol. 4(6):10475–84. https://doi.org/10.1021/ACSOMEGA.9B00920/SUPPL_FILE/AO9B00920_SI_001.PDF.
- [68] Kobayashi Y, Ogata F, Nakamura T, Kawasaki N. Synthesis of novel zeolites produced from fly ash by hydrothermal treatment in alkaline solution and its evaluation as an adsorbent for heavy metal removal. *J Environ Chem Eng* 2020;vol. 8(2):103687. <https://doi.org/10.1016/J.JECE.2020.103687>.
- [69] A. Kaushal and S.K. Singh, "Removal of heavy metals by nanoadsorbents: A review," no. January, 2017.
- [70] Al aidy El-saied H, Motawea EAT. Optimization and adsorption behavior of nanostructured nife2o4/poly amps grafted biopolymer. *J Polym Environ* 2020;vol. 28(9):2335–51. <https://doi.org/10.1007/S10924-020-01774-Z/TABLES/7>.
- [71] Gokila S, Gomathi T, Sudha PN, Anil S. Removal of the heavy metal ion chromium (VI) using Chitosan and Alginate nanocomposites. *Int J Biol Macromol* 2017;vol. 104:1459–68. <https://doi.org/10.1016/J.IJBIOMAC.2017.05.117>.
- [72] Yang D, Li L, Chen B, Shi S, Nie J, Ma G. Functionalized chitosan electrospun nanofiber membranes for heavy-metal removal. *Polym (Guildf)* 2019;vol. 163:74–85. <https://doi.org/10.1016/J.POLYMER.2018.12.046>.
- [73] Upadhyay U, Sreedhar I, Singh SA, Patel CM, Anitha KL. Recent advances in heavy metal removal by chitosan based adsorbents. *Carbohydr Polym* 2021;vol. 251:117000. <https://doi.org/10.1016/J.CARBPOL.2020.117000>.
- [74] Mandal BK, Suzuki KT. Arsenic round the world: a review. *Talanta* 2002;vol. 58(1):201–35. [https://doi.org/10.1016/S0039-9140\(02\)00268-0](https://doi.org/10.1016/S0039-9140(02)00268-0).
- [75] Choong TSY, Chuah TG, Robiah Y, Koay FLG, Azni I. Arsenic toxicity, health hazards and removal techniques from water: an overview. *Desalination* 2007;vol. 217(1–3):139–66. <https://doi.org/10.1016/J.DESAL.2007.01.015>.
- [76] Sodhi KK, Kumar M, Agrawal PK, Singh DK. Perspectives on arsenic toxicity, carcinogenicity and its systemic remediation strategies. *Environ Technol Innov* 2019;vol. 16:100462. <https://doi.org/10.1016/J.ETI.2019.100462>.
- [77] S. Sara Hassan , S. Shane Zehra , Z. Ahmed , M. Younis Younis TALPUR , and S. Panhwar Balochistan , "Removal of arsenic contaminants from water using iron oxide nanoparticles by inductively coupled plasma mass spectrometry," 2022, <doi:10.21203/rs.3.rs-1469404/v1>.
- [78] Gao C, Wang XL, An QDa, Xiao ZY, Zhai SR. Synergistic preparation of modified alginate aerogel with melamine/chitosan for efficiently selective adsorption of lead ions. *Carbohydr Polym* 2021;vol. 256. <https://doi.org/10.1016/J.CARBPOL.2020.117564>.
- [79] Gupta A, Yunus M, Sankaramakrishnan N. Zerovalent iron encapsulated chitosan nanospheres – A novel adsorbent for the removal of total inorganic Arsenic from aqueous systems. *Chemosphere* 2012;vol. 86(2):150–5. <https://doi.org/10.1016/J.CHEMOSPHERE.2011.10.003>.
- [80] Pontoni L, Fabbicino M. Use of chitosan and chitosan-derivatives to remove arsenic from aqueous solutions—a mini review. *Carbohydr Res* 2012;vol. 356:86–92. <https://doi.org/10.1016/J.CARRES.2012.03.042>.
- [81] Boddur VM, Abburi K, Talbott JL, Smith ED, Haasch R. Removal of arsenic (III) and arsenic (V) from aqueous medium using chitosan-coated biosorbent. *Water Res* 2008;vol. 42(3):633–42. <https://doi.org/10.1016/J.WATRES.2007.08.014>.
- [82] Ayub A, Raza ZA, Majeed MI, Tariq MR, Irfan A. Development of sustainable magnetic chitosan biosorbent beads for kinetic remediation of arsenic contaminated water. *Int J Biol Macromol* 2020;vol. 163:603–17. <https://doi.org/10.1016/J.IJBIOMAC.2020.06.287>.
- [83] Gupta A, Chauhan VS, Sankaramakrishnan N. Preparation and evaluation of iron–chitosan composites for removal of As(III) and As(V) from arsenic contaminated real life groundwater. *Water Res* 2009;vol. 43(15):3862–70. <https://doi.org/10.1016/J.WATRES.2009.05.040>.
- [84] Sherlala AlA, Raman AAA, Bello MM, Buthiyappan A. Adsorption of arsenic using chitosan magnetic graphene oxide nanocomposite. *J Environ Manag* 2019;vol. 246:547–56. <https://doi.org/10.1016/J.JENVMAN.2019.05.117>.
- [85] Shan H, Peng S, Zhao C, Zhan H, Zeng C. Highly efficient removal of As(III) from aqueous solutions using goethite/graphene oxide/chitosan nanocomposite. *Int J Biol Macromol* 2020;vol. 164:13–26. <https://doi.org/10.1016/J.IJBIOMAC.2020.07.108>.
- [86] Kumar ASK, Jiang SJ. Chitosan-functionalized graphene oxide: A novel adsorbent an efficient adsorption of arsenic from aqueous solution. *J Environ Chem Eng* 2016;vol. 4(2):1698–713. <https://doi.org/10.1016/J.JECE.2016.02.035>.
- [87] Wang B, et al. Selective heavy metal removal and water purification by microfluidically-generated chitosan microspheres: Characteristics, modeling and application. *J Hazard Mater* 2019;vol. 364:192–205. <https://doi.org/10.1016/J.JHAZMAT.2018.10.024>.
- [88] Pincus LN, et al. Selective adsorption of arsenic over phosphate by transition metal cross-linked chitosan. *Chem Eng J* 2021;vol. 412:128582. <https://doi.org/10.1016/J.CEJ.2021.128582>.
- [89] Lobo C, Castellari J, Lerner JC, Bertola N, Zaritzky N. Functional iron chitosan microspheres synthesized by ionotropic gelation for the removal of arsenic (V) from water. *Int J Biol Macromol* 2020;vol. 164:1575–83. <https://doi.org/10.1016/J.IJBIOMAC.2020.07.253>.
- [90] Gogoi P, Thakur AJ, Devi RR, Das B, Maji TK. Adsorption of As(V) from contaminated water over chitosan coated magnetite nanoparticle: Equilibrium and kinetics study. *Environ Nanotechnol Monit Manag* 2017;vol. 8:297–305. <https://doi.org/10.1016/J.ENMM.2017.09.002>.
- [91] Shahzad A, et al. Heavy metals removal by EDTA-functionalized chitosan graphene oxide nanocomposites. *RSC Adv* 2017;vol. 7(16):9764–71. <https://doi.org/10.1039/C6RA28406J>.
- [92] Abdollahi M, Zeinali S, Nasirimoghaddam S, Sabbaghi S. Effective removal of As (III) from drinking water samples by chitosan-coated magnetic nanoparticles. *N pub: Balaban* 2014;vol. 56(8):2092–104. <https://doi.org/10.1080/19443994.2014.958538>.
- [93] Wang J, Xu W, Chen L, Huang X, Liu J. Preparation and evaluation of magnetic nanoparticles impregnated chitosan beads for arsenic removal from water. *Chem Eng J* 2014;vol. 251:25–34. <https://doi.org/10.1016/J.CEJ.2014.04.061>.
- [94] Cho DW, et al. A novel chitosan/clay/magnetite composite for adsorption of Cu(II) and As(V). *Chem Eng J* 2012;vol. 200–202:654–62. <https://doi.org/10.1016/J.CEJ.2012.06.126>.
- [95] Pyrzynska K. Removal of cadmium from wastewaters with low-cost adsorbents. *J Environ Chem Eng* 2019;vol. 7(1):102795. <https://doi.org/10.1016/J.JECE.2018.11.040>.
- [96] Godt J, et al. The toxicity of cadmium and resulting hazards for human health. *J Occup Med Toxicol* 2006;vol. 1(1):1–6. <https://doi.org/10.1186/1745-6673-1-22/TABLES/1>.
- [97] Huang Y-Y, et al. Toxicity of cadmium and its health risks from leafy vegetable consumption. 2017;vol. 8:1373. <https://doi.org/10.1039/C6FO01580H>.
- [98] Babakhani A, Sartaj M. Removal of Cadmium (II) from aqueous solution using tripolyphosphate cross-linked chitosan. *J Environ Chem Eng* 2020;vol. 8(4):103842. <https://doi.org/10.1016/J.JECE.2020.103842>.
- [99] Wu S, et al. Chitosan-based hollow nanofiber membranes with polyvinylpyrrolidone and polyvinyl alcohol for efficient removal and filtration of organic dyes and heavy metals. *Int J Biol Macromol* 2023;vol. 239:124264. <https://doi.org/10.1016/J.IJBIOMAC.2023.124264>.
- [100] Vilela PB, Dalalibera A, Duminielli EC, Becegato VA, Paulino AT. "Adsorption and removal of chromium (VI) contained in aqueous solutions using a chitosan-based hydrogel." *Environ Sci Pollut Res* 2019;vol. 26(28):28481–9. <https://doi.org/10.1007/S11356-018-3208-3/TABLES/4>.
- [101] Shao Z, et al. Novel green chitosan-pectin gel beads for the removal of Cu(II), Cd (II), Hg(II) and Pb(II) from aqueous solution. *Int J Biol Macromol* 2021;vol. 176:217–25. <https://doi.org/10.1016/J.IJBIOMAC.2021.02.037>.
- [102] Wang Y, et al. Novel environmental-friendly nano-composite magnetic attapulgitic functionalized by chitosan and EDTA for cadmium (II) removal. *J Alloy Compd* 2020;vol. 817:153286. <https://doi.org/10.1016/J.JALLCOM.2019.153286>.
- [103] Sahebamee N, Soltanieh M, Mousavi SM, Heydarinasab A. Removal of Cu2+, Cd2+ and Ni2+ ions from aqueous solution using a novel chitosan/polyvinyl alcohol adsorptive membrane. *Carbohydr Polym* 2019;vol. 210:264–73. <https://doi.org/10.1016/J.CARBPOL.2019.01.074>.
- [104] Chen L, et al. Preparation and characterization of the eco-friendly chitosan/vermiculite biocomposite with excellent removal capacity for cadmium and lead. *Appl Clay Sci* 2018;vol. 159:74–82. <https://doi.org/10.1016/J.CLAY.2017.12.050>.

- [105] Ahmadi M, et al. Synthesis of chitosan zero-valent iron nanoparticles-supported for cadmium removal: characterization, optimization and modeling approach. *J Water Supply: Res Technol-Aqua* 2017;vol. 66(2):116–30. <https://doi.org/10.2166/AQUA.2017.07>.
- [106] Prakash N, Soundarrajan M, Arungalai Vendan S, Sudha PN, Renganathan NG. Contemplating the feasibility of vermiculite blended chitosan for heavy metal removal from simulated industrial wastewater. *Appl Water Sci* 2015 7:8 2015;vol. 7(8):4207–18. <https://doi.org/10.1007/S13201-015-0366-Z>.
- [107] Park S, Gomez-Flores A, Chung YS, Kim H. Removal of cadmium and lead from aqueous solution by hydroxyapatite/chitosan hybrid fibrous sorbent: Kinetics and equilibrium studies. *J Chem*, Vol 2015;2015. <https://doi.org/10.1155/2015/396290>.
- [108] Chen A, et al. Novel thiourea-modified magnetic ion-imprinted chitosan/TiO₂ composite for simultaneous removal of cadmium and 2,4-dichlorophenol. *Chem Eng J* 2012;vol. 191:85–94. <https://doi.org/10.1016/J.CEJ.2012.02.071>.
- [109] Wei J, et al. Carbon-coated montmorillonite nanocomposite for the removal of chromium(VI) from aqueous solutions. *J Hazard Mater* 2019;vol. 368:541–9. <https://doi.org/10.1016/J.JHAZMAT.2019.01.080>.
- [110] Cao J, et al. Hydroxypropyl chitosan-based dual self-healing hydrogel for adsorption of chromium ions. *Int J Biol Macromol* 2021;vol. 174:89–100. <https://doi.org/10.1016/J.IJBIOMAC.2021.01.089>.
- [111] Dehghani MH, Sanaei D, Ali I, Bhatnagar A. Removal of chromium(VI) from aqueous solution using treated waste newspaper as a low-cost adsorbent: Kinetic modeling and isotherm studies. *J Mol Liq* 2016;vol. 215:671–9. <https://doi.org/10.1016/J.MOLLIQ.2015.12.057>.
- [112] Cai W, et al. Preparation of thiourea-modified magnetic chitosan composite with efficient removal efficiency for Cr(VI). *Chem Eng Res Des* 2019;vol. 144:150–8. <https://doi.org/10.1016/J.CHERD.2019.01.031>.
- [113] Zeng X, Zhang G, Wen J, Li X, Zhu J, Wu Z. Simultaneous removal of aqueous same ionic type heavy metals and dyes by a magnetic chitosan/polyethyleneimine embedded hydrophobic sodium alginate composite: Performance, interaction and mechanism. *Chemosphere* 2023;vol. 318:137869. <https://doi.org/10.1016/J.CHEMOSPHERE.2023.137869>.
- [114] Vilela PB, Dalalibera A, Duminelli EC, Beccegato VA, Paulino AT. “Adsorption and removal of chromium (VI) contained in aqueous solutions using a chitosan-based hydrogel.”. *Environ Sci Pollut Res* 2019;vol. 26(28):28481–9. <https://doi.org/10.1007/S11356-018-3208-3/TABLES/4>.
- [115] Li QH, et al. Enhancement of Cr(VI) removal efficiency via adsorption/photocatalysis synergy using electrospon chitosan/g-C₃N₄/TiO₂ nanofibers. *Carbohydr Polym* 2021;vol. 253:117200. <https://doi.org/10.1016/J.CARBPOL.2020.117200>.
- [116] Niu C, Zhang N, Hu C, Zhang C, Zhang H, Xing Y. Preparation of a novel citric acid-crosslinked Zn-MOF/chitosan composite and application in adsorption of chromium(VI) and methyl orange from aqueous solution. *Carbohydr Polym* 2021;vol. 258:117644. <https://doi.org/10.1016/J.CARBPOL.2021.117644>.
- [117] Omer AM, El-Monaem EMA, El-Latif MMA, El-Subruiti GM, Eltaweil AS. Facile fabrication of novel magnetic ZIF-67 MOF/aminated chitosan composite beads for the adsorptive removal of Cr(VI) from aqueous solutions. *Carbohydr Polym* 2021;vol. 265:118084. <https://doi.org/10.1016/J.CARBPOL.2021.118084>.
- [118] Dinh VP, et al. Chitosan-MnO₂ nanocomposite for effective removal of Cr (VI) from aqueous solution. *Chemosphere* 2020;vol. 257:127147. <https://doi.org/10.1016/J.CHEMOSPHERE.2020.127147>.
- [119] Shahnaz T, Sharma V, Subbiah S, Narayanasamy S. Multivariate optimisation of Cr (VI), Co (III) and Cu (II) adsorption onto nanobentonite incorporated nanocellulose/chitosan aerogel using response surface methodology. *J Water Process Eng* 2020;vol. 36:101283. <https://doi.org/10.1016/J.JWPE.2020.101283>.
- [120] Wang X, et al. Triethylenetetramine-modified hollow Fe₃O₄/SiO₂/chitosan magnetic nanocomposites for removal of Cr(VI) ions with high adsorption capacity and rapid rate. *Microporous Mesoporous Mater* 2020;vol. 297:110041. <https://doi.org/10.1016/J.MICROMESO.2020.110041>.
- [121] Ma L, Shi X, Zhang X, Dong S, Li L. Electrospon Cellulose Acetate-Polycaprolactone/Chitosan Core-Shell Nanofibers for the Removal of Cr (VI). *Phys Status Solidi (a)* 2019;vol. 216(22):1900379. <https://doi.org/10.1002/PSSA.201900379>.
- [122] Jiang Y, Gu RC, Zhang Y, Wang JT. Heterogeneous structure controlled by shear bands in partially recrystallized nano-laminated copper. *Mater Sci Eng: A* 2018;vol. 721:226–33. <https://doi.org/10.1016/J.MSEA.2018.02.098>.
- [123] Samuel MS, Shah SS, Subramanian V, Qureshi T, Bhattacharya J, Singh NDP. Preparation of graphene oxide/chitosan/ferrite nanocomposite for Chromium(VI) removal from aqueous solution. *Int J Biol Macromol* 2018;vol. 119:540–7. <https://doi.org/10.1016/J.IJBIOMAC.2018.07.052>.
- [124] Chen D, Li W, Wu Y, Zhu Q, Lu Z, Du G. Preparation and characterization of chitosan/montmorillonite magnetic microspheres and its application for the removal of Cr (VI). *Chem Eng J* 2013;vol. 221:8–15. <https://doi.org/10.1016/J.CEJ.2013.01.089>.
- [125] Shen C, et al. Highly efficient detoxification of Cr(VI) by chitosan-Fe(III) complex: Process and mechanism studies. *J Hazard Mater* 2013;vol. 244–245:689–97. <https://doi.org/10.1016/J.JHAZMAT.2012.10.061>.
- [126] Sun X, et al. Synthesis of polythymine-functionalized poly(glycidyl methacrylate) magnetic microspheres and their excellent Cr(VI) ion removal properties. *Chem Eng J* 2013;vol. 234:338–45. <https://doi.org/10.1016/J.CEJ.2013.08.082>.
- [127] Eltaweil AS, El-Monaem EMA, Mohy-Eldin MS, Omer AM. Fabrication of attapulgite/magnetic aminated chitosan composite as efficient and reusable adsorbent for Cr (VI) ions. *Sci Rep* 2021 11:1 2021;vol. 11(1):1–15. <https://doi.org/10.1038/s41598-021-96145-6>.
- [128] Zhu C, et al. Nitrogen-doped chitosan-Fe(III) composite as a dual-functional material for synergistically enhanced co-removal of Cu(II) and Cr(VI) based on adsorption and redox. *Chem Eng J* 2016;vol. 306:579–87. <https://doi.org/10.1016/J.CEJ.2016.07.096>.
- [129] Saleem A, Wang J, Sun T, Sharaf F, Haris M, Lei S. Enhanced and selective adsorption of Copper ions from acidic conditions by diethylenetriaminepentaacetic acid-chitosan sewage sludge composite. *J Environ Chem Eng* 2020;vol. 8(6):104430. <https://doi.org/10.1016/J.JECE.2020.104430>.
- [130] Yang SC, Liao Y, Karthikeyan KG, Pan XJ. Mesoporous cellulose-chitosan composite hydrogel fabricated via the co-dissolution-regeneration process as biosorbent of heavy metals. *Environ Pollut* 2021;vol. 286:117324. <https://doi.org/10.1016/J.ENVPOL.2021.117324>.
- [131] Hosseinzadeh H, Ramin S. Effective removal of copper from aqueous solutions by modified magnetic chitosan/graphene oxide nanocomposites. *Int J Biol Macromol* 2018;vol. 113:859–68. <https://doi.org/10.1016/J.IJBIOMAC.2018.03.028>.
- [132] He Y, et al. Amidoxime-functionalized polyacrylamide-modified chitosan containing imidazoline groups for effective removal of Cu²⁺ and Ni²⁺. *Carbohydr Polym* 2021;vol. 252:117160. <https://doi.org/10.1016/J.CARBPOL.2020.117160>.
- [133] Khalil NA, et al. Magnetic chitosan hydrogel beads as adsorbent for copper removal from aqueous solution. *Mater Today Proc* 2023;vol. 74:499–503. <https://doi.org/10.1016/J.MATPR.2022.12.018>.
- [134] Zhang H, Omer AM, Hu Z, Yang LY, Ji C, Ouyang X kun. Fabrication of magnetic bentonite/carboxymethyl chitosan/sodium alginate hydrogel beads for Cu (II) adsorption. *Int J Biol Macromol* 2019;vol. 135:490–500. <https://doi.org/10.1016/J.IJBIOMAC.2019.05.185>.
- [135] Surgutskaia NS, et al. Efficient Cu²⁺, Pb²⁺ and Ni²⁺ ion removal from wastewater using electrospon DTPA-modified chitosan/polyethylene oxide nanofibers. *Sep Purif Technol* 2020;vol. 247:116914. <https://doi.org/10.1016/J.SEPUR.2020.116914>.
- [136] Dou J, et al. Functionalization of carbon nanotubes with chitosan based on MALI multicomponent reaction for Cu²⁺ removal. *Int J Biol Macromol* 2019;vol. 136:476–85. <https://doi.org/10.1016/J.IJBIOMAC.2019.06.112>.
- [137] Ibrahim AG, Saleh AS, Elsharma EM, Metwally E, Siyam T. “Chitosan-g-maleic acid for effective removal of copper and nickel ions from their solutions.”. *Int J Biol Macromol* 2019;vol. 121:1287–94. <https://doi.org/10.1016/J.IJBIOMAC.2018.10.107>.
- [138] Wu Z, Deng W, Zhou W, Luo J. Novel magnetic polysaccharide/graphene oxide @ Fe₃O₄ gel beads for adsorbing heavy metal ions. *Carbohydr Polym* 2019;vol. 216:119–28. <https://doi.org/10.1016/J.CARBPOL.2019.04.020>.
- [139] Fan C, Li K, Li J, Ying D, Wang Y, Jia J. Comparative and competitive adsorption of Pb(II) and Cu(II) using tetraethylenepentamine modified chitosan/CoFe₂O₄ particles. *J Hazard Mater* 2017;vol. 326:211–20. <https://doi.org/10.1016/J.JHAZMAT.2016.12.036>.
- [140] Ngwabebhoh FA, Erdem A, Yildiz O. Synergistic removal of Cu(II) and nitrazine yellow dye using an eco-friendly chitosan-montmorillonite hydrogel: Optimization by response surface methodology. *J Appl Polym Sci* 2016;vol. 133(29):43664. <https://doi.org/10.1002/APP.43664>.
- [141] Sabourian V, Ebrahimi A, Naseri F, Irani M, Rahimi A. Fabrication of chitosan/silica nanofibrous adsorbent functionalized with amine groups for the removal of Ni(II), Cu(II) and Pb(II) from aqueous solutions: batch and column studies.”. *RSC Adv* 2016;vol. 6(46):40354–65. <https://doi.org/10.1039/C6RA00456C>.
- [142] Lu C, Yu S, Yao T, Zeng C, Wang C, Zhang L. “Zeolite X/chitosan hybrid microspheres and their adsorption properties for Cu(II) ions in aqueous solutions.”. *J Porous Mater* 2015;vol. 22(5):1255–63. <https://doi.org/10.1007/S10934-015-0003-0/FIGURES/6>.
- [143] Gandhi MR, Meenakshi S. Preparation and characterization of silica gel/chitosan composite for the removal of Cu(II) and Pb(II). *Int J Biol Macromol* 2012;vol. 50(3):650–7. <https://doi.org/10.1016/J.IJBIOMAC.2012.01.012>.
- [144] Wang X, Zheng Y, Wang A. Fast removal of copper ions from aqueous solution by chitosan-g-poly(acrylic acid)/attapulgite composites. *J Hazard Mater* 2009;vol. 168(2–3):970–7. <https://doi.org/10.1016/J.JHAZMAT.2009.02.120>.
- [145] Wang Q, Li Y. Facile and green fabrication of porous chitosan aerogels for highly efficient oil/water separation and metal ions removal from water. *J Environ Chem Eng* 2023;vol. 11(3):109689. <https://doi.org/10.1016/J.JECE.2023.109689>.
- [146] He W, Yu Q, Wang N, Ouyang X kun. Efficient adsorption of Cu(II) from aqueous solutions by acid-resistant and recyclable ethylenediamine tetraacetic acid-grafted polyvinyl alcohol/chitosan beads. *J Mol Liq* 2020;vol. 316:113856. <https://doi.org/10.1016/J.MOLLIQ.2020.113856>.
- [147] Dong Q, et al. Selective removal of lead ions through capacitive deionization: Role of ion-exchange membrane. *Chem Eng J* 2019;vol. 361:1535–42. <https://doi.org/10.1016/J.CEJ.2018.10.208>.
- [148] Chen Y, Cai W, Dang C, Fan J, Zhou J, Liu Z. A facile sol-gel synthesis of chitosan-boehmite film with excellent acid resistance and adsorption performance for Pb(II). *Chem Eng Res Des* 2020;vol. 161:332–9. <https://doi.org/10.1016/J.CHERD.2020.07.018>.
- [149] H.N. Saleh et al., “Carcinogenic and Non-carcinogenic Risk Assessment of Heavy Metals in Groundwater Wells in Neyshabur Plain, Iran,” 2011, <doi:10.1007/s12011-018-1516-6>.
- [150] Wang Y, et al. An electrochemical aptasensor based on gold-modified MoS₂/rGO nanocomposite and gold-palladium-modified Fe-MOFs for sensitive detection of lead ions. *Sens Actuators B Chem* 2020;vol. 319. <https://doi.org/10.1016/J.SNB.2020.128313>.
- [151] Patel PK, Pandey LM, Uppaluri RVS. Adsorptive removal of Zn, Fe, and Pb from Zn dominant simulated industrial wastewater solution using polyvinyl alcohol grafted chitosan variant resins. *Chem Eng J* 2023;vol. 459:141563. <https://doi.org/10.1016/J.CEJ.2023.141563>.
- [152] Amin KF, Gulshan F, Asrafuzzaman, Das H, Rashid R, Hoque SM. Synthesis of mesoporous silica and chitosan-coated magnetite nanoparticles for heavy metal

- adsorption from wastewater. *Environ Nanotechnol Monit Manag* 2023;vol. 20:100801. <https://doi.org/10.1016/J.ENMM.2023.100801>.
- [153] Xu X, Ouyang X kum, Yang LY. Adsorption of Pb(II) from aqueous solutions using crosslinked carboxylated chitosan/carboxylated nanocellulose hydrogel beads. *J Mol Liq* 2021;vol. 322:114523. <https://doi.org/10.1016/J.MOLLIQ.2020.114523>.
- [154] Hu D, et al. Adsorption of Pb(II) from aqueous solution by polyacrylic acid grafted magnetic chitosan nanocomposite. *Int J Biol Macromol* 2020;vol. 154:1537–47. <https://doi.org/10.1016/J.IJBIOMAC.2019.11.038>.
- [155] Karim MR, Aijaz MO, Alharth NH, Alharbi HF, Al-Mubaddel FS, Awual MR. Composite nanofibers membranes of poly(vinyl alcohol)/chitosan for selective lead(II) and cadmium(II) ions removal from wastewater. *Ecotoxicol Environ Saf* 2019;vol. 169:479–86. <https://doi.org/10.1016/J.ECOENV.2018.11.049>.
- [156] Dinh VP, Le NC, Tuyen LA, Hung NQ, Nguyen VD, Nguyen NT. Insight into adsorption mechanism of lead(II) from aqueous solution by chitosan loaded MnO₂ nanoparticles. *Mater Chem Phys* 2018;vol. 207:294–302. <https://doi.org/10.1016/J.MATCHEMPHYS.2017.12.071>.
- [157] Guo DM, An QDa, Xiao ZY, Zhai SR, Yang DJ. Efficient removal of Pb(II), Cr(VI) and organic dyes by polydopamine modified chitosan aerogels. *Carbohydr Polym* 2018;vol. 202:306–14. <https://doi.org/10.1016/J.CARBPOL.2018.08.140>.
- [158] ting Li T, et al. Removal of lead(II) from aqueous solution with ethylenediamine-modified yeast biomass coated with magnetic chitosan microparticles: Kinetic and equilibrium modeling. *Chem Eng J* 2013;vol. 214:189–97. <https://doi.org/10.1016/J.CEJ.2012.10.055>.
- [159] X.-X. Liang et al., “molecules Facile Preparation of Metal-Organic Framework (MIL-125)/Chitosan Beads for Adsorption of Pb(II) from Aqueous Solutions”, [doi:10.3390/molecules23071524](https://doi.org/10.3390/molecules23071524).
- [160] Bhatnagar A, Sillanpää M. Applications of chitin- and chitosan-derivatives for the detoxification of water and wastewater - a short review. *Nov. 30 Adv Colloid Interface Sci* 2009;vol. 152(1–2):26–38. <https://doi.org/10.1016/j.cis.2009.09.003>.
- [161] Crini G. Recent developments in polysaccharide-based materials used as adsorbents in wastewater treatment. *Prog Polym Sci (Oxf)* Jan. 2005;vol. 30(1):38–70. <https://doi.org/10.1016/j.progpolymsci.2004.11.002>.
- [162] Vakili M, et al. Regeneration of chitosan-based adsorbents used in heavy metal adsorption: a review. *Oct. 01 Separation and Purification Technology* vol. 224. Elsevier B.V.; 2019. p. 373–87. <https://doi.org/10.1016/j.seppur.2019.05.040>.
- [163] H. Ali, E. Khan, and I. Ilahi, “Environmental Chemistry and Ecotoxicology of Hazardous Heavy Metals: Environmental Persistence, Toxicity, and Bioaccumulation,” 2019, [doi:10.1155/2019/6730305](https://doi.org/10.1155/2019/6730305).
- [164] S. Sara Hassan , S. Shane Zehra , Z. Ahmed , M. Younis TALPUR , and S. Panhwar Balochistan , “Removal of arsenic contaminants from water using iron oxide nanoparticles by inductively coupled plasma mass spectrometry,” 2022, [doi:10.21203/rs.3.rs-1469404/v1](https://doi.org/10.21203/rs.3.rs-1469404/v1).
- [165] Hayat MT, Nauman M, Nazir N, Ali S, Bangash N. Environmental Hazards of Cadmium: Past, Present, and Future. *Cadmium Toxic Toler Plant: Physiol Remediat* 2019:163–83. <https://doi.org/10.1016/B978-0-12-814864-8.00007-3>.
- [166] Shin DY, et al. Adverse Human Health Effects of Chromium by Exposure Route: A Comprehensive Review Based on Toxicogenomic Approach. *International Journal of Molecular Sciences* vol. 24. Multidisciplinary Digital Publishing Institute (MDPI); Feb. 01, 2023. <https://doi.org/10.3390/ijms24043410>.
- [167] B. Gworek, W. Dmuchowski, and A.H. Baczewska-Dąbrowska, “Mercury in the terrestrial environment: a review”, [doi:10.1186/s12302-020-00401-x](https://doi.org/10.1186/s12302-020-00401-x).
- [168] Loranger S, Zayed J. Environmental and occupational exposure to manganese: a multimedia assessment. *Int Arch Occup Environ Health* 1995.
- [169] S.L. O’neal and W. Zheng, “Manganese Toxicity Upon Overexposure: a Decade in Review,” 2015, [doi:10.1007/s40572-015-0056-x](https://doi.org/10.1007/s40572-015-0056-x).
- [170] S.G. Li et al., “Lutein alleviates arsenic-induced reproductive toxicity in male mice via Nrf2 signaling”, [doi:10.1177/0960327115595682](https://doi.org/10.1177/0960327115595682).
- [171] H. Lu, X. Shi, M. Costa, and C. Huang, “Carcinogenic effect of nickel compounds,” pp. 45–67, 2005, [doi:10.1007/s11010-005-8215-2](https://doi.org/10.1007/s11010-005-8215-2).
- [172] G. Genchi, A. Carocci, G. Lauria, M.S. Sinicropi, and A. Catalano, “Nickel: Human Health and Environmental Toxicology”, [doi:10.3390/ijerph17030679](https://doi.org/10.3390/ijerph17030679).
- [173] J.L. Domingo, “Cobalt in the Environment and Its Toxicological Implications,” 1989.
- [174] D.M. Jolliffe, A.J. Budd, and D.J. Gwilt, “Massive acute arsenic poisoning,” *Anaesthesia*, vol. 46. pp. 288–290.
- [175] Luo JH, Qiu ZQ, Zhang L, Shu WQ. Arsenite exposure altered the expression of NMDA receptor and postsynaptic signaling proteins in rat hippocampus. *Toxicol Lett* 2012;vol. 211(1):39–44. <https://doi.org/10.1016/J.TOXLET.2012.02.021>.
- [176] S. Shen, X.-F. Li, W.R. Cullen, M. Weinfeld, and X.C. Le, “Arsenic Binding to Proteins,” 2013, [doi:10.1021/cr300015c](https://doi.org/10.1021/cr300015c).
- [177] Struzyńska L, Dąbrowska-Bouta B, Koza K, Sulkowski G. Inflammation-like glial response in lead-exposed immature rat brain. *Toxicol Sci* 2007;vol. 95(1):156–62. <https://doi.org/10.1093/TOXSCI/KFL134>.
- [178] Wang J, Zhu H, Yang Z, Liu Z. Antioxidative effects of hesperetin against lead acetate-induced oxidative stress in rats. *Indian J Pharm* 2013;vol. 45(4):395–8. <https://doi.org/10.4103/0253-7613.115015>.
- [179] N.N. Dongre and A.N. Suryakar, “Biochemical Effects of Lead Exposure on Systolic & Diastolic Blood Pressure, Heme Biosynthesis and Hematological Parameters in Automobile Workers of North Karnataka (India),” vol. 26, no. 4, pp. 400–406, 2011, [doi:10.1007/s12291-011-0159-6](https://doi.org/10.1007/s12291-011-0159-6).
- [180] Boskabady MH, Tabatabai SA, Parkhondeh T. Inhaled lead affects lung pathology and inflammation in sensitized and control guinea pigs. *Environ Toxicol* 2016;vol. 31(4):452–60. <https://doi.org/10.1002/TOX.22058>.
- [181] Cheng JP, Wang WH, Jia JP, Zheng M, Shi W, Lin XY. “Expression of c-fos in rat brain as a prelude marker of central nervous system injury in response to methylmercury-stimulation,”. *Biomed Environ Sci* vol. 19. 2006. p. 67–72.
- [182] Bottino C, Vázquez M, Devesa V, Laforenza U. Impaired aquaporins expression in the gastrointestinal tract of rat after mercury exposure. *J Appl Toxicol* 2016;vol. 36(1):113–20. <https://doi.org/10.1002/jat.3151>.
- [183] Chen R, et al. Associations between mercury exposure and the risk of nonalcoholic fatty liver disease (NAFLD) in US adolescents. *Environ Sci Pollut Res* 2019;vol. 26(30):31384–91. <https://doi.org/10.1007/s11356-019-06224-5>.
- [184] Zhang C, Gan C, Ding L, Xiong M, Zhang A, Li P. Maternal inorganic mercury exposure and renal effects in the Wanshan mercury mining area, southwest China. *Ecotoxicol Environ Saf* 2020;vol. 189. <https://doi.org/10.1016/J.ECOENV.2019.109987>.
- [185] R. Schutte et al., “Bone Resorption and Environmental Exposure to Cadmium in Women: A Population Study,” vol. 116, no. 6, pp. 1985–1989, 2008, [doi:10.1289/ehp.11167](https://doi.org/10.1289/ehp.11167).
- [186] C. Pan et al., “Cadmium is a potent inhibitor of PPM phosphatases and targets the M1 binding site”, [doi:10.1038/srep02333](https://doi.org/10.1038/srep02333).
- [187] M.J. Fay et al., “toxics Cadmium Nephrotoxicity Is Associated with Altered MicroRNA Expression in the Rat Renal Cortex”, [doi:10.3390/toxics6010016](https://doi.org/10.3390/toxics6010016).
- [188] Wang Y, et al. Roles of ROS, Nrf2, and autophagy in cadmium-carcinogenesis and its prevention by sulforaphane. *Toxicol Appl Pharm* 2018;vol. 353:23–30. <https://doi.org/10.1016/j.taap.2018.06.003>.
- [189] T. Pavesi and J.C. Moreira, “Mechanisms and individuality in chromium toxicity in humans chromium susceptibility, chromium toxicity, formation of DNA-Cr; formation of DNA-protein-Cr adducts, polymorphism,” 2020, [doi:10.1002/jat.3965](https://doi.org/10.1002/jat.3965).
- [190] Chen T, et al. The effect of hexavalent chromium on the incidence and mortality of human cancers: a meta-analysis based on published epidemiological cohort studies. (www.frontiersin.org). *Front Oncol* 2019;vol. 9:24. <https://doi.org/10.3389/fonc.2019.00024>.
- [191] Schwartz GG. Urinary Cadmium, Impaired Fasting Glucose, and Diabetes in the NHANES III DORA IL’YASOVA, PHD 2 ANASTASIA IVANOVA, PHD 3. *Diabetes Care* 2003;vol. 26:468–70.
- [192] Zhang X, et al. Impacts of lead/zinc mining and smelting on the environment and human health in China. *Environ Monit Assess* 2012;vol. 184:2261–73. <https://doi.org/10.1007/s10661-011-2115-6>.