

# Fabrication and characterization of composite TiO<sub>2</sub> nanotubes/ boron-doped diamond electrodes towards enhanced supercapacitors

*M. Sobaszek<sup>1</sup>, K. Siuzdak<sup>2</sup>, M. Sawczak<sup>2</sup>, J. Ryl<sup>3</sup> and R. Bogdanowicz<sup>1\*</sup>*

<sup>1</sup>Department of Metrology and Optoelectronics, Faculty of Electronics, Telecommunications and Informatics, Gdańsk University of Technology, 11/12 G. Narutowicza St., 80-233 Gdańsk, Poland

<sup>2</sup> Polish Academy of Sciences, The Szewalski Institute of Fluid-Flow Machinery, 14 Fiszerza St., 80-231 Gdańsk, Poland

<sup>3</sup>Department of Electrochemistry, Corrosion and Material Engineering, Faculty of Chemistry Gdańsk University of Technology, 11/12 G. Narutowicza St., 80-233 Gdańsk, Poland

## **Abstract**

The composite TiO<sub>2</sub> nanotubes / boron-doped diamond electrodes were deposited using Microwave Plasma Enhanced Chemical Vapor Deposition resulting in the improved electrochemical performance. This composite electrode can deliver high specific capacitance of 7.46 mFcm<sup>-2</sup> comparing to BDD deposited onto flat Ti plate (0.11 mFcm<sup>-2</sup>). The morphology and composition of composite electrode were characterized by scanning electron microscopy, Raman spectroscopy

and X-ray photoelectron spectroscopy (XPS) techniques. According to XPS and Raman analysis, structure of TiO<sub>2</sub> was greatly changed during Chemical Vapor Deposition process: formation of Ti<sup>3+</sup> sites, partial anatase to rutile transformation and titanium carbide phase formation. This effect is attributed to the simultaneous presence of activated hydrogen and carbon in the plasma leading to enhanced dehydration of NTs (nanotubes) followed by carbon bonding. The enhanced capacitive effect of TiO<sub>2</sub> NT / BDD could be recognized as: (1) the unique synergistic morphology of NTs and BDD providing more efficient conducting pathway for the diffusion of ions and (2) partial decomposition of NTs and transformation towards to TiC and Ti<sub>2</sub>O<sub>3</sub> fractions. Finally, highly ordered titania nanotubes produced *via* simply, quick and controllable method – anodization, could act as promising substrate for conductive BDD layer deposition and further application of such composites for supercapacitor construction.

**Keywords:** Microwave Plasma Enhanced Chemical Vapor Deposition, Boron-Doped Diamond, Titania Nanotube, Supercapacitors

\*Corresponding author: rbogdan@eti.pg.gda.pl, Phone: +48583471503, Fax: +48583471848

## 1. Introduction

In recent years, various efforts have been made towards development of electrode materials especially including extended surface area [1–4] and usage of metal oxides [5] or organic compounds [6] together in order to form composite structures with unique electrochemical features. Among these oxide materials, TiO<sub>2</sub> nanotubes are the most attractive candidates which can be prepared by a simple electrochemical anodization. The titania nanotubes provide a large specific surface area, a direct pathway of charge transport but the specific capacitances are generally limited to less than 1 mFcm<sup>-2</sup> without intentional doping or treatment. Lu *et al.* [7] and Li *et al.* [8]



reported that hydrogenated TiO<sub>2</sub> obtained by heating in hydrogen atmosphere resulted in an improvement of specific capacitance up to 3.24 mFcm<sup>-2</sup>. Furthermore, Wang and Leshuk *et al.* [9,10] received also hydrogenated TiO<sub>2</sub> under hydrogen plasma treatment characterized with similar electrochemical behaviour. Several groups reported results on composite structures based on carbon / TiO<sub>2</sub> nanotubes multilayer. Chen and Dwivedi *et al.* [11,12] showed synthesis of diamond-like carbon (DLC) nanorods onto TiO<sub>2</sub>/Ti nanotubes and DLC films on nanostructured titanium. Zanin *et al.* [13,14] reported electrochemically active (DLC) electrodes featuring high specific surface area prepared by microwave plasma enhanced chemical vapor deposition (MWPECVD) onto multiwall carbon nanotubes. Yuan *et al.* [15,16] proposed a direct deposition of titania nanotubes onto boron-doped diamond (BDD) films. Moreover, Gao *et al.*[17] showed Multiwall nanotubes-TiO<sub>2</sub> composite electrode with specific capacitance up to 4.4 mF cm<sup>-2</sup> for 10 mg ml<sup>-1</sup> of APS in 1 M H<sub>2</sub>SO<sub>4</sub> and long-term cycle stability. Dash *et al.* [18] fabricated titanium carbide derived nanoporous carbon by thermo-chemical etching of titanium carbide. Those electrodes showed specific up to 130 F g<sup>-1</sup> in organic electrolyte.

The advantage of using diamond in supercapacitor applications were recently reported by several authors [13,19,20]. They demonstrate that deposition of diamond on porous substrate significantly increases specific capacitance on different substrates like Si, Ti or carbon nanotubes. Moreover, the combining diamond with porous or structured substrate can occurs with nanopores and mesopores that significantly increase capacitance investigated by Chmiola *et al.* [21,22]. Gao *et al.* reported various bottom-up grown diamond nanostructures like diamond-coated Si nanowires [23] or SiO<sub>2</sub> spheres [24], which could deliver capacitance of 105 μF/cm<sup>2</sup> and 0.598 mF cm<sup>-2</sup>, respectively. Moreover, they proved that diamond based materials show the potential to work as pseudocapacitor electrode without organic electrolyte [24] offering simultaneously the high specific capacitance, low cost, non-toxicity and the high conductivity.



In this paper, we show the formation of TiO<sub>2</sub> nanotubes (NTs) / BDD structure and resolve the potential origin of capacitive effect. The electrode material dedicated for supercapacitor application based on TiO<sub>2</sub> nanotubes over-grown by thin boron-doped diamond film in MWPECVD deposition process was presented. In our previous work, we concluded that the BDD over-grown titania NTs can provide high specific capacitance increase resulting in 2.10, 4.79, and 7.46 mF cm<sup>-2</sup> at a scan rate of 10 mV s<sup>-1</sup> for the [B]/[C] ratio of 2, 5 and 10k, respectively [25]. Nevertheless, the precise explanation of improved electrochemical performance of composite TiO<sub>2</sub> NTs / BDD has not yet been resolved and reported.

The surface analysis was employed to investigate structure and its potential influence on the increase of capacitance. The scanning electron microscopy (SEM) was applied to investigate evolution of surface morphology. Cross-sectional studies of composition of electrode was investigated by means of Raman spectroscopy and the electrode composition was analyzed by means of X-ray photoelectron spectroscopy (XPS).

Figure 1

**Figure 1.** Formation scheme of composite TiO<sub>2</sub> nanotubes / boron-doped diamond electrode.

## 2. Experimental details

The fabrication process of TiO<sub>2</sub> nanotubes and diamond film synthesis can be found elsewhere [25]. Titania nanotube arrays were formed by anodization of 0.5 mm thick titanium foils (1 x 1 cm, ASTM Grade 1, 99.5%, Spinex, Poland). The boron-doped diamond was synthesized in an MWPECVD system (SEKI Technotron AX5400S, Japan) on titanium/titania nanotubes (NT) substrates (see Fig. 1). The diborane (B<sub>2</sub>H<sub>6</sub>) was used as dopant precursor, and [B]/[C] ratio of boron level in the gas phase was 2000, 5000 and 10 000 ppm. The growth time was 1 h, producing microcrystalline film of ca. 400 nm thickness.

The surface morphology and molecular structure of the electrode surface was analyzed using SEM (EVO-40, Zeiss, Germany) and Raman spectroscopy (InVia, Renishaw, UK), respectively. The SEM photographs were taken under high vacuum conditions. Beam accelerating voltage was kept at 20kV. The Raman spectra were recorded at room temperature using micro-Raman system with 514 nm argon ion laser as excitation. Spectra were recorded in the range of 120 – 3300  $\text{cm}^{-1}$ .

Electrochemical measurements of prepared electrode materials were performed by the potentiostat-galvanostat system AutoLab PGStat302N in a three-electrode assembly at 295 K. Ti metal plate covered with pure nanotubes, BDD layer or composite material  $\text{TiO}_2/\text{BDD}$  with different [B]/[C] ratio stayed as a working electrode. The counter electrode consisted of Pt gauze and reference electrode was: Ag/AgCl/0.1 M KCl. Electrodes with a geometrical surface area of 1  $\text{cm}^2$  were tested by cyclic voltammetry in deaerated solutions: 0.1 M  $\text{NaNO}_3$  without and with 1 mM  $\text{K}_3\text{Fe}(\text{CN})_6$ . Prior to taking electrochemical measurement, a pretreatment was performed holding electrode at -0.1 V for 60 s.

The high-resolution photoelectron spectroscopy (ThermoFisher Scientific, Escalab 250Xi, UK) was used to determine chemical binding properties of the surface, utilizing monochromatic Al- $\text{K}\alpha$  source with spot diameter of 650  $\mu\text{m}$ . High-resolution spectra were recorded in CAE mode, at energy step size of 0.1 eV at a pass energy of 10 eV and dwell time 50 ms. Charge neutralization was implemented by means of a flood gun. In order to normalize spectroscopic measurements, X axis (BE) was calibrated for peak characteristics of neutral carbon 1s (BE = 284.6 eV). Data analysis was performed using Avantage v.5 software provided by the manufacturer.

### 3. Results and discussion

#### 3.1. Composition and surface morphology of $\text{TiO}_2$ NT/BDD electrode

**Structure of composite electrode (SEM, Raman):** As it is presented in Figure 1, the electrode is expected to have the multilayer structure consisting of layer of titania nanotubes covered in MWPECVD process with layer of boron doped diamonds. The morphology of composite electrode was investigated using SEM. To visualise the internal structure of electrode the top BDD layer was partially removed what is presented in Figure 2a. The BDD layer (R1) forms a fully encapsulated film of total thickness of 400 nm and average diamond diameter of 250 nm. The polycrystalline BDD exhibits columnar growth. Thus, such films have highly tailorable microstructure and intergrain porosity [26]. Under BDD film the regular structure of TiO<sub>2</sub> NTs can be observed – Figure 2a (R2). The nanotubular architecture is not affected by BDD growth process and keep their pristine shape [25]. On the cross sectional SEM image (Fig. 2b) it can be observed that TiO<sub>2</sub> NTs layer is overgrown with semi-spherical nanostructures. Such a TiO<sub>2</sub> NTs /BDD composite have been subjected to a detailed analysis using Raman spectroscopy, giving information about molecular composition of the interface between TiO<sub>2</sub> NTs and diamond overlayer. Additionally, XPS was utilized to identify semi-spherical nanostructures across TiO<sub>2</sub> NTs and explain origin of these carbonous inclusions.

Figure 2

**Figure 2.** SEM image of composite BDD-TiO<sub>2</sub> NTs electrode (left image): (a) top view of electrode with partially removed BDD layer and (b) cross section image showing top BDD layer and titania nanotubes overgrown with semispherical nanostructures; (c) Raman spectra recorded for top BDD layer (R1) and TiO<sub>2</sub> NTs layer (R2).

Figure 3

**Figure 3.** Raman spectra recorded for TiO<sub>2</sub> NTs processed in carbon free plasma (a) and diamond deposition process (b).

Raman spectra recorded for top BDD layer (R1) and TiO<sub>2</sub> NTs layer uncovered by mechanical removing of BDD film (R2) are presented in Figure 2c. Raman spectrum of BDD film (R1) is characterised with bands typical for BDD structures [27]. Raman spectra (R1) presented in Figure 2c is standard for BDD deposited on the titanium based substrates. Similar spectra were recently reported by other authors in electrochemical field [28,29]. Relatively low quality of BDDs deposited on titanium base substrates is mostly caused by low quality of substrate surface (no polishing), thermal stresses (different thermal expansions coefficients) as well as preferable growth of graphitic phase on non-diamond materials.

In the deeper layer of titania NTs only carbon structures characterised with bands D (1353 cm<sup>-1</sup>) and G (1600 cm<sup>-1</sup>) typical for *sp*<sup>2</sup>-type bonded carbon can be identified. It allows to conclude that semi-spherical nanostructures observed in the SEM image are composed of carbon. The width and intensity of Raman bands suggest the disordered nature of these carbon forms. The absence of anatase bands (143.7, 396.6, 518.6 and 637.7 cm<sup>-1</sup>) observed for pristine titania NTs indicates transformation of primary crystalline structure of nanotubular layer into another structure characterised with intense Raman bands located near 243 and 331 cm<sup>-1</sup>. These signals are found to be typical for Ti<sub>2</sub>O<sub>3</sub>. [30]. The Raman spectrum also exhibits broad signals centred around ~289 and 450 cm<sup>-1</sup>, corresponding to Ti–O vibration modes in the titania framework [31,32]. The wide bands located at 420 and 605 cm<sup>-1</sup> indicates the presence of TiC inside NTs structure.

**Table 1.** Raman bands positions for un-processed and plasma processed TiO<sub>2</sub> NTs.

Table 1

The comparison of Raman spectra recorded for carbon overgrown titania NTs present in composite electrode and titania NTs processed in carbon free H<sub>2</sub> plasma (Fig. 3, Tab. 1) allows to



observe the shifts in Raman band positions attributed to internal stress in the structure induced by lattice defects generated by TiO<sub>2</sub> and TiC inclusions.

**Composite electrode composition (XPS):** Figure 4 presents high-resolution C1s spectra carried out for thin BDD film grown on TiO<sub>2</sub> NTs at two different [B]/[C] ratios (2k and 10k). For both analyzed BDD electrodes, XPS spectra contains four main peak components. For the purpose of peak deconvolution during analysis, all the C-C peaks were constrained in the FWHM range between 0.8 and 1.2 and C-O peak in the FWHM range between 1.0 and 1.5. Peaks had a form of Lorentz/Gaussian mix sum of 10:40. Peak background type used was Smart, as implemented in Avantage software.

Figure 4

**Figure 4.** The high-resolution C1s spectra carried out for thin BDD film grown on TiO<sub>2</sub> NTs with 2k and 10k [B]/[C] ratio.

The main C1s peak was noted at  $284.4 \pm 0.2$  eV and corresponds to hydrogen terminated boron doped diamond (HT-BDD). Its location can shift for different dopant levels [33]. However, it remains within  $\pm 0.2$  eV range for both 2k and 10k BDD samples. The second peak is shifted at +0.8 eV and corresponds to oxygen terminated boron doped diamond (OT-BDD). The third peak is observed at +1.2 eV shifts and is related with the presence of oxidized carbon atoms C-OH and C-OC. Finally, a small peak was observed for 283.4 eV, which should be interpreted as  $sp^2$  hybridized carbon. Its presence is over two times higher in the case of BDD electrode with 10k [B]/[C], which results from higher disorder of diamond structure with higher boron dopant level. Such interpretation is in agreement with previously published results [34,35].





**Table 2.** Percentage contribution (in at.%) of each C1s peak for BDD grown on TiO<sub>2</sub> NTs with 2k and 10k [B]/[C] ratio.

Table 2

High-resolution XPS spectra of Ti2p peaks of TiO<sub>2</sub> NT reference sample consists mostly of a mixture of anatase (17.2 at.%) and rutile (12.2 at.%), Ti2p3 BE of those is 459.1 eV and 458.6 eV respectively [36]. Third Ti2p3 component corresponds to Ti<sub>2</sub>O<sub>3</sub> and can be observed at BE of 457.2 eV[37].

As a result of BDD deposition on the top of TiO<sub>2</sub> NTs, fourth component was found on Ti2p high-resolution spectra. It originates from TiO, which was confirmed by both position (455.3 eV) as well as an energy separation value between Ti2p3 and Ti2p1 peaks [38]. The BDD deposition or exposition to hydrogen rich microwave plasma changes the structure of TiO<sub>2</sub> NTs significantly and results in decrease in the oxygen stoichiometry. Higher amount of Ti<sup>3+</sup> and Ti<sup>2+</sup> can be observed, together with a significant drop of Ti<sup>4+</sup> and oxygen in so treated TiO<sub>2</sub> NT substrate.

Furthermore, the cross-sectional XPS spectrum recorded at the composite electrode reveals another peak, at considerably lower energy (454.6 eV), corresponding to TiC [39]. Presence of TiC arrangement was also confirmed via Raman analysis (see Fig. 2 and 3) and by cross-sectional SEM observations - semi-spherical nanostructures across TiO<sub>2</sub> NTs (see Fig. 2B).

### *3.2. Electrochemical characterization of TiO<sub>2</sub>/BDDelectrode*

Cyclic voltammetry performed in ferricyanide solution was used to investigate the difference in electrochemical properties between composite material and its pure counterparts, because such redox system is characterized with kinetics highly dependent on density of electronic states near



the formal potential ( $E_f$ ). As it can be seen in Figure 5, typical redox behavior is observed for BDD modified samples. For pure titania any redox peaks is never observed because  $E_f$  overlaps bandgap energy of  $\text{TiO}_2$  nanotubes [40]. The replacement of titanium flat plate by  $\text{TiO}_2$  nanotube arrays as a support for BDD deposition results in charging character of registered cyclic voltammetry (CV) curves. The voltammograms were registered also at different scan rates and the relation  $j$  vs.  $(V/s)^{-0.5}$  was depicted in Figure 5b. According to given plots, clear linear relation shows that oxidation process is under diffusion control. Same linear dependence but with opposite slope was also observed for reduction peak current. The value of double layer capacitance calculated on the CV obtained in purely 0.1M  $\text{NaNO}_3$ . The specific areal capacitance of  $\text{TiO}_2$ /BDD composites equals 2.10, 4.79, 7.46  $\text{mF cm}^{-2}$  for the respective [B]/[C] ratios of 2k, 5k and 10k at a scan rate of 10 mV/s, whereas for the pure BDD film, the value of double-layer capacitance reached only 0.11  $\text{mF/cm}^{-2}$  [25]. Such small capacitance value reported for Ti plate covered by BDD layer [41] or pure titania nanotubes [42,43] is typical for these electrode materials. The increase in charging current displayed on CV curves can be caused by two main factors: (a) specific architecture of titania nanotube that increase remarkably real surface area available for BDD growth and each tube could act as a straight path for charge movement [20]; (b) transformation of crystalline phase and chemical composition of titania during BDD deposition *via* MWPECVD processing. Concerning (a), highly enlarged surface area provides improved boundary density comparing to simple metal plate [44]. Therefore, expanded electrode/electrolyte interface for  $\text{TiO}_2$ /BDD materials is ready for charge accumulation exhibited as a capacitive current [13]. On the other hand, according to detailed XPS and Raman analysis described above, structure of  $\text{TiO}_2$  was greatly changed during MWPECVD process: formation of  $\text{Ti}^{3+}$  sites, partial transformation from anatase to rutile crystalline phase and titanium carbide formation. According to literature, the mixture of anatase and rutile phase [45], oxygen non-stoichiometry [46] as well as appearance of Ti-C



[47] greatly improve electrical properties observed here as huge capacitive current. Thus, highly ordered titania nanotubes produced *via* simply, quick and controllable method – anodization, could act as promising substrate for conductive BDD layer deposition and its further application for supercapacitor construction.

Figure 5

**Figure 5.** Cyclic voltammetry curves: (a) the composite electrodes TiO<sub>2</sub>NTs /BDD-10k, pure titania and BDD layer immersed in 0.1 M NaNO<sub>3</sub> ( $v = 50$  mV/s), (b) The plots of peak currents versus the square root of the scan rate for different BDD covered electrodes.

#### 4. Conclusions

The fabrication and characterization of composite TiO<sub>2</sub> nanotubes / boron-doped diamond electrodes grown in MWPECVD was investigated in details. The BDD overlayer fully encapsulates TiO<sub>2</sub>NTs exhibiting typical columnar growth character. Thus, obtained electrode has highly tailorable microstructure and intergrain porosity. The architecture of NTs are not affected by BDD growth process and keep their pristine shape. The XPS and Raman analyses reveal that structure of TiO<sub>2</sub> is changed during MWPECVD process: formation of Ti<sup>3+</sup> sites, partial transformation from anatase to rutile crystalline phase and titanium carbide formation. Furthermore, the cross-sectional SEM images display that TiO<sub>2</sub> NTs are overgrown with semi-spherical nanostructures. These effects are attributed to the simultaneous presence of activated hydrogen and carbon in the plasma leading to enhanced dehydration of NTs followed by carbon bonding. The electrochemical studies showed the strong effect of enhanced specific areal capacitance of TiO<sub>2</sub>/BDD up to 7.46 mF cm<sup>-2</sup> for the highest [B]/[C] ratio at a scan rate of 10 mV/s, whereas the pure BDD reached only 0.11 mF/cm<sup>2</sup>.



Summarizing, highly ordered titania NTs produced *via* simply and controllable method – anodization, could act as promising substrate for conductive BDD layer deposition and its further application for supercapacitor and energy storage devices.

## Acknowledgements

The authors gratefully acknowledge financial support from the Polish National Science Centre (NCN) under Grant No. 2011/03/D/ST7/03541 and No. 2012/07/D/ST5/02269. The DS funds of the Faculty of Electronics, Telecommunications and Informatics of the Gdansk University of Technology are also acknowledged.

## References

- [1] A.G. Pandolfo, A.F. Hollenkamp, Carbon properties and their role in supercapacitors, *J. Power Sources*. 157 (2006) 11–27. doi:10.1016/j.jpowsour.2006.02.065.
- [2] R.R. Salunkhe, Y. Kamachi, N.L. Torad, S.M. Hwang, Z. Sun, S.X. Dou, J.H. Kim, Y. Yamauchi, Fabrication of symmetric supercapacitors based on MOF-derived nanoporous carbons, *J. Mater. Chem. A*. 2 (2014) 19848–19854. doi:10.1039/C4TA04277H.
- [3] R.R. Salunkhe, Y.-H. Lee, K.-H. Chang, J.-M. Li, P. Simon, J. Tang, N.L. Torad, C.-C. Hu, Y. Yamauchi, Nanoarchitected Graphene-Based Supercapacitors for Next-Generation Energy-Storage Applications, *Chem. – Eur. J.* 20 (2014) 13838–13852. doi:10.1002/chem.201403649.
- [4] R.R. Salunkhe, J. Lin, V. Malgras, S.X. Dou, J.H. Kim, Y. Yamauchi, Large-scale synthesis of coaxial carbon nanotube/Ni(OH)<sub>2</sub> composites for asymmetric supercapacitor application, *Nano Energy*. 11 (2015) 211–218. doi:10.1016/j.nanoen.2014.09.030.
- [5] T.-D. Dang, A.N. Banerjee, S.W. Joo, B.-K. Min, Synthesis of Amorphous and Crystalline Hollow Manganese Oxide Nanotubes with Highly Porous Walls Using Carbon Nanotube Templates and Enhanced Catalytic Activity, *Ind. Eng. Chem. Res.* 53 (2014) 9743–9753. doi:10.1021/ie5006756.
- [6] A. Thomas, F. Goettmann, M. Antonietti, Hard Templates for Soft Materials: Creating Nanostructured Organic Materials, *Chem. Mater.* 20 (2008) 738–755. doi:10.1021/cm702126j.
- [7] X. Lu, G. Wang, T. Zhai, M. Yu, J. Gan, Y. Tong, Y. Li, Hydrogenated TiO<sub>2</sub> Nanotube Arrays for Supercapacitors, *Nano Lett.* 12 (2012) 1690–1696. doi:10.1021/nl300173j.
- [8] S.-C. Li, Z. Zhang, D. Sheppard, B.D. Kay, J.M. White, Y. Du, I. Lyubinetsky, G. Henkelman, Z. Dohnálek, Intrinsic Diffusion of Hydrogen on Rutile TiO<sub>2</sub>(110), *J. Am. Chem. Soc.* 130 (2008) 9080–9088. doi:10.1021/ja8012825.
- [9] Z. Wang, C. Yang, T. Lin, H. Yin, P. Chen, D. Wan, F. Xu, F. Huang, J. Lin, X. Xie, M. Jiang, H-Doped Black Titania with Very High Solar Absorption and Excellent Photocatalysis



Enhanced by Localized Surface Plasmon Resonance, *Adv. Funct. Mater.* 23 (2013) 5444–5450. doi:10.1002/adfm.201300486.

- [10] T. Leshuk, R. Parviz, P. Everett, H. Krishnakumar, R.A. Varin, F. Gu, Photocatalytic Activity of Hydrogenated TiO<sub>2</sub>, *ACS Appl. Mater. Interfaces.* 5 (2013) 1892–1895. doi:10.1021/am302903n.
- [11] J.-B. Chen, C.-W. Wang, J. Wang, Y. Li, R.-S. Guo, B.-H. Ma, F. Zhou, W.-M. Liu, Synthesis and field emission of diamond-like carbon nanorods on TiO<sub>2</sub>/Ti nanotube arrays, *Appl. Surf. Sci.* 256 (2009) 39–42. doi:10.1016/j.apsusc.2009.07.049.
- [12] N. Dwivedi, S. Kumar, H.K. Malik, Nanostructured Titanium/Diamond-Like Carbon Multilayer Films: Deposition, Characterization, and Applications, *ACS Appl. Mater. Interfaces.* 3 (2011) 4268–4278. doi:10.1021/am200939j.
- [13] H. Zanin, P.W. May, D.J. Fermin, D. Plana, S.M.C. Vieira, W.I. Milne, E.J. Corat, Porous Boron-Doped Diamond/Carbon Nanotube Electrodes, *ACS Appl. Mater. Interfaces.* 6 (2014) 990–995. doi:10.1021/am4044344.
- [14] H. Zanin, P.W. May, R.L. Harniman, T. Risbridger, E.J. Corat, D.J. Fermin, High surface area diamond-like carbon electrodes grown on vertically aligned carbon nanotubes, *Carbon.* 82 (2015) 288–296. doi:10.1016/j.carbon.2014.10.073.
- [15] J. Yuan, H. Li, Q. Wang, S. Cheng, X. Zhang, H. Yu, X. Zhu, Y. Xie, Fabrication, characterization and optical properties of TiO<sub>2</sub> nanotube arrays on boron-doped diamond film through liquid phase deposition, *Chem. Res. Chin. Univ.* 30 (2014) 18–22. doi:10.1007/s40242-014-3320-y.
- [16] J. Yuan, H. Li, S. Gao, Y. Lin, H. Li, A facile route to n-type TiO<sub>2</sub>-nanotube/p-type boron-doped-diamond heterojunction for highly efficient photocatalysts, *Chem. Commun.* 46 (2010) 3119–3121. doi:10.1039/C003172K.
- [17] Z. Gao, Z. Cui, S. Zhu, Y. Liang, Z. Li, X. Yang, Design and synthesis of MWNTs-TiO<sub>2</sub> nanotube hybrid electrode and its supercapacitance performance, *J. Power Sources.* 283 (2015) 397–407. doi:10.1016/j.jpowsour.2015.02.080.
- [18] R. Dash, J. Chmiola, G. Yushin, Y. Gogotsi, G. Laudisio, J. Singer, J. Fischer, S. Kucheyev, Titanium carbide derived nanoporous carbon for energy-related applications, *Carbon.* 44 (2006) 2489–2497. doi:10.1016/j.carbon.2006.04.035.
- [19] N.A. Braga, C. a. A. Cairo, J.T. Matsushima, M.R. Baldan, N.G. Ferreira, Diamond/porous titanium three-dimensional hybrid electrodes, *J. Solid State Electrochem.* 14 (2009) 313–321. doi:10.1007/s10008-009-0855-9.
- [20] N.G. Ferreira, A.F. Azevedo, A.F. Beloto, M. Amaral, F.A. Almeida, F.J. Oliveira, R.F. Silva, Nanodiamond films growth on porous silicon substrates for electrochemical applications, *Diam. Relat. Mater.* 14 (2005) 441–445. doi:10.1016/j.diamond.2005.01.007.
- [21] J. Chmiola, G. Yushin, Y. Gogotsi, C. Portet, P. Simon, P.L. Taberna, Anomalous Increase in Carbon Capacitance at Pore Sizes Less Than 1 Nanometer, *Science.* 313 (2006) 1760–1763. doi:10.1126/science.1132195.
- [22] J. Chmiola, G. Yushin, R. Dash, Y. Gogotsi, Effect of pore size and surface area of carbide derived carbons on specific capacitance, *J. Power Sources.* 158 (2006) 765–772. doi:10.1016/j.jpowsour.2005.09.008.
- [23] F. Gao, G. Lewes-Malandrakis, M.T. Wolfer, W. Müller-Sebert, P. Gentile, D. Aradilla, T. Schubert, C.E. Nebel, Diamond-coated silicon wires for supercapacitor applications in ionic liquids, *Diam. Relat. Mater.* 51 (2015) 1–6. doi:10.1016/j.diamond.2014.10.009.
- [24] F. Gao, M.T. Wolfer, C.E. Nebel, Highly porous diamond foam as a thin-film micro-supercapacitor material, *Carbon.* 80 (2014) 833–840. doi:10.1016/j.carbon.2014.09.007.

- [25] K. Siuzdak, R. Bogdanowicz, M. Sawczak, M. Sobaszek, Enhanced capacitance of composite TiO<sub>2</sub> nanotube/boron-doped diamond electrodes studied by impedance spectroscopy, *Nanoscale*. 7 (2014) 551–558. doi:10.1039/C4NR04417G.
- [26] Y.-G. Lu, S. Turner, J. Verbeeck, S.D. Janssens, P. Wagner, K. Haenen, G.V. Tendeloo, Direct visualization of boron dopant distribution and coordination in individual chemical vapor deposition nanocrystalline B-doped diamond grains, *Appl. Phys. Lett.* 101 (2012) 041907. doi:10.1063/1.4738885.
- [27] R. Bogdanowicz, A. Fabiańska, L. Golunski, M. Sobaszek, M. Gnyba, J. Ryl, K. Darowicki, T. Ossowski, S.D. Janssens, K. Haenen, E.M. Siedlecka, Influence of the boron doping level on the electrochemical oxidation of the azo dyes at Si/BDD thin film electrodes, *Diam. Relat. Mater.* 39 (2013) 82–88. doi:10.1016/j.diamond.2013.08.004.
- [28] R.M. Reis, J.A.F. Baio, F.L. Migliorini, R. da S. Rocha, M.R. Baldan, N.G. Ferreira, M.R. de V. Lanza, Degradation of dipyrone in an electrochemical flow-by reactor using anodes of boron-doped diamond (BDD) supported on titanium, *J. Electroanal. Chem.* 690 (2013) 89–95. doi:10.1016/j.jelechem.2012.12.003.
- [29] F.L. Souza, T.Q. Teodoro, V.M. Vasconcelos, F.L. Migliorini, P.C.F. Lima Gomes, N.G. Ferreira, M.R. Baldan, R.L.A. Haiduke, M.R.V. Lanza, Electrochemical oxidation of imazapyr with BDD electrode in titanium substrate, *Chemosphere*. 117 (2014) 596–603. doi:10.1016/j.chemosphere.2014.09.051.
- [30] Y. Chen, J. Mao, Sol–gel preparation and characterization of black titanium oxides Ti<sub>2</sub>O<sub>3</sub> and Ti<sub>3</sub>O<sub>5</sub>, *J. Mater. Sci. Mater. Electron.* 25 (2014) 1284–1288. doi:10.1007/s10854-014-1723-7.
- [31] V.P. Godbole, G.S. Kim, M.A. Dar, Y.S. Kim, H.K. Seo, G. Khang, H.S. Shin, Hot filament chemical vapour deposition processing of titanate nanotube coatings, *Nanotechnology*. 16 (2005) 1186. doi:10.1088/0957-4484/16/8/035.
- [32] X. Sun, Y. Li, Synthesis and Characterization of Ion-Exchangeable Titanate Nanotubes, *Chem. – Eur. J.* 9 (2003) 2229–2238. doi:10.1002/chem.200204394.
- [33] S. Ghodbane, D. Ballutaud, F. Omnès, C. Agnès, Comparison of the XPS spectra from homoepitaxial {111}, {100} and polycrystalline boron-doped diamond films, *Diam. Relat. Mater.* 19 (2010) 630–636. doi:10.1016/j.diamond.2010.01.014.
- [34] J. Ryl, R. Bogdanowicz, P. Slepski, M. Sobaszek, K. Darowicki, Dynamic Electrochemical Impedance Spectroscopy (DEIS) as a Tool for Analyzing Surface Oxidation Processes on Boron-Doped Diamond Electrodes, *J. Electrochem. Soc.* 161 (2014) H359–H364. doi:10.1149/2.016406jes.
- [35] V.P. Godbole, G.S. Kim, M.A. Dar, Y.S. Kim, H.K. Seo, G. Khang, H.S. Shin, Hot filament chemical vapour deposition processing of titanate nanotube coatings, *Nanotechnology*. 16 (2005) 1186. doi:10.1088/0957-4484/16/8/035.
- [36] D.O. Scanlon, C.W. Dunnill, J. Buckeridge, S.A. Shevlin, A.J. Logsdail, S.M. Woodley, C.R.A. Catlow, M.J. Powell, R.G. Palgrave, I.P. Parkin, G.W. Watson, T.W. Keal, P. Sherwood, A. Walsh, A.A. Sokol, Band alignment of rutile and anatase TiO<sub>2</sub>, *Nat. Mater.* 12 (2013) 798–801. doi:10.1038/nmat3697.
- [37] A.R. González-Elipe, G. Munuera, J.P. Espinos, J.M. Sanz, Compositional changes induced by 3.5 keV Ar<sup>+</sup> ion bombardment in Ni-Ti oxide systems: A comparative study, *Surf. Sci.* 220 (1989) 368–380. doi:10.1016/0039-6028(89)90239-2.
- [38] A.R. González-Elipe, G. Munuera, J.P. Espinos, J.M. Sanz, Compositional changes induced by 3.5 keV Ar<sup>+</sup> ion bombardment in Ni-Ti oxide systems: A comparative study, *Surf. Sci.* 220 (1989) 368–380. doi:10.1016/0039-6028(89)90239-2.

- [39] Y. Cheng, Y.F. Zheng, Characterization of TiN, TiC and TiCN coatings on Ti–50.6 at.% Ni alloy deposited by PIII and deposition technique, *Surf. Coat. Technol.* 201 (2007) 4909–4912. doi:10.1016/j.surfcoat.2006.07.216.
- [40] R. Hahn, F. Schmidt-Stein, J. Salonen, S. Thiemann, Y. Song, J. Kunze, V.-P. Lehto, P. Schmuki, Semimetallic TiO<sub>2</sub> Nanotubes, *Angew. Chem.* 121 (2009) 7372–7375. doi:10.1002/ange.200902207.
- [41] T. Kondo, Y. Kodama, S. Ikezoe, K. Yajima, T. Aikawa, M. Yuasa, Porous boron-doped diamond electrodes fabricated via two-step thermal treatment, *Carbon.* 77 (2014) 783–789. doi:10.1016/j.carbon.2014.05.082.
- [42] S.-C. Li, Z. Zhang, D. Sheppard, B.D. Kay, J.M. White, Y. Du, I. Lyubinetsky, G. Henkelman, Z. Dohnálek, Intrinsic Diffusion of Hydrogen on Rutile TiO<sub>2</sub>(110), *J. Am. Chem. Soc.* 130 (2008) 9080–9088. doi:10.1021/ja8012825.
- [43] H. Zhou, Y. Zhang, Electrochemically Self-Doped TiO<sub>2</sub> Nanotube Arrays for Supercapacitors, *J. Phys. Chem. C.* 118 (2014) 5626–5636. doi:10.1021/jp4082883.
- [44] M. Salari, K. Konstantinov, H.K. Liu, Enhancement of the capacitance in TiO<sub>2</sub> nanotubes through controlled introduction of oxygen vacancies, *J. Mater. Chem.* 21 (2011) 5128–5133. doi:10.1039/C0JM04085A.
- [45] D. Zhang, J. Li, J. Zheng, Synthesis and electrochemical properties of PANI–TiC nanocomposite and its electrocatalytic behavior, *Mater. Lett.* 93 (2013) 99–102. doi:10.1016/j.matlet.2012.11.054.
- [46] Y.-T. Weng, H.-A. Pan, N.-L. Wu, G.Z. Chen, Titanium carbide nanocube core induced interfacial growth of crystalline polypyrrole/polyvinyl alcohol lamellar shell for wide-temperature range supercapacitors, *J. Power Sources.* 274 (2015) 1118–1125. doi:10.1016/j.jpowsour.2014.10.158.
- [47] M. Arulepp, J. Leis, M. Lätt, F. Miller, K. Rumma, E. Lust, A.F. Burke, The advanced carbide-derived carbon based supercapacitor, *J. Power Sources.* 162 (2006) 1460–1466. doi:10.1016/j.jpowsour.2006.08.014.



*List of figure and table captions:*

**Figure 1.** Formation scheme of composite TiO<sub>2</sub> nanotubes / boron-doped diamond electrode.

**Figure 2.** SEM image of composite BDD-TiO<sub>2</sub> NTs electrode (left image): (a) top view of electrode with partially removed BDD layer and (b) cross section image showing top BDD layer and titania nanotubes overgrown with semispherical nanostructures; (c) Raman spectra recorded for top BDD layer (R1) and TiO<sub>2</sub> NTs layer (R2).

**Figure 3.** Raman spectra recorded for TiO<sub>2</sub> NTs processed in carbon free plasma (a) and diamond deposition process (b).

**Figure 4.** The high-resolution C1s spectra carried out for thin BDD film grown on TiO<sub>2</sub> NTs with 2k and 10k [B]/[C] ratio.

**Figure 5.** Cyclic voltammetry curves: (a) the composite electrodes TiO<sub>2</sub>NTs /BDD-10k, pure titania and BDD layer immersed in 0.1 M NaNO<sub>3</sub> ( $v = 50$  mV/s), (b)The plots of peak currents versus the square root of the scan rate for different BDD covered electrodes.

**Table 1.** Raman bands positions for un-processed and plasma processed TiO<sub>2</sub> NTs.

**Table 2.** Percentage contribution (in at.%), binding energy of core levels (in eV) and FWHM (in eV) of each C1s peak for BDD grown on TiO<sub>2</sub> NTs with 2k and 10k [B]/[C] ratio.